

Table 1 presents the complete assay results, and Table 2 presents the technical data.

Hole #	From (m)	To (m)	Hole length (m)	True thickness (m)	Cu (%)*	Zn (%)*	Au (g/t)*	Ag (g/t)*
1274-16-223	358.1	358.8	0.7	0.3	0.002	2.17	0.01	2.50
1274-16-224	120.0	161.5	41.5	17.2	2.75	0.03	0.61	6.34
1274-16-224	403.0	406.6	3.6	1.8	0.84	14.08	0.05	237.43
1274-16-225	383.4	394.0	10.6	4.6	0.003	1.09	0.01	4.16
1274-16-226	499.4	515.9	16.5	6.3	0.75	6.40	0.21	49.20
including	502.25	507.40	5.15	2.0	0.77	10.18	0.23	54.28
1274-16-227	193.9	196.5	2.6	1.3	3.69	0.02	0.46	13.84
1274-16-227	306.85	307.20	0.35	0.2	0.003	8.50	0.04	11.10
1274-16-228	78.7	97.0	18.3	7.5	1.52	0.03	0.10	3.11
1274-16-228	358.5	366.7	8.2	4.2	1.01	12.92	0.08	354.82
including	363.3	366.7	3.4	1.8	0.70	21.15	0.13	526.59
1274-16-229	202.0	204.5	2.5	1.1	2.68	1.28	0.14	17.82
1274-16-230	839.25	845.00	5.75	2.81	0.02	1.10	0.03	8.00
1274-16-231	770.3	771.6	1.3	0.8	0.46	18.25	0.41	35.43
1274-16-232	441.5	442.9	1.4	0.6	0.63	9.96	0.10	79.76
1274-16-232	529.0	536.0	7.0	2.9	0.01	1.11	0.62	723.95
1274-16-233	524.3	532.0	7.7	2.8	0.07	7.70	0.26	64.76
1274-16-234	670.8	674.0	3.2	1.9	2.57	0.03	0.11	8.30
1274-16-235	147.8	152.5	4.7	1.5	3.44	0.11	0.18	8.33
1274-16-235	180.7	188.9	8.2	2.7	2.60	0.03	0.30	5.57
including	185.5	188.9	3.4	1.1	4.72	0.05	0.57	10.43
1274-16-235	520.65	533.50	12.85	4.4	0.30	6.68	0.04	61.72
1274-16-236	1079.4	1120.5	41.1	22.2	1.38	0.01	0.25	1.95
inquant	1079.4	1086.5	7.1	3.8	4.69	0.03	0.50	5.52
inquant	1116.5	1120.5	4.0	2.3	3.38	0.01	1.33	5.49
1274-16-236	1168.5	1169.65	1.15	0.7	0.10	4.89	0.24	18.91
1274-16-237	117.0	173.8	56.8	22.7	1.81	0.04	0.30	4.22
inquant	118.0	123.4	5.4	2.1	6.77	0.07	0.78	20.78
1274-16-237	422.20	425.45	3.25	1.5	0.18	7.66	0.03	36.62
1274-16-238	175.0	189.4	14.4	4.3	2.32	0.01	0.45	2.75
including	175.0	178.9	3.9	1.2	4.52	0.02	0.82	5.22
1274-16-238	600.2	605.8	5.6	1.7	0.17	9.09	0.19	585.27
1274-16-239	1111.0	1113.0	2.0	1.0	2.73	0.01	0.05	8.72
1274-16-239	1154.4	1158.1	3.7	1.9	0.17	6.38	0.11	32.33
1274-16-239	1190.8	1191.1	0.3	0.2	0.16	12.65	0.57	583.00
1274-16-240	156.9	189.2	32.3	11.5	1.43	0.01	0.34	2.20
including	181.0	189.2	8.2	3.0	4.09	0.01	1.05	6.46
1274-16-240	505.80	508.65	2.85	1.2	0.02	6.12	0.06	150.14
1274-16-241	813.0	826.0	13.0	6.8	1.63	0.03	0.66	6.43
including	822.0	826.0	4.0	2.1	2.46	0.02	0.33	10.31

Table 1: Drilling intersections – March to July 2016

*Uncut, preliminary assay content, check assays in progress

Hole #	Easting UTM NAD83 z17	Northing UTM NAD83 z17	Elevation	Azimuth	Dip	Final depth (m)
1274-16-223	651959.6	5513587.5	275.8	180	-67	525
1274-16-224	652964.4	5513528.5	274.6	180	-66	613
1274-16-225	652029.0	5513584.0	273.9	180	-67	477
1274-16-226	652964.4	5513528.5	274.6	180	-70	718
1274-16-227	652105.5	5513577.9	274.0	180	-60	412
1274-16-228	653004.3	5513514.3	274.2	180	-65	757
1274-16-229	652105.5	5513577.9	274.0	180	-66	436
1274-16-230	652900.4	5513683.3	272.7	189	-70	1050
1274-16-230A	652900.4	5513683.3	272.7	183	-70	67
1274-16-231	653010.8	5513682.1	271.1	194	-69	934
1274-16-231A	653010.8	5513682.1	271.1	189.5	-72	274.6
1274-16-232	653004.3	5513514.3	274.2	187	-70	643
1274-16-233	653019.5	5513527.4	273.7	181	-70	658
1274-16-233A	653019.5	5513527.4	273.7	181	-70	36
1274-16-233B	653019.5	5513527.4	273.7	176.6	-74	36
1274-16-234	653249.5	5513707.5	268.4	183.6	-66	979.6
1274-16-235	652964.4	5513528.5	274.6	196	-70	685
1274-16-236	652345.7	5513888.5	271.1	186	-72	1533
1274-16-237	652964.4	5513528.5	274.6	196	-65	583
1274-16-238	652860.5	5513528.5	277.8	183	-71	799
1274-16-239	652856.0	5513854.9	270.4	185	-70	1350
1274-16-240	652860.5	5513528.5	277.8	185	-68.5	619
1274-16-241	652692.3	5513774.4	272.7	184	-69	1163.4

Table 2: Technical drilling data (A or B = abandoned drill hole)