


Graph of recovery curves for 19 column tests (sulphide sample GS-03 not shown)



*Weighted average gold extraction is obtained using the following equation: $(\text{composite head grade (g/t)} \times \text{extraction (\%)}) / \text{sum of all head grades}$. Using arithmetic averages tend to over-represent low grade composites and under-represent high grade composites. The arithmetic average of the 24 coarse bottle rolls is 77.5%. The arithmetic average of the 20 column tests is 81.3%.