

Appendix – Selected Stage 2 drill results (latest results shaded)

Drill Hole	From m	To m	Interval m	La ₂ O ₃ ppm	Ce ₂ O ₃ ppm	Pr ₂ O ₃ ppm	Nd ₂ O ₃ ppm	Sm ₂ O ₃ ppm	Eu ₂ O ₃ ppm	Gd ₂ O ₃ ppm	Tb ₂ O ₃ ppm	Dy ₂ O ₃ ppm	Y ₂ O ₃ ppm	Other ¹ ppm	TREO ² %	Nb ₂ O ₅ %	% HREO ³ + Y ₂ O ₃
PX006	100.0	130.4	30.4	3,255	7,318	859	3,096	531	154	382	47	217	883	159	1.7%	0.04%	10.9%
PX007a	51.9	97.3	45.5 (i)	3,615	7,916	930	3,392	475	133	312	39	194	847	163	1.8%	0.22%	9.4%
(i) Includes two cavities totalling 9.4m not sampled.																	
PX008	26.1	191.9	165.8	3,532	5,894	601	1,934	262	70	168	19	87	444	91	1.3%	0.16%	6.7%
	257.0	291.0	34.0	4,108	8,137	900	3,208	457	108	223	22	93	452	77	1.8%	0.04%	5.5%
	318.9	339.0	20.1	6,002	9,220	912	2,944	378	99	230	29	152	807	152	2.1%	0.17%	7.0%
PX013	5.7	72.2	66.5 (i)	6,924	10,801	1,005	2,978	319	85	196	24	117	514	93	2.3%	0.20%	4.5%
including	21.1	39.2	18.1	9,950	15,126	1,375	3,980	404	106	236	28	133	593	109	3.2%	0.15%	3.8%
	44.6	54.8	10.2	12,157	17,333	1,491	4,132	395	102	225	26	114	466	83	3.7%	0.23%	2.8%
(i) Includes 5.3m cavity not sampled.																	
PX014	142.0	181.1	39.1	4,481	7,605	770	2,535	336	92	222	27	128	534	103	1.7%	0.26%	6.6%
PX015	20.1	97.8	77.8	2,687	5,048	522	1,793	248	71	183	25	135	652	131	1.1%	0.10%	10.4%
including	82.0	92.0	10.0	5,957	8,954	803	2,557	309	88	211	28	136	611	123	2.0%	0.16%	6.1%
PX016	322.7	363.6	40.9	3,681	7,705	874	3,125	435	121	281	37	191	1,001	223	1.8%	0.16%	10.5%
PX017a	-	39.1	39.1	5,353	8,445	846	2,676	373	107	249	32	147	659	134	1.9%	0.16%	7.0%
including	-	13.5	13.5	11,170	16,233	1,536	4,562	594	165	379	44	190	804	155	3.6%	0.21%	4.8%

¹ Other comprises Ho₂O₃, Er₂O₃, Tm₂O₃, Yb₂O₃ and Lu₂O₃; ² TREO: total rare earth oxides including yttrium; ³ HREO defined here as oxides of Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb & Lu

Drill Hole	From m	To m	Interval m	La ₂ O ₃ ppm	Ce ₂ O ₃ ppm	Pr ₂ O ₃ ppm	Nd ₂ O ₃ ppm	Sm ₂ O ₃ ppm	Eu ₂ O ₃ ppm	Gd ₂ O ₃ ppm	Tb ₂ O ₃ ppm	Dy ₂ O ₃ ppm	Y ₂ O ₃ ppm	Other ¹ ppm	TREO ² %	Nb ₂ O ₅ %	% HREO ³ + Y ₂ O ₃	
PX017b	10.4	25.6	15.3	4,825	8,378	903	3,310	507	129	288	29	137	701	129	1.9%	0.09%	7.3%	
	42.3	100.8	58.4	3,780	6,895	746	2,697	379	97	215	23	110	551	109	1.6%	0.18%	7.1%	
including	77.3	97.8	20.5	5,213	8,973	927	3,246	424	113	261	31	155	752	149	2.0%	0.25%	7.2%	
PX018	9.0	56.3	47.3	6,290	10,224	1,028	3,209	420	118	278	31	146	540	98	2.2%	0.12%	5.4%	
	102.8	116.4	13.6	5,608	9,136	941	3,208	487	141	318	37	160	611	111	2.1%	0.17%	6.6%	
	125.6	225.4	99.8	2,745	5,378	603	2,137	303	79	169	18	75	328	63	1.2%	0.10%	6.2%	
including	125.6	164.3	38.7	3,444	6,490	718	2,569	382	105	228	25	106	442	86	1.5%	0.14%	6.8%	
	236.0	260.2	24.2	2,928	5,421	586	2,032	291	75	163	16	71	343	68	1.2%	0.10%	6.1%	
PX019	6.1	76.3	70.2	2,457	4,878	533	1,853	269	81	206	30	162	784	156	1.1%	0.03%	12.4%	
PX020	4.2	100.0	95.8	3,918	7,432	795	2,800	409	110	248	28	127	556	107	1.7%	0.14%	7.1%	
	147.2	195.2	48.0	4,127	6,883	686	2,318	330	89	215	23	101	389	70	1.5%	0.18%	5.8%	
	215.0	347.0	132.0	2,984	5,845	656	2,327	371	103	245	28	124	575	121	1.3%	0.20%	8.9%	
PX021	5.7	106.5	100.8	3,742	7,295	804	2,894	436	120	274	35	165	792	149	1.7%	0.20%	9.2%	
	117.0	171.0	54.0	3,935	7,380	788	2,726	392	104	220	24	116	508	92	1.6%	0.17%	6.5%	
	184.9	211.5	26.5	2,861	5,817	688	2,551	385	111	254	29	144	703	124	1.4%	0.33%	10.0%	
PX022a	11.6	73.2	61.7	(i)	2,671	5,933	700	2,700	419	116	258	32	162	774	143	1.4%	0.17%	10.7%
including	37.0	68.0	31.0	(i)	3,362	7,274	825	3,068	441	123	281	37	193	930	175	1.7%	0.25%	10.4%
	88.0	103.7	15.7		3,576	7,919	904	3,394	514	135	296	34	161	731	142	1.8%	0.21%	8.4%

(i) Includes 5.7m cavity not sampled.

¹ Other comprises Ho₂O₃, Er₂O₃, Tm₂O₃, Yb₂O₃ and Lu₂O₃; ² TREO: total rare earth oxides including yttrium; ³ HREO defined here as oxides of Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb & Lu

Drill Hole	From m	To m	Interval m	La ₂ O ₃ ppm	Ce ₂ O ₃ ppm	Pr ₂ O ₃ ppm	Nd ₂ O ₃ ppm	Sm ₂ O ₃ ppm	Eu ₂ O ₃ ppm	Gd ₂ O ₃ ppm	Tb ₂ O ₃ ppm	Dy ₂ O ₃ ppm	Y ₂ O ₃ ppm	Other ¹ ppm	TREO ² %	Nb ₂ O ₅ %	% HREO ³ + Y ₂ O ₃
PX022b	15.0	347.7	332.7	3,224	6,190	690	2,510	357	96	219	26	124	590	122	1.4%	0.15%	8.3%
including	49.1	89.5	40.4	2,776	6,069	719	2,652	381	109	258	34	172	831	162	1.4%	0.17%	11.1%
	112.5	195.0	82.5	3,901	7,133	768	2,745	385	102	223	25	119	566	122	1.6%	0.08%	7.2%
	202.0	229.0	27.0	4,363	8,148	856	3,096	414	110	259	32	142	659	135	1.8%	0.16%	7.3%
	235.5	347.7	112.2	3,627	6,710	741	2,665	370	100	229	27	124	572	124	1.5%	0.20%	7.7%
PX025	89.4	117.0	27.6	3,724	7,801	895	3,308	455	124	280	33	159	692	127	1.8%	0.25%	8.0%
PX026	163.6	190.1	26.5	2,409	4,702	537	1,919	341	101	249	28	132	544	95	1.1%	0.10%	10.4%
	243.0	271.9	28.9	3,071	5,753	610	2,140	309	79	171	17	74	316	59	1.3%	0.12%	5.7%
PX028	10.7	145.0	134.3	5,215	8,379	836	2,769	379	103	243	28	120	489	88	1.9%	0.14%	5.7%
including	40.3	108.0	67.7	6,668	10,344	1,018	3,337	437	116	265	30	130	531	94	2.3%	0.13%	5.1%
	159.0	188.0	29.0	2,621	5,290	604	2,189	363	106	256	29	138	686	137	1.2%	0.13%	10.9%
PX029	4.6	117.3	112.7	4,568	7,728	791	2,621	357	94	212	25	124	548	114	1.7%	0.16%	6.5%
including	5.6	30.2	24.6	7,052	10,968	1,054	3,265	398	100	226	26	128	541	114	2.4%	0.22%	4.8%
PX032	2.5	167.0	164.5	2,567	5,021	576	2,024	311	85	205	26	125	630	130	1.2%	0.17%	10.3%
including	2.5	48.6	46.1	3,548	6,809	781	2,715	398	108	267	37	188	1,015	217	1.6%	0.30%	11.4%
PX033	4.2	101.0	96.8 (i)	4,005	7,004	731	2,539	379	103	247	30	136	596	114	1.6%	0.18%	7.7%
including	42.0	84.3	42.3	5,920	9,323	914	2,968	411	110	258	30	132	552	102	2.1%	0.15%	5.7%

(i) Includes 2.2m cavity not sampled.

¹ Other comprises Ho₂O₃, Er₂O₃, Tm₂O₃, Yb₂O₃ and Lu₂O₃; ² TREO: total rare earth oxides including yttrium; ³ HREO defined here as oxides of Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb & Lu

Drill Hole	From m	To m	Interval m	La ₂ O ₃ ppm	Ce ₂ O ₃ ppm	Pr ₂ O ₃ ppm	Nd ₂ O ₃ ppm	Sm ₂ O ₃ ppm	Eu ₂ O ₃ ppm	Gd ₂ O ₃ ppm	Tb ₂ O ₃ ppm	Dy ₂ O ₃ ppm	Y ₂ O ₃ ppm	Other ¹ ppm	TREO ² %	Nb ₂ O ₅ %	% HREO ³ + Y ₂ O ₃
PX034	13.0	34.5	21.5	4,664	7,779	756	2,450	322	92	231	30	140	561	108	1.7%	0.15%	6.8%
	47.0	126.0	79.0	5,030	7,522	692	2,148	271	75	180	23	112	489	92	1.7%	0.17%	5.8%
including	89.0	102.2	13.2	9,108	13,724	1,256	3,861	451	120	282	38	192	945	181	3.0%	0.12%	5.8%
	155.0	199.9	44.9	4,024	6,669	697	2,354	311	85	210	26	132	580	116	1.5%	0.11%	7.6%
	241.4	269.0	27.6	2,356	4,603	479	1,663	251	73	186	27	142	663	130	1.1%	0.10%	11.5%
PX035	-	96.3	96.3 (i)	3,390	6,589	731	2,570	373	107	254	32	156	741	158	1.5%	0.22%	9.6%
including	41.5	66.5	25.0	3,940	7,877	890	3,165	465	130	303	37	176	810	162	1.8%	0.27%	9.0%
	72.3	95.0	22.7	4,204	8,368	930	3,222	428	121	285	35	160	611	130	1.8%	0.21%	7.3%

(i) Includes 2.6m cavity not sampled.

¹ Other comprises Ho₂O₃, Er₂O₃, Tm₂O₃, Yb₂O₃ and Lu₂O₃; ² TREO: total rare earth oxides including yttrium; ³ HREO defined here as oxides of Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb & Lu