



Blue highlighted sections contain holes announced in latest release. Please see sections for assay intervals.



Hole ID	From (m)	To (m)	Interval (m)	Gold (g/t)	Silver (g/t)	Gold Eq (g/t)
TU-10-011	122.70	124.20	1.50	0.65	229.8	5.2
TU-10-011	185.09	185.64	0.55	1.13	405.7	9.2
TU-10-011	204.98	408.63	203.65	1.01	44.3	1.9
including	207.82	208.40	0.58	1.27	274.5	6.8
including	223.05	224.50	1.45	3.02	284.7	8.7
including	241.03	242.94	1.91	6.72	551.5	17.8
including	255.42	338.50	83.08	1.83	77.7	3.4
including	258.68	260.45	1.77	48.98	1391.7	76.8
including	279.23	280.63	1.40	7.82	560.3	19.0
including	292.93	296.34	3.41	2.91	133.9	5.6
including	303.09	306.90	3.81	2.79	113.1	5.1
including	333.85	336.36	2.51	6.30	237.1	11.0
TU-10-013	64.90	89.00	24.10	1.43	99.0	3.4
TU-10-013	193.65	201.33	7.68	0.21	19.2	0.6
TU-10-013	212.80	213.42	0.62	2.72	269.0	8.1
TU-10-013	289.50	289.92	0.42	6.67	304.0	13.8
TU-10-013	420.01	420.42	0.41	5.54	35.7	6.3
TU-10-013	426.62	427.70	1.08	1.69	37.2	2.4
TU-11-016	208.00	409.35	201.35	0.99	86.2	2.7
including	208.00	237.19	29.19	0.67	105.7	2.8
including	235.30	237.19	1.89	3.68	776.1	19.2
including	256.48	286.60	30.12	1.62	187.9	5.4
including	269.28	273.68	4.40	4.33	577.3	15.9
including	270.68	272.68	2.00	6.78	1038.5	27.5
including	281.79	282.84	1.05	18.15	2250.0	63.2
including	317.20	351.48	34.28	1.73	95.2	3.6
including	326.32	329.34	3.02	6.13	601.9	18.2
including	338.91	349.10	10.19	2.85	72.4	4.3
including	365.90	409.35	43.45	1.62	118.9	4.0
including	374.22	378.75	4.53	4.19	280.3	9.8
including	374.22	376.83	2.61	5.74	336.9	12.5
including	386.70	387.70	1.00	6.88	524.0	17.4
including	395.63	409.35	13.72	1.74	138.7	4.5
including	395.63	402.99	7.36	2.46	208.2	6.6
TU-11-016	439.00	443.00	4.00	1.11	13.0	1.4
TU-11-019	203.40	328.90	125.50	0.48	39.9	1.3
including	234.45	235.15	0.70	2.38	642.2	15.2
including	285.59	328.90	43.31	0.91	74.4	2.4
including	285.59	294.14	8.55	3.04	184.7	6.7
including	287.24	292.03	4.79	4.64	273.1	10.1
including	305.92	308.36	2.44	1.59	161.2	4.8
TU-11-019	369.20	372.12	2.92	3.45	418.9	11.8
TU-11-056	58.95	66.95	8.00	1.84	46.8	2.8
TU-11-056	72.54	106.60	34.06	1.63	56.2	2.8
including	73.25	78.50	5.25	5.26	77.7	6.8
including	85.65	86.65	1.00	5.95	412.5	14.2
including	92.65	100.00	7.35	1.88	100.8	3.9
TU-11-056	226.15	251.00	24.85	0.75	163.4	4.0
including	234.14	235.40	1.26	2.45	853.5	19.5
including	248.45	249.40	0.95	13.86	2576.8	65.4
TU-11-059	145.00	189.80	44.80	0.29	9.9	0.5
including	154.00	179.80	25.80	0.39	12.2	0.6
TU-11-059	277.08	277.88	0.80	0.99	112.2	3.2
TU-11-059	345.50	346.25	0.75	1.25	130.5	3.9
TU-11-059	356.50	367.95	11.45	0.33	8.1	0.5
TU-11-059	488.92	490.55	1.63	1.50	30.9	2.1
TU-11-059	522.40	534.22	11.82	0.22	3.8	0.3
TU-11-059	611.95	614.33	2.38	0.38	26.8	0.9
TU-11-059	617.97	624.82	6.85	0.44	33.8	1.1
including	618.17	620.33	2.16	0.76	60.9	2.0
TU-11-066	145.00	189.80	44.80	0.51	8.8	0.7
including	176.12	182.08	5.96	1.26	10.4	1.5
TU-11-078	3.59	76.50	72.91	0.65	28.5	1.2
including	24.50	54.50	30.00	1.24	50.5	2.3
including	37.00	48.00	11.00	2.04	100.8	4.1
TU-11-078	100.00	119.60	19.60	0.42	40.6	1.2
TU-11-078	150.00	173.00	23.00	0.72	44.0	1.6
including	155.00	167.42	12.42	1.11	70.5	2.5
including	163.70	167.42	3.72	1.84	154.8	4.9
TU-11-078	208.70	250.00	41.30	0.51	49.0	1.5
TU-11-083	55.45	60.80	5.35	0.33	38.4	1.1
TU-11-083	120.45	283.90	163.45	1.27	61.6	2.5
including	146.10	200.24	54.14	2.32	105.7	4.4
including	146.10	154.10	8.00	9.82	492.8	19.7
including	179.70	182.97	3.27	6.42	83.0	8.1
including	244.65	255.50	10.85	1.95	98.3	3.9
including	267.50	272.30	4.80	3.18	93.9	5.1
TU-11-088	109.00	113.00	4.00	0.37	50.8	1.4
TU-11-088	120.00	127.80	7.80	0.33	58.9	1.5
TU-11-088	150.40	170.50	20.10	0.32	26.7	0.9
including	167.62	170.50	2.88	1.41	103.8	3.5
TU-11-088	181.50	256.57	75.07	0.87	59.5	2.1
including	216.70	255.96	39.26	1.36	91.2	3.2
including	238.55	246.28	7.73	3.93	249.5	9.0
TU-12-125	332.00	351.50	19.50	1.20	64.1	2.5
TU-13-318	64.00	101.00	37.00	0.33	18.9	0.7
including	64.00	67.10	3.10	0.14	37.2	0.9
including	92.40	100.50	8.10	0.93	43.2	1.8
TU-13-318	109.50	141.00	31.50	1.51	62.0	2.7
including	121.40	133.80	12.40	3.52	122.4	6.0

Gold Equivalent (AuEq) is calculated using silver to gold ratios of 50 to 1.



Intervals Greater than 0.3 g/t AuEq

- 0.3 - 0.5
- 0.5 - 1.0
- 1.0 - 2.5
- 2.5 - 5.0
- 5.0 - 10.0
- >10.0


Assay results pending

Almaden Minerals
NYSE MKT: AAU
TSX: AMM

Section 10550E
Looking 60 degrees (+/- 12.5m)

0m 150m

Hole ID	From (m)	To (m)	Interval (m)	Gold (g/t)	Silver (g/t)	Gold Eq (g/t)
TU-11-015	138.30	276.00	137.70	0.82	28.4	1.4
including	138.30	150.59	12.29	6.16	40.4	7.0
including	139.70	142.00	2.30	31.46	69.4	32.8
including	197.87	200.46	2.59	1.68	148.0	4.6
including	253.66	259.86	6.20	1.29	122.5	3.7
including	258.68	259.86	1.18	3.49	237.5	8.2
TU-11-017	128.00	329.00	201.00	0.55	45.7	1.5
including	149.33	253.80	104.47	0.79	77.7	2.3
including	183.38	191.14	7.76	1.46	123.3	3.9
including	226.28	247.00	20.72	1.87	228.2	6.4
including	238.73	247.00	8.27	2.68	416.9	11.0
including	238.73	253.80	15.07	1.79	260.8	7.0
including	296.75	305.00	8.25	0.88	9.1	1.1
TU-11-048	35.84	74.63	38.79	0.49	44.0	1.4
including	37.00	44.00	7.00	1.70	148.5	4.7
TU-11-048	133.76	187.50	53.74	0.58	86.2	2.3
including	168.60	185.45	16.85	1.58	212.2	5.8
including	177.88	181.35	3.47	7.25	847.0	24.2
including	179.10	180.38	1.28	18.69	2129.0	61.3
TU-11-051	39.32	137.90	98.58	0.92	76.3	2.5
including	46.19	55.44	9.25	1.54	30.6	2.2
including	80.10	133.60	53.50	1.26	120.1	3.7
including	110.50	112.70	2.20	4.03	215.3	8.3
including	120.93	133.60	12.67	1.62	142.1	4.5
TU-11-079	160.00	178.15	18.15	0.37	12.4	0.6
TU-11-079	228.30	303.00	74.70	0.24	18.8	0.6
including	264.00	286.47	22.47	0.46	33.1	1.1
including	266.00	276.30	10.30	0.63	45.2	1.5
TU-11-082	157.28	398.30	241.02	0.43	31.2	1.0
including	221.82	238.14	16.32	1.27	80.3	2.9
including	340.00	341.14	1.14	4.54	405.4	12.6
including	359.32	384.68	25.36	1.21	91.5	3.0
including	359.32	361.62	2.30	6.88	463.5	16.1
TU-11-082	438.00	439.75	1.75	1.54	52.6	2.6
TU-11-091	3.05	13.00	9.95	0.49	12.2	0.7
TU-11-091	28.75	36.00	7.25	0.34	10.8	0.6
TU-11-091	84.10	97.95	13.85	0.79	105.5	2.9
TU-11-091	152.20	269.60	117.40	0.43	42.7	1.3
including	178.30	184.48	6.18	1.06	63.8	2.3
including	236.93	256.60	19.67	1.17	121.1	3.6
including	250.70	256.60	5.90	2.73	246.5	7.7
TU-11-095	12.20	80.10	67.90	0.24	20.6	0.6
including	74.55	79.60	5.05	0.92	89.2	2.7
TU-11-095	133.95	137.00	3.05	0.83	32.3	1.5
TU-11-095	149.25	167.23	17.98	0.50	36.4	1.2
TU-11-095	176.07	214.40	38.33	0.51	69.9	1.9
including	209.70	214.40	4.70	0.92	194.2	4.8
TU-12-138	43.50	87.27	43.77	0.59	4.3	0.7
including	61.00	71.50	10.50	0.88	4.9	1.0
including	84.00	87.27	3.27	2.07	10.5	2.3
TU-12-138	135.50	184.25	48.75	0.22	16.7	0.6
including	179.95	182.50	2.55	2.98	216.4	7.3
TU-12-138	202.00	359.50	157.50	0.36	41.4	1.2
including	264.30	359.50	95.20	0.54	61.1	1.8
including	292.50	302.00	9.50	1.27	234.3	6.0
including	304.00	307.00	3.00	3.87	439.9	12.7
TU-12-144	45.50	92.60	47.10	0.52	3.7	0.6
TU-12-144	210.00	258.00	48.00	0.52	32.0	1.2
including	227.40	235.80	8.40	1.68	59.3	2.9
TU-13-321	73.50	90.50	17.00	0.10	14.2	0.4
TU-13-321	103.50	128.50	25.00	0.60	49.1	1.6
including	117.25	127.00	9.75	0.97	46.5	1.9
TU-13-321	173.00	177.00	4.00	0.15	28.1	0.7
TU-13-321	182.50	227.99	45.49	0.81	57.9	2.0
including	182.50	196.80	14.30	1.61	140.0	4.4
including	182.50	187.50	5.00	2.61	180.0	6.2
including	192.50	195.60	3.10	1.30	298.8	7.3




Almaden Minerals
 NYSE MKT: AAU
 TSX: AMM

Section 10650E
 Looking 60 degrees (+/- 12.5m)

0m 150m

Gold Equivalent (AuEq) is calculated using silver to gold ratios of 50 to 1.



Hole ID	From (m)	To (m)	Interval (m)	Gold (g/t)	Silver (g/t)	Gold Eq (g/t)
TU-12-120	260.90	290.90	30.00	0.74	96.7	2.7
including	260.90	266.10	5.20	2.78	437.0	11.5
TU-12-124	116.50	301.50	185.00	1.00	60.5	2.2
including	167.50	181.40	13.90	6.04	179.7	9.6
TU-12-127	155.95	186.00	30.05	0.70	56.7	1.8
including	174.00	186.00	12.00	1.05	105.7	3.2
TU-12-127	210.00	233.50	23.50	1.02	20.2	1.4
including	213.90	218.30	4.40	3.92	86.0	5.6
TU-12-127	243.00	285.60	42.60	0.57	10.8	0.8
TU-12-127	297.00	314.00	17.00	0.38	8.7	0.6
TU-12-132	64.50	204.20	139.70	0.22	18.0	0.6
including	137.00	166.60	29.60	0.35	27.8	0.9
including	148.25	153.30	5.05	1.16	79.0	2.7
including	174.40	204.20	29.80	0.33	34.1	1.0
TU-12-136	63.10	123.60	60.50	0.84	48.9	1.8
including	82.20	93.00	10.80	1.10	85.2	2.8
including	98.00	110.50	12.50	1.84	98.5	3.8
TU-13-324	32.92	62.00	29.08	1.31	16.5	1.6
including	42.50	57.75	15.25	2.10	23.7	2.6
including	43.00	45.25	2.25	1.71	72.0	3.2
TU-13-324	113.50	128.00	14.50	0.25	47.0	1.2
including	120.00	121.00	1.00	0.59	117.5	2.9
including	125.00	128.00	3.00	0.79	155.0	3.9
TU-13-324	154.00	174.00	20.00	0.08	29.1	0.7
including	160.00	161.00	1.00	0.42	167.0	3.8
including	167.50	172.00	4.50	0.07	53.4	1.1
TU-13-325	128.50	136.50	8.00	0.58	132.2	3.2
TU-13-325	190.00	236.50	46.50	1.06	53.1	2.1
including	193.40	216.00	22.60	1.72	97.2	3.7
including	194.00	195.20	1.20	2.05	147.0	5.0
including	203.90	205.00	1.10	3.97	175.0	7.5
including	210.50	216.00	5.50	4.40	240.8	9.2

Intervals Greater than 0.3 g/t AuEq

- 0.3 - 0.5
- 0.5 - 1.0
- 1.0 - 2.5
- 2.5 - 5.0
- 5.0 - 10.0
- >10.0

Assay results pending

Almaden Minerals
NYSE MKT: AAU
 TSX: AMM

Section 10675E
 Looking 60 degrees (+/- 12.5m)

0m 150m

Gold Equivalent (AuEq) is calculated using silver to gold ratios of 50 to 1.