


Blue highlighted sections contain holes announced in latest release. Please see sections for assay intervals.




Intervals Greater than 0.3 g/t AuEq

Grey	0.3 - 0.5
Light Green	0.5 - 1.0
Orange	1.0 - 2.5
Red	2.5 - 5.0
Pink	5.0 - 10.0
Purple	>10.0

Assay results pending

0 200m
SCALE



Hole ID	From (m)	To (m)	Interval (m)	Gold (g/t)	Silver (g/t)	Gold Eq (g/t)
TU-12-234	28.30	73.00	44.70	0.65	4.1	0.7
including	65.40	71.00	5.60	1.00	6.7	1.1
TU-12-237	49.16	150.00	100.84	0.67	7.5	0.8
including	57.25	63.25	6.00	1.74	8.5	1.9
including	81.50	86.50	5.00	1.23	3.7	1.3
including	114.50	120.50	6.00	1.19	10.0	1.4
including	130.00	142.00	12.00	0.97	23.5	1.4
TU-12-239	30.48	54.25	23.77	0.50	6.2	0.6
TU-12-239	88.40	100.40	12.00	0.08	7.9	0.2
TU-12-241	30.48	67.05	36.57	0.46	4.9	0.6
including	44.00	51.21	7.21	0.98	11.5	1.2
TU-12-241	73.60	98.85	25.25	0.26	1.0	0.3
TU-12-241	107.85	127.41	19.56	0.30	8.9	0.5
TU-12-241	140.40	162.60	22.20	0.15	21.4	0.6
TU-12-241	185.50	200.65	15.15	0.11	39.5	0.9
including	189.00	189.60	0.60	0.50	356.0	7.6
including	199.15	199.65	0.50	0.94	415.0	9.2
TU-13-310	29.50	53.50	24.00	0.22	0.8	0.2
TU-13-310	75.50	148.00	72.50	0.74	4.7	0.8
including	86.00	107.00	21.00	1.39	3.5	1.5
including	123.00	126.00	3.00	1.09	9.2	1.3
TU-13-312	20.50	51.50	31.00	0.44	0.8	0.5
including	28.00	32.50	4.50	0.96	1.0	1.0
TU-13-312	62.00	157.00	95.00	0.67	4.3	0.8
including	77.50	101.00	23.50	1.34	6.7	1.5
TU-13-314	23.00	176.00	153.00	1.60	8.3	1.8
including	90.00	172.00	82.00	2.62	12.3	2.9
including	129.50	131.50	2.00	2.67	101.0	4.7
including	165.50	168.00	2.50	6.06	11.1	6.3
TU-13-320	31.00	35.00	4.00	0.64	0.0	0.6
TU-13-320	43.00	59.00	16.00	0.41	0.3	0.4
TU-13-320	73.00	98.00	25.00	0.43	0.7	0.4
TU-13-320	117.00	144.00	27.00	0.58	1.5	0.6
including	120.00	124.00	4.00	1.20	1.7	1.2
TU-13-320	151.50	161.50	10.00	0.58	1.3	0.6
TU-13-320	172.00	177.50	5.50	0.20	1.5	0.2

Gold Equivalent (AuEq) is calculated using silver to gold ratios of 50 to 1.

Intervals Greater than 0.3 g/t AuEq

- 0.3 - 0.5
- 0.5 - 1.0
- 1.0 - 2.5
- 2.5 - 5.0
- 5.0 - 10.0
- >10.0


* Denotes intervals less than 0.3 g/t AuEq

⊕ Assay results pending

Almaden Minerals
NYSE MKT: AAU
TSX: AMM

Section 11050E
Looking 60 degrees (+/- 25m)

0m 150m




CLAY ALTERED VOLCANICLASTICS

MINERALIZED VOLCANICLASTICS

CHEMALACO ZONE (NORTHEAST EXTENSION)

Intervals Greater than 0.3 g/t AuEq



Assay results pending

Reference Line

2400m

2200m


Hole ID	From (m)	To (m)	Interval (m)	Gold (g/t)	Silver (g/t)	Gold Eq (g/t)
TU-13-322	55.50	79.00	23.50	0.22	2.3	0.3
TU-13-326	56.00	98.00	42.00	0.34	5.1	0.4
TU-13-327	38.50	62.50	24.00	0.18	4.6	0.3
TU-13-329	53.00	91.00	38.00	0.24	1.7	0.3
TU-13-329	147.00	206.60	59.60	0.42	24.9	0.9
including	164.00	185.00	21.00	0.68	42.0	1.5
including	182.00	185.00	3.00	0.36	123.5	2.8

Gold Equivalent (AuEq) is calculated using silver to gold ratios of 50 to 1.

Almaden Minerals
 NYSE MKT: AAU
 TSX: AMM

Section 11100E
 Looking 60 degrees (+/- 12.5m)

0m 150m



CLAY ALTERED VOLCANICLASTICS

MINERALIZED VOLCANICLASTICS

CHEMALACO ZONE (NORTHEAST EXTENSION)

Reference Line

2400m


2200m

Intervals Greater than 0.3 g/t AuEq

- 0.3 - 0.5
- 0.5 - 1.0
- 1.0 - 2.5
- 2.5 - 5.0
- 5.0 - 10.0
- >10.0
- * Denotes intervals less than 0.3 g/t AuEq
- ⊕ Assay results pending




Section 11125E
Looking 60 degrees (+/- 12.5m)



Hole ID	From (m)	To (m)	Interval (m)	Gold (g/t)	Silver (g/t)	Gold Eq (g/t)
TU-13-331	21.00	24.50	3.50	0.21	0.3	0.2
TU-13-331	98.00	101.00	3.00	0.25	4.2	0.3
TU-13-331	119.00	121.00	2.00	0.19	4.0	0.3
TU-13-334	115.00	119.00	4.00	0.11	5.1	0.2
TU-13-334	159.00	166.00	7.00	0.44	12.8	0.7
including	160.00	161.00	1.00	2.13	55.7	3.2
TU-13-335	20.00	28.00	8.00	0.26	0.0	0.3
TU-13-335	98.00	106.50	8.50	0.24	6.8	0.4
TU-13-338	30.00	36.00	6.00	0.31	0.0	0.3
TU-13-338	81.00	97.00	16.00	0.50	1.8	0.5
TU-13-338	112.50	123.50	11.00	0.24	5.7	0.4

Gold Equivalent (AuEq) is calculated using silver to gold ratios of 50 to 1.



Hole ID	From (m)	To (m)	Interval (m)	Gold (g/t)	Silver (g/t)	Gold Eq (g/t)
TU-13-345	30.00	36.50	6.50	0.52	0.0	0.5
TU-13-345	66.50	72.00	5.50	0.24	0.0	0.2
TU-13-345	108.50	118.00	9.50	0.23	6.8	0.4
TU-13-348	87.00	96.00	9.00	0.44	0.8	0.5
TU-13-348	170.00	191.50	21.50	0.39	6.6	0.5
including	183.85	185.85	2.00	1.27	18.7	1.6
TU-13-350	96.93	112.17	15.24	0.32	1.8	0.4
TU-13-350	202.00	272.00	70.00	0.57	13.2	0.8
including	205.00	240.00	35.00	0.87	12.8	1.1
including	205.00	216.00	11.00	1.31	17.6	1.7
including	229.00	234.00	5.00	1.45	18.7	1.8
TU-13-356	30.48	34.48	4.00	0.44	0.0	0.4
TU-13-356	164.50	166.45	1.95	1.25	36.7	2.0
TU-13-358	36.00	42.00	6.00	0.61	0.0	0.6
TU-13-358	216.00	218.00	2.00	0.00	82.0	1.6

Intervals Greater than 0.3 g/t AuEq

- 0.3 - 0.5
- 0.5 - 1.0
- 1.0 - 2.5
- 2.5 - 5.0
- 5.0 - 10.0
- >10.0

* Denotes intervals less than 0.3 g/t AuEq


⊕ Assay results pending

Almaden Minerals
 NYSE MKT: AAU
 TSX: AMM

Section 11175E
 Looking 60 degrees (+/- 12.5m)

0m 150m

Gold Equivalent (AuEq) is calculated using silver to gold ratios of 50 to 1.



CLAY ALTERED VOLCANICLASTICS

MINERALIZED VOLCANICLASTICS

CHEMALACO ZONE (NORTHEAST EXTENSION)

Reference Line

2400m
2200m

Hole ID	From (m)	To (m)	Interval (m)	Gold (g/t)	Silver (g/t)	Gold Eq (g/t)
TU-13-250	69.00	118.70	49.70	0.29	9.4	0.5
including	91.70	112.20	20.50	0.58	12.4	0.8
including	102.70	108.70	6.00	0.88	18.1	1.2
TU-13-250	149.60	170.50	20.90	0.06	14.4	0.3
including	155.60	158.80	3.20	0.09	47.4	1.0
TU-13-252	64.80	98.00	33.20	0.41	9.9	0.6
TU-13-252	119.00	125.50	6.50	0.39	9.4	0.6
TU-13-252	133.50	136.50	3.00	0.29	4.9	0.4
TU-13-252	144.00	157.40	13.40	0.13	10.1	0.3
TU-13-255	77.00	107.50	30.50	0.25	13.3	0.5
including	78.90	84.00	5.10	0.88	37.1	1.6
TU-13-255	119.00	187.00	68.00	0.36	54.5	1.5
including	133.00	144.50	11.50	0.25	80.9	1.9
including	141.25	143.00	1.75	0.32	192.7	4.2
including	151.00	160.00	9.00	0.56	151.1	3.6
including	151.00	154.50	3.50	0.73	226.0	5.3
including	180.25	186.00	5.75	1.61	102.1	3.7
TU-13-255	191.00	198.50	7.50	0.20	13.7	0.5
TU-13-255	214.00	237.13	23.13	0.24	28.7	0.8
including	217.00	218.00	1.00	1.28	341.5	8.1
TU-13-258	88.00	97.00	9.00	0.12	18.1	0.5
TU-13-258	106.00	123.00	17.00	0.15	12.4	0.4
TU-13-258	164.50	262.65	98.15	0.33	28.1	0.9
including	182.00	184.00	2.00	0.45	58.2	1.6
including	192.50	198.50	6.00	0.32	34.4	1.0
including	205.50	209.00	3.50	0.55	34.3	1.2
including	223.50	243.50	20.00	0.61	77.0	2.2
including	223.50	234.25	10.75	0.77	95.4	2.7
including	240.50	243.50	3.00	0.90	120.9	3.3
including	242.00	243.00	1.00	1.53	224.5	6.0
TU-13-258	270.50	287.00	16.50	0.15	23.6	0.6
including	281.60	287.00	5.40	0.15	46.9	1.1
TU-13-363	119.00	138.50	19.50	0.22	8.0	0.4
TU-13-363	158.00	184.00	26.00	0.10	13.9	0.4
TU-13-363	197.50	200.56	3.06	0.06	8.3	0.2
TU-13-365	42.06	51.21	9.15	0.27	0.0	0.3

Intervals Greater than 0.3 g/t AuEq


- 0.3 - 0.5
- 0.5 - 1.0
- 1.0 - 2.5
- 2.5 - 5.0
- 5.0 - 10.0
- >10.0

* Denotes intervals less than 0.3 g/t AuEq


⊕ Assay results pending



Section 11225E
Looking 60 degrees (+/- 12.5m)



Gold Equivalent (AuEq) is calculated using silver to gold ratios of 50 to 1.



Intervals Greater than 0.3 g/t AuEq

- 0.3 - 0.5
- 0.5 - 1.0
- 1.0 - 2.5
- 2.5 - 5.0
- 5.0 - 10.0
- >10.0

Assay results pending


Almaden Minerals
 NYSE MKT: AAU
 TSX: AMM

Section 49675N
 Looking 340 degrees (+/- 12.5m)

0m 150m

Hole ID	From (m)	To (m)	Interval (m)	Gold (g/t)	Silver (g/t)	Gold Eq (g/t)
TU-13-317	23.00	100.25	77.25	0.41	3.5	0.5
including	81.50	87.50	6.00	0.83	5.6	0.9

Gold Equivalent (AuEq) is calculated using silver to gold ratios of 50 to 1.



Hole ID	From (m)	To (m)	Interval (m)	Gold (g/t)	Silver (g/t)	Gold Eq (g/t)
TU-12-229	37.00	72.50	35.50	0.78	6.5	0.9
including	43.00	56.00	13.00	1.40	11.0	1.6
including	68.50	72.50	4.00	1.31	4.5	1.4
TU-12-229	257.00	263.20	6.20	0.09	11.9	0.3
TU-12-229	325.00	330.30	5.30	0.29	4.7	0.4
TU-12-229	359.10	365.70	6.60	0.06	43.4	0.9
TU-12-232	42.67	54.70	12.03	0.65	8.2	0.8
TU-12-232	69.70	88.35	18.65	0.28	8.6	0.4
including	71.70	73.70	2.00	0.78	29.3	1.4
TU-12-232	298.80	305.90	7.10	0.06	12.6	0.3
TU-12-243	104.00	128.00	24.00	0.14	11.0	0.4
including	134.00	138.00	4.00	0.29	17.1	0.6
TU-12-246	12.19	63.70	51.51	0.45	11.9	0.7
including	12.19	19.50	7.31	1.03	20.1	1.4
TU-12-246	97.40	106.30	8.90	0.43	99.6	2.4
including	97.40	98.00	0.60	4.47	988.0	24.2
TU-12-246	208.50	214.00	5.50	0.79	112.1	3.0
including	211.00	213.00	2.00	1.72	225.0	6.2
TU-13-369	127.50	130.50	3.00	0.17	10.6	0.4
TU-13-369	149.00	168.00	19.00	0.43	22.3	0.9
TU-13-369	277.00	279.00	2.00	0.01	27.0	0.6

Gold Equivalent (AuEq) is calculated using silver to gold ratios of 50 to 1.

Intervals Greater than 0.3 g/t AuEq

- 0.3 - 0.5
- 0.5 - 1.0
- 1.0 - 2.5
- 2.5 - 5.0
- 5.0 - 10.0
- >10.0

* Denotes intervals less than 0.3 g/t AuEq

⊕ Assay results pending

Almaden Minerals
NYSE MKT: AAU
TSX: AMM

Section 49775N
Looking 340 degrees (+/- 25m)

0m 150m