



**Figure 1:** Plan view of the Degmen target area showing the location of recent exploration diamond drilling together with all drill hole intersections (0.33g/t AuEq cut-off), summary geology (PO1: early-mineralized porphyry, PO2: intra-mineral porphyry, PO3: late-porphyry dykes, VOL: andesitic volcanics) and topography. The section line relates to Figure 2. Note that the grid spacing is 500 meters.



**Figure 2:** Shows a representative south-southwest to north-northeast long-section (looking west) through the Degrmen target area highlighting the recently completed exploration diamond drill holes together with all drill hole intersections (0.33g/t AuEq cut-off) and summary geology based on Dunav's understanding to date (RED: early-mineralized porphyry (PO1), BROWN: intra-mineralized porphyry (PO2), PURPLE: late-porphyry dykes (PO3), YELLOW: andesitic volcanic pile). Note that gold-copper mineralization remains open at depth across a significant majority of the long-section. Grid spacing is 200 meters in the horizontal and 100 meters in the vertical.



**Figure 3:** Shows the location of the Degmen Porphyry Project relative to the Tulare Porphyry Project together with the well-developed infrastructure setting within the immediate Project area. Dunav exploration properties are outlined in blue.

**Table 1:** Degmen Gold-Copper Porphyry Significant Intervals – Phase 2 Diamond Drilling

Drilling Significant Intervals								
Degmen								
<i>0.33 g/t AuEq cut-off (\$1,400/oz Au &amp; \$3.30/lb Cu), 5m min. length, 5m max. internal dilution</i>								
Hole ID	EOH (m)	From (m)	To (m)	Interval (m)	Au (g/t)	Cu (%)	AuEq (g/t)	CuEq (%)
DGRDD012*	203.1	23.0	44.0	21.0	0.30	0.09	0.45	0.28
DGRDD012*		51.0	79.0	28.0	0.19	0.10	0.35	0.22
DGRDD012*		94.0	136.0	42.0	0.36	0.17	0.64	0.39
DGRDD012*		142.0	173.0	31.0	0.27	0.14	0.50	0.31
DGRDD012*		179.0	203.1	24.1	0.36	0.13	0.56	0.35
DGRDD013*	412.2	3.0	41.0	38.0	0.29	0.07	0.41	0.25
DGRDD013*		127.0	132.0	5.0	0.19	0.10	0.35	0.22
DGRDD013*		141.0	148.0	7.0	0.19	0.09	0.34	0.21
DGRDD013*		188.0	196.0	8.0	0.22	0.07	0.33	0.21
DGRDD013*		263.0	411.0	148.0	0.62	0.18	0.92	0.57
DGRDD014	449.2							
DGRDD015	404.5	35.0	179.0	144.0	0.37	0.13	0.58	0.36
DGRDD015		226.0	235.0	9.0	0.25	0.05	0.34	0.21
DGRDD015		275.0	390.0	115.0	0.36	0.11	0.53	0.33
DGRDD016	195.7	73.0	78.0	5.0	0.21	0.09	0.36	0.22
DGRDD016		129.0	153.0	24.0	0.26	0.10	0.43	0.26
DGRDD017	225.1	38.0	44.0	6.0	0.53	0.03	0.58	0.36
DGRDD018	203.0	72.0	80.0	8.0	0.32	0.12	0.51	0.32
DGRDD018		97.0	130.0	33.0	0.36	0.12	0.55	0.34
DGRDD018		189.0	201.0	12.0	0.22	0.08	0.34	0.21
DGRDD019	200.7	0.9	40.0	39.1	0.17	0.12	0.36	0.22
DGRDD019		47.0	93.1	46.1	0.21	0.13	0.42	0.26
DGRDD019		139.0	144.0	5.0	0.19	0.12	0.39	0.24
DGRDD019		150.0	175.0	25.0	0.14	0.13	0.36	0.22

- 0.33g/t AuEq cut-off (\$1,400/oz. Au, \$3.30/lb. Cu), 5m minimum composite length, 5m maximum internal dilution.
  - $\text{AuEq} = ((\text{Au g/t} * 45.01) + (\text{Cu%} * 72.75)) / 45.01$
  - $\text{CuEq} = ((\text{Cu%} * 72.75) + (\text{Au g/t} * 45.01)) / 72.75$
- Diamond drill samples are PQ, HQ or NQ half core, using a nominal 1m sampling basis and weigh ~3-6kg.
- Assay method: Fire assay Au (50g); Cu by aqua regia digestion with AAS finish.
- Intercept widths do not necessarily represent true width.
- No top cut applied.
- (\*) Drill hole terminates in mineralization i.e. mineralization remains open at depth.
- Refer to [www.dunavresources.com](http://www.dunavresources.com) for a full listing of significant intervals at various cut-off grades.