

Schedule 'A'

NOTE THAT ALL WIDTHS ARE CORE WIDTHS - NOT TRUE WIDTHS

Hole	Dip	Pad	FROM (m)	TO (m)	CORE WIDTH (m)	LENGTH WEIGHTED AVERAGE GRADE (%)														HREO/TREO Ratio (%)				
						La ₂ O ₃	Ce ₂ O ₃	Pr ₂ O ₃	Nd ₂ O ₃	Sm ₂ O ₃	Eu ₂ O ₃	Gd ₂ O ₃	Tb ₂ O ₃	Dy ₂ O ₃	Ho ₂ O ₃	Er ₂ O ₃	Tm ₂ O ₃	Yb ₂ O ₃	Lu ₂ O ₃		Y ₂ O ₃	LREO*	HREO**	TREO***
LM14-140	-64	14-05	236.50	238.96	2.46	0.072	0.166	0.020	0.075	0.016	0.002	0.014	0.002	0.011	0.002	0.005	0.001	0.004	0.000	0.062	0.348	0.102	0.451	22.62%
LM14-143	-65	14-9	259.71	261.70	1.99	0.075	0.164	0.020	0.075	0.017	0.002	0.016	0.003	0.017	0.003	0.009	0.001	0.007	0.001	0.097	0.350	0.156	0.507	30.77%
LM14-143	-65	14-9	336.12	340.41	4.29	0.081	0.176	0.022	0.087	0.021	0.002	0.021	0.004	0.024	0.005	0.013	0.002	0.010	0.001	0.130	0.386	0.212	0.599	35.39%
LM14-143	-65	14-9	348.50	351.50	3.00	0.098	0.195	0.024	0.092	0.019	0.002	0.021	0.004	0.030	0.007	0.022	0.003	0.020	0.003	0.213	0.429	0.327	0.755	43.31%
LM14-143	-65	14-9	364.69	366.43	1.74	0.094	0.239	0.030	0.121	0.030	0.003	0.028	0.005	0.029	0.006	0.015	0.002	0.012	0.001	0.175	0.514	0.277	0.790	35.06%
LM14-147	-45	14-16	174.72	176.55	1.83	0.053	0.127	0.015	0.055	0.011	0.001	0.008	0.001	0.005	0.001	0.002	0.000	0.001	0.000	0.023	0.261	0.042	0.303	13.86%
LM14-147	-45	14-16	183.67	189.58	5.91	0.083	0.229	0.029	0.121	0.032	0.003	0.032	0.006	0.034	0.006	0.015	0.002	0.009	0.001	0.178	0.494	0.286	0.779	36.71%
LM14-147	-45	14-16	207.00	209.18	2.18	0.104	0.251	0.032	0.124	0.026	0.002	0.022	0.003	0.016	0.003	0.006	0.001	0.004	0.000	0.077	0.537	0.133	0.670	19.85%
LM14-148	-60	14-9	250.45	252.74	2.29	0.118	0.278	0.035	0.144	0.041	0.004	0.048	0.009	0.056	0.011	0.029	0.004	0.021	0.002	0.331	0.616	0.516	1.132	45.59%
LM14-148	-60	14-9	267.69	270.30	2.61	0.042	0.107	0.013	0.050	0.013	0.001	0.015	0.003	0.020	0.004	0.012	0.002	0.010	0.001	0.135	0.224	0.204	0.428	47.66%
LM14-148	-60	14-9	289.40	291.70	2.30	0.073	0.169	0.021	0.080	0.021	0.002	0.025	0.005	0.031	0.007	0.019	0.003	0.014	0.002	0.190	0.364	0.297	0.661	44.93%
LM14-148	-60	14-9	317.68	320.10	2.42	0.027	0.064	0.008	0.031	0.009	0.001	0.011	0.002	0.014	0.003	0.007	0.001	0.005	0.001	0.079	0.139	0.123	0.262	46.95%
LM14-150	-59	14-9	119.45	121.50	2.05	0.029	0.064	0.008	0.031	0.009	0.001	0.011	0.002	0.013	0.003	0.008	0.001	0.006	0.001	0.075	0.140	0.121	0.261	46.36%
LM14-150	-59	14-9	233.86	236.78	2.92	0.088	0.204	0.026	0.105	0.028	0.003	0.031	0.006	0.034	0.006	0.017	0.002	0.011	0.001	0.198	0.451	0.309	0.760	40.66%
LM14-150	-59	14-9	239.61	241.60	1.99	0.048	0.113	0.015	0.059	0.015	0.001	0.014	0.003	0.015	0.003	0.007	0.001	0.005	0.001	0.083	0.250	0.132	0.382	34.55%
LM14-150	-59	14-9	262.29	265.00	2.71	0.032	0.077	0.010	0.039	0.010	0.001	0.011	0.002	0.011	0.002	0.006	0.001	0.004	0.000	0.064	0.167	0.101	0.268	37.69%
LM14-150	-59	14-9	275.18	277.63	2.45	0.131	0.309	0.035	0.139	0.035	0.004	0.041	0.008	0.048	0.010	0.027	0.004	0.020	0.002	0.307	0.649	0.471	1.120	42.05%
LM14-150	-59	14-9	285.15	287.24	2.09	0.107	0.281	0.034	0.132	0.030	0.003	0.026	0.004	0.023	0.004	0.011	0.001	0.007	0.001	0.126	0.582	0.207	0.789	26.24%
LM14-150	-59	14-9	306.37	308.78	2.41	0.032	0.081	0.011	0.043	0.011	0.001	0.011	0.002	0.012	0.002	0.006	0.001	0.004	0.000	0.067	0.177	0.107	0.284	37.68%

*Light Rare Earth Oxide (LREO) is the sum of the Light Rare Earth Oxide analyses (La₂O₃, Ce₂O₃, Pr₂O₃, Nd₂O₃ and Sm₂O₃)

**Heavy Rare Earth Oxide (HREO) is the sum of the Heavy Rare Earth Oxide analyses (Eu₂O₃, Gd₂O₃, Tb₂O₃, Dy₂O₃, Ho₂O₃, Er₂O₃, Tm₂O₃, Yb₂O₃, Lu₂O₃, plus Y₂O₃)

***Total Rare Earth Oxide (TREO) is the sum of the individual Rare Earth Oxide analyses (La₂O₃, Ce₂O₃, Pr₂O₃, Nd₂O₃, Sm₂O₃, Eu₂O₃, Gd₂O₃, Tb₂O₃, Dy₂O₃, Ho₂O₃, Er₂O₃, Tm₂O₃, Yb₂O₃, Lu₂O₃, plus Y₂O₃).

Note that totals may not agree due to rounding.