

Attachment 4 – 2007 Sabodala Project Reserves and Resources

Sabodala Resources (inclusive of reserves)

Cutoff (g/t)	Measured			Indicated			Measured+Indicated			Inferred		
	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)
0.40	33.8	1.62	1,760	12.2	1.48	581	46.0	1.58	2,341	6.1	1.23	241
0.60	26.3	1.94	1,640	9.1	1.83	535	35.4	1.91	2,176	3.9	1.64	206
0.80	21.3	2.23	1,527	7.0	2.17	488	28.3	2.22	2,015	2.8	2.02	182
1.00	17.7	2.50	1,423	5.7	2.46	451	23.4	2.49	1,873	2.2	2.33	165
1.50	11.7	3.16	1,189	3.9	3.01	377	15.6	3.12	1,566	1.3	3.05	127

Niakafiri Resources (inclusive of reserves)

Cutoff (g/t)	Measured			Indicated			Measured+Indicated			Inferred		
	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)
0.50	0.3	1.77	15	7.9	1.329	340	8.2	1.34	355	6.2	0.97	192
0.75	0.3	1.84	15	6.1	1.554	304	6.3	1.57	319	3.5	1.25	139

Sabodala Reserves

Cutoff (g/t)	Proven			Probable			Proven+Probable			Inferred		
	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)
1.00	11.56	2.74	1,019	2.0	2.81	182	13.6	2.75	1,201	0.07	2.28	5
0.8 - 1.0	1.98	0.90	57	0.2	0.90	7	2.2	1.91	64	0.01	0.90	0
Total	13.5	2.47	1,076	2.2	2.62	188	15.8	2.49	1,264	0.07	2.12	5

Niakafiri Reserves

	Cutoff (g/t)	Proven			Probable			Proven+Probable			Inferred		
		MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)
Oxide	0.56	0.1	2.01	7	1.8	1.71	100	1.9	1.73	107	0.20	1.28	8
Fresh	0.69	0.0	1.97	3	0.5	1.85	32	0.6	1.86	35	0.01	1.51	0
Total		0.2	1.99	10	2.4	1.74	132	2.5	1.76	142	0.21	1.29	9

The mineral reserves and mineral resources estimations reported above are documented in conformity with Canadian National Instrument 43-101. The estimations are based on a technical report that will be made available on SEDAR. Reserves are based on a US\$600 gold price and assume life-of-mine milling recoveries of 91.4% for Sabodala ore, 92% for Niakafiri oxide ore and 90% for Niakafiri fresh ore. Direct milling costs are expected to average \$13.52 per tonne Sabodala ore milled, \$11.61 per tonne Niakafiri fresh ore milled and \$9.53 per tonne Niakafiri oxide ore milled.