

DRILL HOLE ASSAY TABLES FOR RESULTS MENTIONED

GOLDEN RIDGE

GOLDEN RIDGE DRILL INTERSECTIONS ^(1,2)									
Hole No.	Easting	Northing	Azimuth	Dip	From (metres)	To (metres)	Interval (metres)	Au (g/t)	
GR-11-69	2400311	7433061	025	-45	21.90	49.50	27.60	0.71	
					including 28.40	39.00	10.60	1.13	
					73.55	166.00	92.45	0.89	
					including 115.30	119.80	4.50	1.29	
					and 142.30	165.00	22.70	2.37	
including 149.25	151.25	2.00	5.78						
GR-11-73 ⁽³⁾	2400328	7433244	190	-55	32.95	41.00	8.05	1.44	
					61.60	62.95	1.35	1.09	
					See Footnote #3	73.70	241.10	167.40	0.70
					including 73.70	77.70	4.00	1.82	
					and 100.15	130.20	30.05	1.37	
					and 136.00	145.00	9.00	1.51	
					and 204.00	207.00	3.00	2.56	
and 228.00	241.10	13.10	1.67						
GR-11-81	2400329	7433248	190	-70	See Footnote #4	32.00	186.10	154.10	0.76
					including 32.00	47.00	15.00	1.28	
					and 108.50	155.00	46.50	1.12	
					and 161.13	186.10	24.97	1.20	
¹ Intervals are core length. True width will be defined with additional drilling									
² Assays performed by Activation Laboratories Ltd, Ontario using the fire assay method 1A3-50 (Fire Assay Gravimetric (QOP AA-Au) on 50 grams of prepared sample.									
³ The GR-11-73 intersection of 167.40m grading 0.70 g/t Au, includes 6 intervals totaling 37m which have not been sampled. A zero grade was used in the weighted average grade calculation.									
⁴ The GR-11-81 intersection of 154.10m grading 0.76 g/t Au, includes 3 intervals totaling 17m which have not been sampled. A zero grade was used in the weighted average grade calculation.									