

Table 1: Summaries of Selected Assays from the Main Homestake Zone

Hole #	Collar Data			From (m)	To (m)	Interval (m)	Est. Tr. Thck (m)	Au (g/t)	Ag (g/t)	Cu (%)
	Az Deg	Dip Deg	Depth (m)							
HR09-152 inc. and and inc. and	219.9	-51.0	148.4	74.1	116.4	42.4	41.5	6.1	11.3	---
				78.0	82.1	4.1	4.0	3.5	7.1	---
				90.6	95.4	4.9	4.8	13.8	14.9	0.15
				103.3	115.4	12.2	11.9	13.0	19.5	0.10
				104.7	108.0	3.3	3.2	36.3	50.7	---
			113.2	114.3	1.1	1.1	23.5	25.1	1.10	
HR09-133 inc.	200.9	-55.0	355.7	253.95	263.5	9.5	9.3	1.84	1.62	---
				262.30	263.45	1.15	1.1	8.14	3.3	---

Analyzed by FA-ES/AA for gold and ICP-MS by Acme Labs, Vancouver BC; Samples >10g/t Au re-assayed with FA-Grav – check assays are pending; Silver overlimits (>100g/t Ag) re-assayed with FA-Grav.
>0.2g/t Au or 15g/t Ag cut-off used for compositing intervals, <20% internal dilution on +10 metre intervals