

Figure 1: Plan view of the Tulare Copper-Gold Porphyry Project showing the location of all currently defined exploration target areas together with gold and copper soil geochemical anomalies. Note that the grid spacing is 1,000 meters.




Figure 2: Plan view of the Bakrenjaca target area showing mapped geology and all Dunav drilling and trenching to date (section line relates to Figure 3). Note that the grid spacing is 500 meters.




Figure 3: Shows a representative south-north cross-section (looking west) through the Bakrenjaca target area with all drill hole intersections and summary geology based on Dunav's understanding to date.




Figure 4: Various soil geochemistry plots across the Bakrenjaca carbonate-base metal gold epithermal system. Note that the soil grid spacing was 100 meters by 25 meters.

Table 1: All Bakrenjaca Significant Intervals at Various Cut-offs – Drilling.

Diamond Drilling Significant Intervals									
Bakrenjaca									
0.1 g/t AuEq cut-off (\$1,500/oz Au, \$3.50/lb Cu, \$25/oz Ag, \$0.90/lb Pb, \$0.90/lb Zn)									
3m minimum length, 3m maximum internal dilution									
Hole ID	From (m)	To (m)	Interval (m)	Au (g/t)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)	AuEq (g/t)
BKDD001	1	41	40	0.22	1.23	0.01	0.11	0.25	0.40
BKDD001	46	68	22	0.14	1.50	0.03	0.03	0.05	0.25
BKDD001	77	92	15	0.06	2.17	0.01	0.04	0.04	0.14
BKDD001	96.1	128	31	1.92	122.30	0.44	0.90	0.96	5.43
BKDD001	132	152	20	0.13	2.53	0.01	0.05	0.02	0.21
BKDD001	157	179	22	0.04	1.35	0.04	0.02	0.01	0.14
BKDD001	184	210	26	0.05	0.66	0.01	0.03	0.09	0.12
BKDD002	3	89	86	0.32	1.25	0.01	0.07	0.22	0.47
BKDD002	101.8	109	7.2	0.08	0.72	0.00	0.01	0.01	0.11
BKDD002	113	127	14	0.08	0.79	0.01	0.04	0.10	0.16
BKDD002	132	137	5	0.07	1.10	0.03	0.18	0.83	0.55
GUDD001	0	24	24	0.04	1.28	0.01	0.19	0.17	0.23
GUDD001	30	49	19	0.04	0.93	0.01	0.18	0.14	0.21
GUDD001	80	85	5	0.14	4.14	0.04	0.24	0.34	0.52
GUDD001	91	103	12	0.07	2.18	0.01	0.17	0.10	0.23
GUDD001	116	198	82	0.07	2.42	0.02	0.14	0.15	0.26
GUDD001	205	208	3	0.05	2.97	0.01	0.11	0.06	0.19
GUDD001	213	254	41	0.14	1.93	0.12	0.04	0.03	0.40
GUDD001	288	326.9	38.9	0.07	3.67	0.04	0.55	0.84	0.78
GUDD001	331.9	340	8.1	0.05	1.59	0.02	0.04	0.04	0.14
GUDD001	349	364	15	0.01	0.66	0.02	0.16	0.28	0.23
GUDD001	378	399	21	0.01	0.73	0.01	0.19	0.16	0.18
GUDD001	419	453	34	0.02	0.60	0.02	0.14	0.27	0.23
GUDD001	461	464	3	0.04	0.50	0.01	0.09	0.15	0.15
GUDD001	477	491	14	0.05	2.44	0.02	0.08	0.08	0.18
GUDD002	7	16	9	0.14	1.66	0.00	0.17	0.24	0.34
GUDD002	22	43	21	0.25	3.79	0.03	0.27	0.38	0.62
GUDD002	47	57	10	0.07	4.04	0.03	0.14	0.17	0.31
GUDD002	104	108	4	0.05	1.37	0.00	0.11	0.04	0.14
GUDD002	129	132	3	0.07	0.80	0.00	0.09	0.10	0.16
GUDD002	141	151	10	0.06	1.45	0.00	0.13	0.59	0.38
0.4 g/t AuEq cut-off (\$1,500/oz Au, \$3.50/lb Cu, \$25/oz Ag, \$0.90/lb Pb, \$0.90/lb Zn)									
3m minimum length, 3m maximum internal dilution									

Hole ID	From (m)	To (m)	Interval (m)	Au (g/t)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)	AuEq (g/t)
BKDD001	36	40	4	0.48	5.53	0.03	0.46	0.38	0.96
BKDD001	64	68	4	0.11	5.85	0.11	0.07	0.05	0.43
BKDD001	100	111	11	5.13	345.57	1.19	2.36	1.86	14.52
BKDD001	116	127	11	0.37	7.82	0.08	0.23	0.88	1.09
BKDD002	9	16	7	0.48	1.34	0.00	0.07	0.86	0.89
BKDD002	28	31	3	0.50	0.88	0.00	0.05	0.12	0.59
BKDD002	35	42	7	0.84	1.10	0.01	0.04	0.10	0.93
BKDD002	49	79	30	0.36	1.70	0.01	0.12	0.28	0.58
BKDD002	132	137	5	0.07	1.10	0.03	0.18	0.83	0.55
GUDD001	80	85	5	0.14	4.14	0.04	0.24	0.34	0.52
GUDD001	95	98	3	0.19	5.97	0.01	0.56	0.14	0.60
GUDD001	156	160	4	0.23	6.70	0.01	0.20	0.12	0.49
GUDD001	170	173	3	0.11	3.77	0.05	0.18	0.32	0.45
GUDD001	178	182	4	0.15	7.58	0.05	0.57	0.47	0.78
GUDD001	231	235	4	0.49	6.82	1.12	0.05	0.01	2.41
GUDD001	296	317	21	0.11	4.91	0.07	0.85	1.13	1.12
GUDD001	323	326	3	0.01	2.87	0.07	0.78	2.40	1.48
GUDD001	447	452	5	0.03	0.76	0.05	0.27	0.46	0.42
GUDD002	11	15	4	0.20	2.10	0.00	0.22	0.33	0.46
GUDD002	35	39	4	1.03	13.33	0.05	0.84	1.45	2.28
GUDD002	47	51	4	0.10	8.77	0.06	0.27	0.22	0.55
GUDD002	141	144	3	0.10	1.79	0.00	0.34	1.60	0.93

0.8 g/t AuEq cut-off (\$1,500/oz Au, \$3.50/lb Cu, \$25/oz Ag, \$0.90/lb Pb, \$0.90/lb Zn)

3m minimum length, 3m maximum internal dilution

Hole ID	From (m)	To (m)	Interval (m)	Au (g/t)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)	AuEq (g/t)
BKDD001	100	110	10	5.62	379.34	1.30	2.58	2.03	15.93
BKDD001	116	127	11	0.37	7.82	0.08	0.23	0.88	1.09
BKDD002	9	16	7	0.48	1.34	0.00	0.07	0.86	0.89
BKDD002	38	42	4	1.18	1.13	0.02	0.05	0.15	1.31
BKDD002	61	66	5	0.54	5.21	0.05	0.49	1.17	1.40
GUDD001	296	316	20	0.11	4.81	0.07	0.88	1.17	1.15
GUDD001	323	326	3	0.01	2.87	0.07	0.78	2.40	1.48

1.0 g/t AuEq cut-off (\$1,500/oz Au, \$3.50/lb Cu, \$25/oz Ag, \$0.90/lb Pb, \$0.90/lb Zn)

3m minimum length, 3m maximum internal dilution

Hole ID	From (m)	To (m)	Interval (m)	Au (g/t)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)	AuEq (g/t)
BKDD001	100	110	10	5.62	379	1.30	2.58	2.03	15.9
BKDD001	116	127	11	0.37	7.82	0.08	0.23	0.88	1.09



BKDD002	13	16	3	0.43	1.33	0.00	0.07	1.42	1.07
BKDD002	38	42	4	1.18	1.13	0.02	0.05	0.15	1.31
BKDD002	61	66	5	0.54	5.21	0.05	0.49	1.17	1.40
GUDD001	296	305	9	0.13	4.58	0.06	1.25	1.95	1.63
GUDD001	323	326	3	0.01	2.87	0.07	0.78	2.40	1.48

- 0.4g/t AuEq cut-off (\$1,500/oz. Au, \$25/oz Ag, \$3.50/lb. Cu, \$0.90/lb. Pb, \$0.90/lb. Zn), 3m minimum composite length, 3m maximum internal dilution.
 - $\text{AuEq} = ((\text{Au g/t} * 48.226) + (\text{Ag g/t} * 0.8038) + (\text{Cu\%} * 77.16) + (\text{Pb\%} * 19.84) + (\text{Zn\%} * 19.84)) / 48.226$
- Diamond drill samples are PQ, HQ or NQ half core, using a nominal 1m sampling basis and weigh ~3-6kg.
- Assay method: Fire assay Au (50g); Ag, Cu, Pb & Zn by aqua regia digestion with AAS and/or ICPMS finish.
- Intercept widths do not necessarily represent true width.
- No top cut applied.

Table 2: All Bakrenjaca Significant Intervals at Various Cut-offs – Trenching.

Trenching Significant Intervals									
Bakrenjaca									
0.1 g/t AuEq cut-off (\$1,500/oz Au, \$3.50/lb Cu, \$25/oz Ag, \$0.90/lb Pb, \$0.90/lb Zn)									
3m minimum length, 3m maximum internal dilution									
Trench ID	From (m)	To (m)	Interval (m)	Au (g/t)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)	AuEq (g/t)
BKTR001	8	13	5	0.10	2.02	0.00	0.11	0.16	0.25
BKTR002	1	5	4	0.12	1.50	0.00	0.38	0.86	0.66
BKTR003	0	21	21	0.13	3.11	0.01	0.17	0.17	0.34
BKTR004	0	21	21	0.05	0.67	0.01	0.11	0.24	0.22
BKTR005	0	8	8	0.04	0.56	0.00	0.12	0.70	0.40
BKTR006	5	15	10	0.19	1.07	0.00	0.16	0.26	0.38
BKTR007	0	20	20	0.17	0.92	0.00	0.26	0.59	0.54
BKTR011	2	16	14	0.11	1.02	0.00	0.04	0.07	0.17
BKTR011	22	48	26	0.35	0.96	0.00	0.16	0.10	0.48
BKTR012	8	24	16	0.27	0.82	0.01	0.13	0.48	0.56
BKTR012	28	43	15	0.18	0.73	0.01	0.05	0.20	0.31
BKTR013	0	6	6	0.76	8.48	0.11	0.47	0.11	1.31
BKTR014	0	17	17	0.03	0.62	0.49	0.06	0.15	0.90
BKTR014	42	50	8	0.03	0.50	0.01	0.09	0.13	0.14
BKTR015	0	23	23	0.38	7.73	0.08	0.39	0.65	1.06
BKTR016	1	6	5	0.05	1.62	0.00	0.06	0.07	0.14
BKTR016	33	36	3	0.07	3.50	0.11	0.09	0.07	0.37
BKTR016	54	71	17	0.40	2.63	0.01	0.18	0.05	0.55
BKTR018	0	3	3	0.02	1.40	0.07	0.02	0.48	0.36
BKTR018	9	13	4	0.05	1.00	0.02	0.11	0.11	0.19
BKTR018	20	39	19	0.15	12.4	0.24	0.32	0.14	0.94
BKTR019	0	54	54	0.42	14.2	0.19	0.25	0.59	1.31
BKTR020	0	16	16	0.10	1.50	0.03	0.09	0.06	0.23
BKTR020	20	28	8	0.08	5.61	0.05	0.08	0.05	0.31
BKTR021	0	15	15	0.25	5.03	0.11	0.67	0.04	0.80
BKTR021	20	84	64	0.17	2.43	0.03	0.31	0.10	0.42
BKTR022	0	26	26	0.92	10.5	0.27	2.35	0.33	2.63
BKTR023	1	21	20	0.12	1.94	0.06	0.31	0.07	0.40
0.4 g/t AuEq cut-off (\$1,500/oz Au, \$3.50/lb Cu, \$25/oz Ag, \$0.90/lb Pb, \$0.90/lb Zn)									
3m minimum length, 3m maximum internal dilution									
Trench ID	From (m)	To (m)	Interval (m)	Au (g/t)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)	AuEq (g/t)
BKTR003	0	3	3	0.38	6.50	0.01	0.41	0.20	0.75
BKTR003	16	19	3	0.12	3.80	0.01	0.30	0.30	0.44

BKTR005	4	8	4	0.04	0.63	0.00	0.15	1.02	0.54
BKTR006	6	15	9	0.20	1.13	0.00	0.17	0.26	0.40
BKTR007	6	19	13	0.23	1.11	0.01	0.33	0.76	0.71
BKTR011	30	46	16	0.53	1.06	0.00	0.24	0.11	0.69
BKTR012	14	23	9	0.32	0.96	0.02	0.17	0.79	0.76
BKTR013	1	6	5	0.89	10.1	0.11	0.54	0.11	1.50
BKTR014	0	8	8	0.04	0.75	0.97	0.09	0.13	1.69
BKTR015	1	23	22	0.39	8.02	0.08	0.40	0.68	1.10
BKTR016	56	71	15	0.44	2.85	0.01	0.19	0.05	0.61
BKTR018	20	36	16	0.16	14.3	0.29	0.36	0.17	1.08
BKTR019	0	46	46	0.48	16.4	0.21	0.28	0.69	1.50
BKTR021	0	15	15	0.25	5.03	0.11	0.67	0.04	0.80
BKTR021	21	27	6	0.11	1.67	0.04	0.52	0.03	0.42
BKTR021	34	41	7	0.57	4.29	0.06	0.81	0.06	1.09
BKTR021	50	55	5	0.55	8.50	0.06	0.70	0.01	1.07
BKTR021	80	84	4	0.18	4.08	0.05	0.29	0.01	0.45
BKTR022	3	26	23	1.03	11.6	0.31	2.65	0.37	2.96
BKTR023	4	15	11	0.18	2.72	0.08	0.47	0.09	0.58

0.8 g/t AuEq cut-off (\$1,500/oz Au, \$3.50/lb Cu, \$25/oz Ag, \$0.90/lb Pb, \$0.90/lb Zn)

3m minimum length, 3m maximum internal dilution

Trench ID	From (m)	To (m)	Interval (m)	Au (g/t)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)	AuEq (g/t)
BKTR007	13	18	5	0.37	1.88	0.01	0.65	1.35	1.24
BKTR011	32	42	10	0.62	1.40	0.00	0.29	0.14	0.83
BKTR012	14	18	4	0.17	1.52	0.04	0.20	1.36	0.89
BKTR013	1	6	5	0.89	10.1	0.11	0.54	0.11	1.50
BKTR014	0	8	8	0.04	0.75	0.97	0.09	0.13	1.69
BKTR015	2	12	10	0.63	8.81	0.10	0.54	0.74	1.46
BKTR015	17	23	6	0.28	13.4	0.11	0.37	0.58	1.07
BKTR018	20	36	16	0.16	14.3	0.29	0.36	0.17	1.08
BKTR019	0	32	32	0.57	21.2	0.28	0.37	0.97	1.92
BKTR019	36	41	5	0.55	9.64	0.04	0.11	0.04	0.84
BKTR021	3	13	10	0.31	6.60	0.09	0.78	0.03	0.90
BKTR021	36	39	3	1.18	7.00	0.09	1.00	0.02	1.87
BKTR021	50	54	4	0.64	9.65	0.07	0.79	0.02	1.23
BKTR022	4	26	22	1.06	12.0	0.32	2.75	0.39	3.06

1.0 g/t AuEq cut-off (\$1,500/oz Au, \$3.50/lb Cu, \$25/oz Ag, \$0.90/lb Pb, \$0.90/lb Zn)

3m minimum length, 3m maximum internal dilution

Trench ID	From (m)	To (m)	Interval (m)	Au (g/t)	Ag (g/t)	Cu (%)	Pb (%)	Zn (%)	AuEq (g/t)
BKTR013	1	6	5	0.89	10.1	0.11	0.54	0.11	1.50



BKTR014	2	8	6	0.02	0.50	1.15	0.08	0.17	1.96
BKTR015	2	9	7	0.82	12.4	0.13	0.63	0.71	1.78
BKTR018	22	32	10	0.18	16.8	0.30	0.38	0.18	1.17
BKTR019	0	32	32	0.57	21.2	0.28	0.37	0.97	1.92
BKTR021	7	10	3	0.47	10.7	0.08	1.00	0.03	1.21
BKTR022	4	11	7	1.22	14.5	0.12	3.72	0.09	3.21
BKTR022	16	26	10	1.37	14.8	0.59	2.99	0.73	4.09

- 0.4g/t AuEq cut-off (\$1,500/oz. Au, \$25/oz Ag, \$3.50/lb. Cu, \$0.90/lb. Pb, \$0.90/lb. Zn), 3m minimum composite length, 3m maximum internal dilution.
 - $\text{AuEq} = ((\text{Au g/t} * 48.226) + (\text{Ag g/t} * 0.8038) + (\text{Cu\%} * 77.16) + (\text{Pb\%} * 19.84) + (\text{Zn\%} * 19.84)) / 48.226$
- Trench samples are designed to replicate HQ half core, using a nominal 1m sampling basis and weigh ~3-6kg.
- Assay method: Fire assay Au (50g); Ag, Cu, Pb & Zn by aqua regia digestion with AAS and/or ICPMS finish.
- Intercept widths do not necessarily represent true width.
- No top cut applied.