

Table 1: Select Composites from the 2011 Porphyry Creek Drilling at Sultana

Hole #	Collar Data			From (m)	To (m)	Interval (m)	Cu %	Mo %	CuEq %
	Az Deg	Dip Deg	Depth (m)						
PC11-04 inc. and and	250.0	-60.0	616.7	5.0	616.7	611.7	0.07	0.009	0.12
				324.0	375.0	51.0	0.11	0.021	0.22
				402.0	427.0	25.0	0.10	0.017	0.19
				479.0	616.7	137.7	0.09	0.016	0.17
PC11-05 inc. and and	250.0	-60.0	588.0	188.0	586.0	398.0	0.07	0.008	0.11
				189.0	217.0	28.0	0.10	0.002	0.11
				388.0	424.0	36.0	0.11	0.029	0.26
				554.0	578.0	24.0	0.08	0.005	0.11

The copper equivalent (CuEq) calculation was based on long-term average Mo/Cu metal price to arrive at a ratio of 5 to 1. The CuEq calculations reflect gross metal content and have not been adjusted for relative metal recoveries, or relative processing and smelting costs.