

## GOLDEN PIKE

<b>GOLDEN PIKE DRILL INTERSECTIONS<sup>1,2</sup></b>							
<b>Hole No.</b>	<b>Coordinates</b>	<b>Dip</b>	<b>Azimuth</b>	<b>From (metres)</b>	<b>To (metres)</b>	<b>Interval (metres)<sup>1</sup></b>	<b>Au (g/t)<sup>2</sup></b>
FR-94-09 <sup>3</sup>	273421E / 5061266N	-80°	077	<b>64.8</b>	<b>77.80</b>	<b>13.00</b>	<b>43.07</b>
DP-07-04	273283E / 5061285N	-45°	117	<b>83.94</b>	<b>94.00</b>	<b>10.06</b>	<b>32.26</b>
DP-08-15	273196E / 5061396N	-45°	117	<b>319.28</b>	<b>327.00</b>	<b>7.72</b>	<b>8.08</b>
			including	319.28	321.00	1.72	10.30
			and	322.49	323.00	0.51	2.17
			and	324.42	327.00	2.58	16.86
DP-11-48	273298E / 5061277N	-45°	115	<b>64.18</b>	<b>74.80</b>	<b>10.62</b>	<b>6.93</b>
			including	64.18	65.42	1.24	12.30
			and	69.68	74.80	5.12	10.55
			including	74.20	74.80	0.60	34.50
DP-11-49	2733334E / 5061292N	-53°	115	<b>69.65</b>	<b>73.00</b>	<b>3.35</b>	<b>9.09</b>
DP-11-50	273307E / 5061332N	-46°	110	<b>60.5</b>	<b>64.30</b>	<b>3.80</b>	<b>9.42</b>
DP-11-54	273269E / 5061326N	-60°	115	<b>84.65</b>	<b>86.85</b>	<b>2.20</b>	<b>19.47</b>
DP-11-61	273270E / 5061353N	-55°	110	<b>125.74</b>	<b>127.15</b>	<b>1.41</b>	<b>33.30</b>
<i><sup>1</sup>Intervals are core length. True width will be defined with additional drilling</i>							
<i><sup>2</sup>Assays were performed by Activation Laboratories Ltd, Ontario using the fire assay method (1A3-50) on 50 grams of prepared sample. Metallic screen fire assay (1A4) were completed for drill holes DP-11-48, DP-11-49 and DP-11-61. Samples returning assays greater than 10 ppm Au in DP-07-04 and DP-08-15 were automatically assayed by metallic screen fire assay (1A4).</i>							
<i><sup>3</sup>FR-94-09 was completed by Foster Resources Ltd in 1994.</i>							