

TABLE 1. Composite assays, 543S deposit – Jan. 31, 2013

Hole	Interval (m)	Length (m)	% Cu (0.20% Cu cutoff)	Ag (g/t)
CEN322	92.3 - 97.5	5.2	1.01	4.5
	102.0 - 127.5	25.5	1.08	4.4
including	118.2 - 119.7	1.5	7.61	24.2
	131.7 - 150.6	18.9	0.68	2.0
	168.1 - 176.4	8.3	3.22	2.9
including	170.9 - 175.4	4.5	5.37	4.1
CEN379	136.0 - 138.0	2.0	1.36	11.4
	143.1 - 145.2	2.1	2.40	4.4
	158.5 - 161.5	3.0	0.27	0.6
	204.7 - 213.3	8.6	0.80	1.4
	221.9 - 230.5	8.6	0.29	1.8
	238.5 - 241.0	2.5	0.31	1.0
CEN396	64.4 - 65.4	1.0	4.93	1.0
	68.6 - 70.9	2.3	1.68	0.6
	73.9 - 75.9	2.0	1.42	8.7
CEN398	39.6 - 44.5	4.9	2.10	24.2
	56.4 - 57.5	1.1	5.97	1.5
CEN399	56.6 - 62.0	5.4	3.10	3.8
including	57.6 - 59.1	1.5	7.16	1.4
CEN401	32.2 - 45.6	13.4	1.30	4.1
including	32.7 - 33.3	0.6	9.34	2.8
CEN405	48.2 - 61.0	12.8	1.74	2.2
including	48.2 - 50.2	2.0	6.14	7.5
	75.2 - 83.1	7.9	1.21	0.7
including	80.3 - 81.1	0.8	7.46	2.8

Hole	Interval (m)	Length (m)	% Cu (0.20% Cu cutoff)	Ag (g/t)
CEN406	37.2 - 41.1	3.9	2.93	0.9
including	37.7 - 38.7	1.0	10.11	2.2
CEN407	20.0 - 46.0	26.0	1.09	1.2
including	20.5 - 21.2	0.7	8.91	1.9
including	38.1 - 39.8	1.7	5.81	1.2
	54.5 - 58.2	3.7	6.43	1.1
	56.0 - 57.5	1.5	11.01	1.5
CEN409	18.8 - 20.0	1.2	1.25	1.2
	37.0 - 47.0	10.0	3.45	7.0
including	38.5 - 42.0	3.5	8.37	1.6
	54.0 - 57.0	3.0	0.88	0.6
CEN411	81.4 - 84.0	2.6	0.33	0.7
	97.5 - 99.0	1.5	0.99	0.7
	103.5 - 137.0	33.5	2.25	14.5
including	122.2 - 126.9	4.7	4.59	2.6
	148.0 - 149.3	1.3	2.17	0.8
CEN412	9.9 - 12.9	3.0	0.63	1.4
	58.5 - 87.5	29.0	1.95	2.8
including	68.7 - 71.1	2.4	5.37	4.8
including	77.7 - 79.0	1.5	5.47	3.1
including	80.5 - 82.5	2.0	7.93	3.6
CEN414	99.5 - 104.9	5.4	2.03	36.4
	112.6 - 125.6	13.0	3.64	5.9
including	116.1 - 117.1	1.0	8.68	13.0
including	118.1 - 120.1	2.0	7.66	9.0
CEN416	65.2 - 70.8	5.6	1.80	2.9
	76.9 - 91.2	14.3	2.16	2.9

Hole	Interval (m)	Length (m)	% Cu (0.20% Cu cutoff)	Ag (g/t)
including	76.9 - 78.9	2.0	9.81	7.1
	96.2 - 102.0	5.8	0.45	0.5
	113.5 - 116.5	3.0	0.42	0.4
CEN417	80.7 - 107.4	26.7	2.88	4.0
including	84.2 - 85.6	1.4	5.04	5.3
including	90.3 - 92.2	1.9	8.14	7.8
including	95.1 - 98.1	3.0	10.43	14.2
	120.1 - 122.1	2.0	0.27	0.3
CEN424	14.0 - 18.2	4.2	0.31	0.4
	34.2 - 37.7	3.5	0.94	6.3
	45.8 - 50.0	4.2	1.05	0.9
	82.8 - 87.9	5.1	0.85	0.7
CEN434	160.5 - 206.8	46.3	1.99	2.6
<i>including</i>	<i>203.4 - 206.2</i>	<i>2.8</i>	<i>6.37</i>	<i>3.8</i>
CEN447	72.0 - 73.5	1.5	1.93	0.7
	76.0 - 84.6	8.6	0.89	2.0
	88.8 - 91.7	2.9	3.08	2.0
including	88.9 - 90.3	1.4	5.65	2.5