

Table 1: Drill Results from Northeast Fold, Banana Zone, Sections 70125 – 70725 Interval indicates down hole interval

Hole #	Section	Mineralized Zone	From (m)	To (m)	Interval (m)	Est. True Width (m)	Cu Eq (%)	Cu (%)	Ag (g/t)
HA-472-D	N70125	Northeast Fold	149.27	158.32	9.05	9.05	0.71	0.59	8.0
includes			153.63	156.23	2.60	2.60	1.11	1.04	5.0
includes			157.40	158.32	0.92	0.92	2.51	1.86	45.0
HA-473-D	N70725	Northeast Fold	206.00	212.00	6.00	6.00	0.24	0.21	2.0
HA-476-D	N70525	Northeast Fold	181.00	208.00	27.00	24.06	0.56	0.49	5.0
includes			181.76	182.36	0.60	0.53	0.95	0.85	7.0
includes			188.30	195.17	6.87	6.12	0.66	0.61	3.0
includes			198.50	200.00	1.50	1.34	0.73	0.67	4.0
includes			203.84	207.13	3.29	2.93	1.69	1.36	23.0
HA-478c-D	N70325	Northeast Fold	52.00	85.00	33.00	33.00	1.15	1.03	8.0
includes			61.83	75.16	13.33	13.33	1.87	1.76	8.0
includes			78.15	81.00	2.85	2.85	3.01	2.46	38.0
HA-478c-D			91.43	93.13	1.70	1.70	2.93	2.41	36.0
HA-478c-D			97.00	100.26	3.26	3.26	0.53	0.43	7.0
HA-482-D	N70625	Northeast Fold	140.46	193.48	53.02	47.24	1.07	0.85	15.00
HA-482-D			169.70	171.30	1.60	1.43	1.82	1.45	26.00
HA-482-D			188.56	191.85	3.29	2.93	14.23	11.22	206.00
HA-483-D	N70525	Northeast Fold	110.65	173.38	62.73	55.89	1.11	0.95	11.0
includes			112.00	119.00	7.00	6.24	3.16	2.84	22.0
includes			134.07	139.72	5.65	5.03	0.88	0.81	5.0
includes			156.00	163.00	7.00	6.24	1.82	1.41	28.0
includes			168.72	172.35	3.63	3.23	6.62	5.45	80.0
HA-485-D	N70200	Northeast Fold	204.57	208.40	3.83	3.83	1.42	1.10	22.0
HA-487-D	N70425	Northeast Fold	105.80	133.00	27.20	24.24	1.46	1.21	17.0
includes			105.80	109.00	3.20	2.85	0.71	0.63	5.0
includes			110.70	113.00	2.30	2.05	0.86	0.77	6.0
includes			122.80	130.90	8.10	7.22	4.02	3.32	48.0
HA-488b-D	N70325	Northeast Fold	103.44	124.50	21.06	21.06	0.73	0.66	5.00
includes			105.00	110.00	5.00	5.00	0.63	0.57	4.00
includes			113.00	118.00	5.00	5.00	1.43	1.31	8.00
includes			121.82	124.50	2.68	2.68	1.15	1.00	10.00

Hole #	Section	Mineralized Zone	From (m)	To (m)	Interval (m)	Est. True Width (m)	Cu Eq (%)	Cu (%)	Ag (g/t)
HA-490-D	N70525	Northeast Fold	49.00	50.91	1.91	1.70	0.69	0.67	1.00
HA-490-D			57.00	60.00	3.00	2.67	3.19	3.10	6.00
HA-490-D			73.88	76.30	2.42	2.16	1.03	1.00	2.00
HA-490-D			88.67	96.00	7.33	6.53	0.40	0.34	4.00
HA-490-D			104.00	123.00	19.00	16.93	0.32	0.29	2.00
includes			108.00	111.94	3.94	3.51	0.83	0.74	6.00
HA-490-D			146.63	192.70	46.07	41.05	0.39	0.30	6.00
includes			175.11	179.60	4.49	4.00	1.20	0.81	27.00
includes			187.60	192.70	5.10	4.54	0.87	0.63	16.00
HA-495-D	N70125	Northeast Fold	197.12	205.86	8.74	8.74	0.58	0.48	7.00
includes			202.14	205.86	3.72	3.72	0.92	0.70	15.00
HA-496-D	N70325	Northeast Fold	73.82	97.00	23.18	23.18	0.49	0.45	3.00
includes			89.09	91.32	2.23	2.23	2.10	1.99	8.00

Copper equivalent calculated using US\$3.00/lb Cu, US\$30/oz Ag and is not adjusted for metallurgical recoveries. The formula used is as follows:  $CuEq = Cu\% + (Ag\ g/t \times 0.01458)$ .