

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB168													
DUB168	781.74	805.69	23.95	28.0	1830	5290	-772	0.19	15.46	0.19	13.26	0.30	17.57
<i>includes</i>													
DUB168	781.74	782.58	0.84	1.0	1834	5291	-762	0.23	22.29	0.38	21.16	0.01	26.43
DUB168	790.20	805.69	15.49	18.1	1829	5289	-776	0.22	11.36	0.23	18.65	0.05	16.58
DUB168	805.69	818.50	12.81	15.0	1824	5287	-789	0.27	11.47	0.52	2.00	0.01	15.10
DUB168	868.58	869.97	1.39	1.6	1803	5280	-842	2.23	124.49	0.28	5.81	1.74	18.16
DUB168	873.40	874.54	1.14	1.3	1802	5280	-847	3.77	233.49	0.20	0.05	2.85	2.23
DUB168	881.76	884.86	3.10	3.6	1798	5279	-856	0.24	36.58	0.27	10.21	1.23	21.17
DUB168	890.00	891.03	1.03	1.2	1796	5278	-862	5.14	31.54	0.42	0.23	0.19	15.96
DUB168	907.36	910.00	2.64	3.1	1790	5276	-879	0.72	15.32	0.39	1.74	0.02	9.13
DUB168	917.29	917.45	0.16	0.2	1787	5275	-887	1.58	12.69	1.11	6.93	0.00	14.99
DUB168DPN													
DUB168DPN	948.47	954.61	6.14	7.1	1775	5272	-919	1.74	8.62	0.35	0.04	0.00	5.19
<i>includes</i>													
DUB168DPN	948.47	950.10	1.63	1.9	1775	5272	-919	3.17	10.04	0.36	0.02	0.00	3.67
DUB168DPN	973.30	973.63	0.33	0.4	1767	5270	-940	0.48	8.57	0.15	10.21	0.00	9.62
DUB168DPN	980.54	1007.88	27.34	31.4	1760	5268	-959	2.40	56.70	0.69	7.75	1.37	13.18
<i>includes</i>													
DUB168DPN	989.44	1006.40	16.96	19.5	1759	5268	-963	3.17	75.32	0.89	10.59	1.85	15.70
DUB168DPN	1018.70	1020.66	1.96	2.3	1752	5266	-983	1.46	12.69	0.24	2.78	0.00	5.03
DUB168DPN	1030.65	1031.00	0.35	0.4	1748	5265	-994	0.07	2.40	0.20	7.16	0.00	3.16
DUB168DPN	1061.04	1063.83	2.79	3.2	1738	5262	-1023	1.14	17.57	0.83	9.88	0.00	12.70
<i>includes</i>													
DUB168DPN	1061.89	1063.12	1.23	1.4	1738	5262	-1023	0.58	8.98	0.31	15.44	0.00	13.61
DUB169													
DUB169	828.08	833.03	4.95	5.3	1862	5612	-795	0.39	30.90	0.22	2.62	0.48	12.34
DUB169	891.07	923.55	32.48	34.8	1835	5608	-867	5.55	23.79	0.35	0.32	0.22	4.22
<i>includes</i>													
DUB169	900.28	900.62	0.34	0.4	1837	5608	-861	1.27	42.51	0.14	7.13	8.20	2.80
DUB169	901.96	902.21	0.25	0.3	1837	5608	-862	1.92	27.09	0.37	11.03	0.46	6.78
DUB169	903.70	915.00	11.30	12.1	1834	5608	-869	13.47	41.59	0.53	0.06	0.03	4.27
DUB169	919.50	919.60	0.10	0.1	1831	5608	-878	40.70	115.54	6.46	0.68	0.06	9.98
DUB169	929.00	929.79	0.79	0.8	1827	5608	-888	0.62	32.57	0.76	11.80	0.98	15.13
DUB169	936.32	937.00	0.68	0.7	1825	5608	-895	4.80	180.34	0.48	0.24	1.27	2.65
DUB169DPN													
DUB169DPN	No significant values.												
DUB170													
DUB170	841.05	851.00	9.95	12.9	1852	5060	-807	0.67	18.73	0.35	9.58	0.47	26.15
<i>includes</i>													
DUB170	841.05	847.14	6.09	7.9	1853	5060	-805	0.83	22.89	0.21	15.62	0.74	30.41
DUB170W01													
DUB170W01	Drilling.												
DUB171													
DUB171	961.70	967.10	5.40	5.8	1901	5522	-884	0.39	10.75	0.47	8.64	0.52	19.06
<i>includes</i>													
DUB171	962.31	965.62	3.31	3.5	1901	5522	-884	0.52	6.44	0.58	12.76	0.04	22.59

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core ⁽¹⁾ length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB171 Cont.													
DUB171	974.32	993.00	18.68	20.0	1893	5522	-901	1.36	10.24	0.33	0.52	0.05	4.10
DUB171	1005.00	1012.00	7.00	7.5	1882	5523	-924	2.94	4.60	0.06	0.84	0.05	2.00
DUB171	1016.00	1017.00	1.00	1.2	1889	5531	-931	3.63	1.03	0.02	0.08	0.00	2.41
DUB171	1021.00	1022.00	1.00	1.2	1887	5531	-936	5.59	2.74	0.05	0.23	0.00	2.70
DUB171	1025.00	1026.00	1.00	1.1	1875	5524	-939	4.08	1.71	0.06	0.35	0.00	3.87
DUB171	1044.30	1045.00	0.70	0.7	1867	5524	-957	0.62	10.63	0.26	7.29	0.14	6.24
DUB171	1072.90	1108.50	35.60	38.1	1847	5526	-998	3.03	11.99	0.48	0.53	0.01	5.97
<i>includes</i> DUB171	1078.70	1082.50	3.80	4.1	1851	5526	-989	12.90	58.75	1.92	1.49	0.06	18.53
DUB171	1128.65	1131.48	2.83	3.3	1840	5535	-1034	10.95	4.57	0.06	0.04	0.01	3.27
DUB171	1130.50	1131.48	0.98	1.0	1830	5528	-1034	6.86	3.43	0.06	0.03	0.02	2.53
DUB171	1139.00	1141.00	2.00	2.1	1826	5528	-1043	31.05	118.46	1.13	0.29	0.01	6.90
DUB171	1146.20	1146.78	0.58	0.6	1823	5528	-1048	19.20	73.71	1.21	2.83	0.00	12.28
DUB171	1162.00	1162.55	0.55	0.6	1816	5529	-1063	0.17	5.14	0.21	10.55	0.00	15.31
DUB172													
DUB172	906.77	915.24	8.47	9.9	1990	5213	-867	7.10	137.16	0.21	0.00	0.79	4.10
<i>includes</i> DUB172	908.72	910.20	1.48	1.7	1991	5213	-865	20.58	327.08	0.40	0.00	1.92	2.57
DUB172	928.17	954.40	26.23	30.7	1980	5210	-895	5.20	13.75	0.36	3.46	0.11	19.89
<i>includes</i> DUB172	928.17	928.45	0.28	0.3	1984	5211	-883	159.26	302.74	0.35	0.03	3.71	2.03
DUB172	930.00	934.10	4.10	4.8	1983	5211	-886	1.54	10.09	0.53	9.83	0.02	33.93
DUB172DPN													
DUB172DPN	1123.45	1128.76	5.31	5.7	1915	5200	-1068	0.94	8.01	0.47	0.22	0.00	2.16
<i>includes</i> DUB172DPN	1123.45	1124.26	0.81	0.9	1916	5200	-1066	1.89	13.80	1.55	1.17	0.00	3.49
DUB173													
DUB173	901.50	902.80	1.30	1.4	1798	5452	-757	2.84	142.31	0.13	0.00	1.35	7.07
DUB173	966.79	966.99	0.20	0.2	1762	5448	-811	0.55	28.46	0.68	5.34	0.39	13.48
DUB173	976.23	976.75	0.52	0.6	1757	5448	-819	0.50	39.22	0.40	5.63	0.48	12.19
DUB173	980.56	980.73	0.17	0.2	1755	5448	-823	0.34	8.57	0.27	7.64	0.09	10.71
DUB173	982.26	998.81	16.55	17.7	1750	5447	-831	9.98	45.88	3.13	5.44	0.08	21.06
DUB173	1008.82	1017.30	8.48	9.1	1738	5446	-850	2.20	13.83	0.25	2.08	0.10	5.55
DUB173	1024.60	1030.84	6.24	6.7	1730	5445	-863	0.37	18.82	0.09	3.66	0.46	25.69
DUB173	1086.00	1108.00	22.00	23.5	1693	5443	-922	2.03	66.79	0.43	2.31	1.48	12.05
<i>includes</i> DUB173	1086.67	1099.86	13.19	14.1	1695	5443	-918	1.77	54.87	0.58	3.70	1.40	17.56
DUB174													
DUB174	705.18	709.11	3.93	4.5	1709	5305	-687	0.17	17.22	0.43	22.59	0.00	19.71
DUB174	718.33	722.89	4.56	5.2	1705	5304	-700	4.75	169.99	0.20	0.03	1.00	4.05
DUB174	722.89	737.00	14.11	16.2	1702	5304	-709	0.39	14.60	0.74	7.67	0.06	24.24
<i>includes</i> DUB174	722.89	731.12	8.23	9.5	1703	5304	-706	0.22	7.13	0.29	10.61	0.04	30.94
DUB174	738.96	739.61	0.65	0.7	1699	5303	-718	0.24	5.83	0.32	8.30	0.03	20.12
DUB174	739.61	740.22	0.61	0.7	1699	5303	-718	16.25	194.06	0.21	0.23	0.88	15.90

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB174 Cont.													
DUB174	782.47	786.11	3.64	4.2	1686	5301	-761	0.27	17.75	0.06	4.31	0.31	5.36
DUB174	834.29	851.96	17.67	20.3	1669	5297	-817	0.47	9.07	0.29	4.62	0.21	16.54
<i>includes</i> DUB174	834.29	840.22	5.93	6.8	1671	5297	-811	0.34	12.57	0.31	9.94	0.42	23.53
DUB174	852.57	857.43	4.86	5.6	1665	5295	-828	3.82	27.75	0.08	0.20	0.33	3.69
DUB174	865.37	865.86	0.49	0.6	1662	5294	-838	0.17	1.03	0.12	5.87	0.00	31.43
DUB174	872.46	880.61	8.15	9.4	1659	5293	-848	0.76	18.47	0.14	8.53	1.27	20.23
DUB174	885.96	888.92	2.96	3.4	1656	5292	-859	0.72	9.01	0.27	5.90	0.04	10.48
DUB174	901.41	905.65	4.24	4.9	1652	5291	-874	0.39	15.11	0.14	8.15	0.25	22.88
DUB174	910.83	922.93	12.10	13.9	1648	5290	-887	0.86	10.37	0.20	5.52	0.10	17.24
<i>includes</i> DUB174	911.43	916.72	5.29	6.1	1649	5290	-884	0.52	8.27	0.16	7.89	0.04	21.93
DUB174	924.59	925.95	1.36	1.6	1645	5289	-895	4.86	105.25	0.48	0.00	2.90	3.50
DUB174	930.65	931.40	0.75	0.9	1644	5288	-900	0.45	5.14	0.10	6.52	0.04	27.44
DUB174	932.57	933.55	0.98	1.1	1643	5288	-902	1.17	58.63	0.82	10.37	1.60	27.76
DUB174DPN													
DUB174DPN	No samples submitted for assay.												
DUB174W01													
DUB174W01	717.20	719.57	2.37	2.4	1721	5302	-699	0.19	15.86	0.32	17.38	0.01	25.21
DUB174W01	726.34	733.55	7.21	7.4	1720	5302	-710	7.14	221.62	0.24	0.04	1.10	4.67
DUB174W01	733.55	736.14	2.59	2.7	1719	5301	-715	0.13	4.83	0.13	13.19	0.01	30.17
DUB174W01	736.14	745.60	9.46	9.7	1719	5301	-721	1.11	25.50	0.83	1.39	0.13	17.00
DUB174W01	745.60	747.80	2.20	2.3	1718	5300	-727	0.27	3.79	0.23	8.19	0.02	28.50
DUB174W01	841.00	852.28	11.28	11.6	1708	5297	-828	0.68	9.53	0.31	5.05	0.08	12.68
<i>includes</i> DUB174W01	848.13	850.90	2.77	2.9	1708	5296	-831	1.56	12.85	0.33	12.80	0.01	18.12
DUB174W01	863.00	863.45	0.45	0.5	1707	5295	-844	0.38	4.11	0.10	5.98	0.00	4.07
DUB174W01	871.37	879.00	7.63	7.9	1706	5293	-856	0.59	21.41	0.25	1.17	0.21	8.50
DUB174W01	898.18	899.18	1.00	1.0	1704	5290	-879	4.87	60.34	1.04	2.37	0.23	6.43
DUB174W01	900.75	903.30	2.55	2.6	1704	5290	-883	32.89	104.04	0.56	4.38	0.86	6.33
DUB174W01	910.75	911.15	0.40	0.4	1703	5288	-891	3.26	65.14	1.73	0.13	0.03	3.17
DUB174W01	919.90	936.10	16.20	16.7	1702	5286	-908	1.76	42.46	0.22	4.67	0.74	12.98
DUB174W01	941.40	941.60	0.20	0.2	1701	5284	-922	0.14	4.80	0.09	10.61	0.03	6.85
DUB174W01	944.95	945.74	0.79	0.8	1700	5284	-925	0.31	4.46	0.07	9.69	0.00	5.26
DUB174W01	953.81	959.33	5.52	5.7	1700	5282	-937	1.13	27.77	0.15	6.43	0.69	17.70
DUB174W01	969.32	969.71	0.39	0.4	1699	5281	-949	0.86	9.26	0.12	15.71	0.00	17.31
DUB174W01	999.00	999.53	0.53	0.5	1696	5277	-979	0.41	10.29	0.09	10.03	0.02	16.68
DUB174W02													
DUB174W02	741.31	758.98	17.67	18.2	1690	5345	-722	0.29	11.61	0.27	3.74	0.06	22.56
<i>includes</i> DUB174W02	752.31	753.31	1.00	1.0	1689	5346	-724	0.16	11.56	0.50	24.21	0.01	10.54
DUB174W02	764.25	767.64	3.39	3.5	1685	5348	-736	0.36	7.86	0.08	3.35	0.11	17.90
DUB174W02	805.11	805.75	0.64	0.7	1671	5355	-773	19.99	7.54	0.02	0.00	0.00	2.60
DUB174W02	818.84	842.40	23.56	24.3	1662	5360	-796	4.21	40.96	0.36	3.59	0.48	12.39
<i>includes</i> DUB174W02	818.84	819.40	0.56	0.6	1666	5358	-785	26.37	115.54	0.25	0.03	1.91	3.20

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB174W02 Cont.													
DUB174W02	820.28	824.27	3.99	4.1	1665	5358	-788	1.35	24.75	1.15	7.27	0.02	28.53
DUB174W02	824.27	831.11	6.84	7.0	1663	5359	-793	8.66	79.65	0.15	0.05	0.78	3.24
DUB174W02	831.11	834.53	3.42	3.5	1661	5360	-798	0.55	4.89	0.34	14.33	0.02	30.57
DUB174W02	834.53	841.87	7.34	7.6	1660	5361	-803	2.37	32.04	0.20	0.69	0.66	4.82
DUB174W02	846.35	849.80	3.45	3.6	1656	5363	-812	0.22	5.02	0.15	4.84	0.03	39.39
DUB174W02	935.48	936.27	0.79	0.8	1627	5382	-893	0.07	2.74	0.28	10.72	0.02	23.90
DUB174W03													
DUB174W03	735.15	764.84	29.69	30.6	1761	5296	-737	0.23	17.50	0.33	10.58	0.17	22.38
<i>includes</i>													
DUB174W03	735.15	738.95	3.80	3.9	1762	5298	-724	0.10	23.90	0.48	23.61	0.02	24.21
DUB174W03	749.75	764.84	15.09	15.5	1761	5295	-744	0.25	16.74	0.43	14.70	0.19	23.23
DUB174W03	851.20	855.65	4.45	4.6	1756	5272	-836	4.29	131.88	0.17	0.01	2.70	4.52
DUB174W03	855.65	861.68	6.03	6.2	1756	5271	-841	1.13	28.86	0.58	2.46	0.24	12.39
DUB174W03	886.45	888.45	2.00	2.1	1753	5263	-868	2.83	67.54	4.02	1.07	0.08	7.93
DUB174W03	901.00	906.92	5.92	6.1	1752	5258	-884	1.86	13.00	1.24	0.31	0.02	5.46
DUB174W03	909.73	910.50	0.77	0.8	1751	5257	-890	2.88	15.77	1.21	4.49	0.00	4.96
DUB174W03	926.36	934.36	8.00	8.2	1749	5251	-909	4.08	12.47	0.46	0.05	0.00	3.93
DUB174W03	945.91	946.50	0.59	0.6	1747	5247	-925	2.30	37.03	0.49	8.92	0.00	6.20
DUB174W03	970.25	990.80	20.55	21.2	1744	5238	-958	3.72	46.67	0.84	8.51	1.30	13.37
<i>includes</i>													
DUB174W03	984.25	985.25	1.00	1.0	1743	5237	-962	27.70	106.97	1.57	12.79	3.08	17.49
DUB174W04													
DUB174W04	Abandoned. No samples submitted for assay.												
DUB175													
DUB175	915.54	919.51	3.97	4.2	2135	5510	-901	0.23	31.74	0.14	1.01	0.32	10.56
DUB175	936.00	993.57	57.57	60.4	2122	5506	-946	0.58	2.32	0.43	0.02	0.00	7.00
<i>includes</i>													
DUB175	985.73	986.04	0.31	0.3	1562	5298	-599	11.59	109.37	15.82	1.23	0.00	37.90
DUB175	1039.90	1040.22	0.32	0.4	2113	5499	-1018	112.11	356.57	0.34	0.13	2.74	5.79
DUB176													
DUB176	643.34	645.92	2.58	3.0	1710	5075	-638	3.52	97.83	0.14	10.57	0.84	20.40
DUB176	672.33	680.00	7.67	9.0	1705	5070	-669	0.22	12.95	0.08	1.03	0.43	21.85
DUB176	689.34	693.63	4.29	5.0	1702	5068	-683	0.87	12.94	0.48	6.06	0.13	20.85
DUB177													
DUB177	668.60	668.84	0.24	0.3	1565	5299	-594	0.14	162.17	0.09	9.93	1.91	8.72
DUB177	670.77	678.63	7.86	9.5	1562	5298	-599	0.12	5.68	0.09	7.79	0.01	15.15
<i>includes</i>													
DUB177	670.77	676.88	6.11	7.4	1562	5298	-599	0.12	6.00	0.10	9.27	0.01	15.42
DUB177	685.58	692.00	6.42	7.8	1555	5297	-612	3.87	106.87	0.23	0.01	1.08	3.97
DUB177	753.37	755.36	1.99	2.4	1522	5292	-668	0.66	17.62	0.17	7.96	0.33	30.71
DUB177	934.05	934.26	0.21	0.3	1433	5282	-824	3.12	25.37	0.64	3.04	0.33	11.33
DUB178													
DUB178	No significant values.												
DUB179													
DUB179	957.48	966.24	8.76	10.1	1989	5281	-882	2.67	22.62	0.89	11.01	0.14	25.12

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated Vertical thickness meters ⁽²⁾	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB179 Cont.													
DUB179	967.06	969.60	2.54	2.9	1987	5281	-888	40.84	44.80	0.37	0.03	0.10	11.74
DUB179	972.00	973.42	1.42	1.6	1985	5281	-892	4.32	8.57	0.14	0.00	0.00	5.73
DUB179W01													
DUB179W01	960.00	963.10	3.10	3.6	1991	5272	-880	3.83	10.48	0.02	0.96	0.15	13.58
DUB179W01	963.10	973.54	10.44	12.0	1988	5271	-886	9.29	34.43	0.78	7.24	0.25	26.36
DUB179W01	973.54	978.88	5.34	6.1	1985	5270	-893	2.21	2.80	0.17	0.01	0.00	5.79
DUB179W02													
DUB179W02	952.50	987.80	35.30	40.6	1986	5333	-889	2.42	26.24	1.03	0.31	0.05	13.11
<i>includes</i>													
DUB179W02	963.80	966.12	2.32	2.7	1989	5333	-884	14.85	107.84	2.74	1.73	0.26	15.32
DUB179W02	1226.22	1233.26	7.04	8.1	1915	5352	-1038	1.23	12.45	0.22	11.44	0.09	14.46
DUB179W02	1236.26	1237.26	1.00	1.2	1915	5352	-1038	16.05	5.49	0.04	1.58	0.00	3.20
DUB179W03													
DUB179W03	970.40	980.27	9.87	11.4	1915	5300	-850	0.42	14.06	0.50	1.57	0.20	20.12
DUB179W03	1063.55	1069.55	6.00	6.9	1856	5306	-920	3.78	9.60	0.76	0.09	0.02	4.13
<i>includes</i>													
DUB179W03	1063.55	1064.55	1.00	1.2	1857	5306	-918	17.52	32.57	2.32	0.24	0.00	5.70
DUB179W04													
DUB179W04	969.00	988.90	19.90	22.9	1931	5249	-862	0.98	10.67	0.36	4.94	0.05	31.19
<i>includes</i>													
DUB179W04	982.72	988.90	6.18	7.1	1927	5249	-867	1.74	25.22	0.92	8.16	0.14	30.74
DUB179W05													
DUB179W05	962.70	970.11	7.41	8.5	2043	5300	-608	3.33	25.47	0.89	3.64	0.17	18.99
<i>includes</i>													
DUB179W05	967.43	968.43	1.00	1.2	2043	5300	-609	16.29	55.54	2.04	2.39	0.15	22.33
DUB179W05	972.47	973.76	1.29	1.5	2041	5300	-614	4.66	11.73	0.85	0.04	0.02	13.36
DUB179W05	987.49	987.70	0.21	0.2	2037	5300	-628	5.79	15.43	1.31	0.07	0.00	10.68
DUB179W05	991.64	992.19	0.55	0.6	2035	5300	-632	2.17	11.34	0.44	0.03	0.00	9.50
DUB179W06													
DUB179W06	Abandoned. No samples submitted for assay.												
DUB179W07													
DUB179W07	Assays pending.												
DUB180													
DUB180	No significant values.												
DUB181													
DUB181	889.20	899.19	9.99	11.5	1463	5022	-831	0.55	8.93	0.15	2.17	0.18	12.57
DUB182													
DUB182	743.94	747.31	3.37	3.7	1645	5443	-740	0.28	18.48	0.12	2.26	0.30	5.39
DUB182	774.22	791.79	17.57	19.3	1637	5438	-776	4.79	46.76	0.78	1.54	0.52	7.71
<i>includes</i>													
DUB182	779.27	781.21	1.94	2.1	1638	5438	-774	26.00	116.92	2.76	0.41	0.31	11.38
DUB182	787.00	791.79	4.79	5.3	1636	5437	-782	2.96	68.54	0.62	2.93	1.22	12.02
DUB182	906.77	908.00	1.23	1.4	1609	5421	-896	0.40	6.22	0.30	7.90	0.08	23.79

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core ⁽¹⁾ length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB183													
DUB183	718.58	719.00	0.42	0.5	1753	5198	-710	0.21	14.74	0.05	30.25	0.03	18.26
DUB183	722.95	742.00	19.05	21.4	1749	5197	-723	0.35	37.49	0.31	8.69	1.11	20.14
<i>includes</i> DUB183	728.82	734.90	6.08	6.8	1749	5197	-723	0.35	34.95	0.30	20.80	1.40	22.81
DUB183	862.80	867.40	4.60	5.2	1716	5182	-851	0.11	14.10	0.15	1.99	0.25	25.79
DUB183	930.35	932.33	1.98	2.2	1699	5174	-914	0.15	9.45	0.15	10.47	0.04	7.17
DUB183	973.12	974.90	1.78	2.0	1688	5168	-955	0.22	5.64	0.18	4.02	0.04	7.39
DUB184													
DUB184	1229.00	1249.00	20.00	20.5	2586	5863	-1223	0.20	0.87	0.35	0.00	0.00	2.62
DUB184DPN													
DUB184DPN	No significant values.												
DUB185													
DUB185	976.94	987.77	10.83	12.2	2203	5347	-966	6.50	75.47	2.36	0.30	0.10	14.41
<i>includes</i> DUB185	980.90	986.90	6.00	6.8	2203	5347	-968	10.42	117.49	3.39	0.43	0.07	12.86
DUB185	990.77	1007.32	16.55	18.6	2199	5346	-982	1.69	4.56	0.37	0.00	0.00	9.45
<i>includes</i> DUB185	1006.86	1007.32	0.46	0.5	2197	5346	-990	16.29	18.17	1.65	0.02	0.00	5.57
DUB185W01													
DUB185W01	986.35	1017.00	30.65	34.5	2184	5299	-975	2.62	19.80	0.47	0.12	0.11	7.46
<i>includes</i> DUB185W01	995.78	996.00	0.22	0.2	2186	5299	-969	10.22	68.57	2.03	0.24	0.03	12.03
DUB185W01	1004.83	1008.42	3.59	4.0	2183	5298	-980	5.79	54.49	2.14	0.24	0.00	7.68
DUB185W01	1006.66	1007.42	0.76	0.9	2183	5298	-980	16.35	145.03	5.56	0.75	0.00	8.60
DUB185W01	1014.00	1017.00	3.00	3.4	2181	5297	-988	12.87	10.74	0.22	0.00	0.00	4.40
DUB185W01	1015.00	1016.00	1.00	1.1	2181	5297	-988	33.19	16.46	0.18	0.00	0.00	3.65
DUB185W02													
DUB185W02	Assays pending.												
DUB185W03													
DUB185W03	Assays pending.												
DUB186													
DUB186	905.57	907.55	1.98	2.0	2076	5379	-894	0.21	30.05	0.32	4.16	0.01	17.23
DUB186	911.78	916.18	4.40	4.5	2076	5378	-902	0.48	39.63	0.47	1.51	0.76	18.85
DUB186	922.80	928.25	5.45	5.6	2076	5378	-913	2.60	16.69	1.00	0.06	0.00	9.84
DUB187													
DUB187	642.15	642.63	0.48	0.5	1704	5177	-635	0.27	159.09	0.17	10.62	1.14	29.76
DUB187	651.52	658.00	6.48	6.8	1703	5174	-647	0.21	15.21	0.00	1.15	0.20	14.40
DUB187DPN													
DUB187DPN	859.00	860.00	1.00	1.1	1679	5133	-846	3.39	1.71	0.03	0.00	0.02	2.17
DUB187DPN	920.00	923.00	3.00	3.2	1670	5120	-906	1.15	49.03	0.12	0.82	0.73	6.31
DUB188													
DUB188	954.10	955.10	1.00	1.1	2159	5212	-946	3.87	0.69	0.02	0.02	0.00	8.19
DUB188	957.10	964.45	7.35	8.3	2158	5212	-952	1.40	36.08	0.15	0.06	0.36	9.62
<i>includes</i> DUB188	958.10	959.10	1.00	1.1	2158	5212	-950	4.46	73.37	0.23	0.02	0.67	7.84

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB188 Cont.													
DUB188	964.45	967.15	2.70	3.0	2156	5212	-957	0.72	7.67	0.19	17.93	0.04	33.66
DUB189													
DUB189	1141.00	1145.00	4.00	4.3	2314	5889	-1118	6.99	54.69	0.19	1.02	0.00	4.03
<i>includes</i>													
DUB189	1143.00	1145.00	2.00	2.1	2314	5889	-1119	12.36	94.11	0.31	1.87	0.00	5.18
DUB189	1155.00	1161.00	6.00	6.4	2309	5890	-1132	3.57	8.80	0.38	0.26	0.03	2.58
<i>includes</i>													
DUB189	1155.00	1158.00	3.00	3.2	2310	5890	-1131	5.86	13.71	0.64	0.27	0.04	2.96
DUB189	1188.30	1192.00	3.70	4.0	2300	5892	-1163	21.79	30.63	0.09	0.15	0.01	3.02
<i>includes</i>													
DUB189	1191.00	1192.00	1.00	1.1	2299	5892	-1164	76.66	101.83	0.15	0.41	0.05	3.65
DUB190													
DUB190	629.91	631.00	1.09	1.2	1661	5208	-627	0.19	21.62	0.05	29.24	0.22	12.26
<i>includes</i>													
DUB190	629.91	630.62	0.71	0.8	1661	5208	-627	0.07	13.37	0.04	43.70	0.03	9.66
DUB190	794.50	795.54	1.04	1.2	1633	5187	-788	0.47	16.44	0.24	6.62	0.25	18.57
DUB190	803.00	806.00	3.00	3.4	1631	5186	-797	7.67	100.26	0.12	0.14	0.29	9.68
DUB190	806.00	813.00	7.00	7.9	1630	5185	-802	0.60	27.79	0.15	5.20	0.31	21.85
DUB190	834.00	870.00	36.00	40.5	1622	5180	-843	0.77	16.17	0.26	4.30	0.16	11.11
<i>includes</i>													
DUB190	844.25	856.48	12.23	13.8	1622	5180	-841	1.20	24.66	0.29	9.95	0.36	14.10
DUB190	886.28	923.20	36.92	41.5	1612	5172	-894	1.39	33.80	0.36	6.38	0.90	14.46
<i>includes</i>													
DUB190	890.72	904.55	13.83	15.6	1613	5173	-887	0.97	27.81	0.33	9.42	0.76	18.17
DUB190	909.55	917.66	8.11	9.1	1610	5171	-903	3.54	66.58	0.72	10.68	2.19	21.75
DUB191													
DUB191	843.00	846.95	3.95	4.4	1951	5386	-841	0.24	22.03	0.57	2.84	0.08	24.74
DUB191	862.00	880.00	18.00	20.3	1947	5385	-867	1.56	40.86	1.13	5.84	0.09	15.74
<i>includes</i>													
DUB191	862.00	871.00	9.00	10.1	1948	5385	-863	0.95	37.03	1.32	7.08	0.05	18.25
DUB191	882.00	886.00	4.00	4.5	1945	5385	-881	0.54	12.51	0.72	3.90	0.04	14.76
DUB191	905.70	908.00	2.30	2.6	1942	5384	-903	0.14	25.21	0.17	9.25	0.08	11.21
DUB192													
DUB192	869.60	870.66	1.06	1.1	1480	5116	-830	0.72	158.81	0.30	8.75	1.84	21.26
DUB192	870.66	871.56	0.90	0.9	1480	5116	-831	9.22	139.89	0.26	0.23	1.20	3.04
DUB193													
DUB193	983.08	984.08	1.00	1.1	2272	5474	-963	0.07	7.89	0.32	2.03	0.03	15.56
DUB193	997.08	1030.07	32.99	35.1	2262	5474	-992	1.24	1.21	0.27	0.00	0.00	3.44
DUB193	1215.34	1216.34	1.00	1.1	2197	5472	-1183	0.14	1.03	0.04	1.99	0.00	2.73
DUB194													
DUB194	795.00	796.00	1.00	1.0	1842	5402	-792	3.70	41.49	0.04	0.00	0.32	8.89
DUB194	809.00	811.00	2.00	2.1	1840	5403	-807	5.52	193.71	0.12	0.00	0.56	4.70
DUB194	812.90	820.00	7.10	7.3	1839	5403	-813	0.24	10.14	0.05	6.43	0.06	17.19
<i>includes</i>													
DUB194	816.40	817.21	0.81	0.8	1839	5403	-813	0.14	8.57	0.15	43.80	0.04	13.71
DUB194	860.99	891.31	30.32	31.1	1831	5403	-872	2.32	20.06	0.41	4.14	0.32	7.25
<i>includes</i>													
DUB194	871.00	885.36	14.36	14.7	1831	5404	-874	3.37	21.29	0.62	7.10	0.28	8.57

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB194 Cont.													
DUB194	874.53	876.81	2.28	2.3	1831	5404	-872	3.80	17.11	1.29	20.49	0.02	13.74
DUB194	914.70	916.00	1.30	1.3	1825	5404	-911	0.13	2.29	0.05	2.25	0.00	2.52
DUB194	926.10	929.54	3.44	3.5	1824	5405	-923	7.55	24.99	0.62	1.18	0.02	3.01
DUB194	966.18	973.40	7.22	7.4	1817	5405	-965	2.36	11.45	0.38	1.29	0.05	9.07
DUB194	997.00	999.50	2.50	2.6	1813	5405	-993	1.70	89.14	0.61	3.18	1.38	13.75
DUB194	1039.00	1050.00	11.00	11.3	1806	5405	-1039	0.77	5.02	0.17	2.90	0.00	4.11
DUB194	1055.80	1065.45	9.65	9.9	1804	5405	-1055	2.62	19.41	0.40	8.89	0.19	8.61
<i>includes</i>													
DUB194	1055.80	1058.35	2.55	2.6	1804	5405	-1051	1.60	28.12	0.28	11.77	0.72	10.56
DUB194	1063.12	1065.45	2.33	2.4	1803	5405	-1058	8.53	45.89	1.17	23.16	0.00	13.93
DUB195													
DUB195	744.00	745.00	1.00	1.0	1723	5603	-740	0.07	16.80	0.29	5.20	0.75	15.23
DUB195	784.00	788.00	4.00	4.2	1717	5602	-781	3.88	62.83	0.17	1.80	0.28	9.39
DUB195	810.00	829.00	19.00	19.8	1711	5602	-815	9.70	54.94	1.23	10.70	0.12	17.88
<i>includes</i>													
DUB195	810.00	817.00	7.00	7.3	1712	5602	-809	13.86	46.38	0.66	0.32	0.18	3.90
DUB195	817.00	829.00	12.00	12.5	1711	5602	-818	7.27	59.93	1.57	16.75	0.08	26.04
DUB195W01													
DUB195W01	809.50	814.50	5.00	5.2	1713	5601	-802	13.23	26.88	0.58	0.33	0.11	4.15
DUB195W01	814.50	825.68	11.18	11.6	1711	5601	-810	11.08	76.67	2.49	19.90	0.18	27.07
DUB195W02													
DUB195W02	834.00	840.74	6.74	7.0	1705	5546	-821	12.68	13.39	0.25	0.46	0.06	3.50
DUB195W02	840.74	841.37	0.63	0.7	1705	5545	-824	2.71	28.46	0.77	16.38	0.37	21.59
DUB195W02	841.37	844.50	3.13	3.3	1704	5545	-826	7.03	32.77	0.09	0.31	0.27	2.12
DUB195W03													
DUB195W03	840.50	874.92	34.42	35.8	1764	5562	-848	4.44	25.14	0.27	0.47	0.69	3.58
<i>includes</i>													
DUB195W03	840.50	841.00	0.50	0.5	1764	5564	-832	29.31	104.91	1.31	1.80	0.26	5.20
DUB195W03	848.75	849.40	0.65	0.7	1764	5563	-840	115.47	338.40	4.54	0.44	0.12	8.50
DUB195W03	870.00	876.40	6.40	6.7	1764	5560	-864	6.11	81.40	0.49	3.98	3.73	8.04
<i>includes</i>													
DUB195W03	874.92	875.16	0.24	0.2	1764	5559	-866	60.93	196.11	2.13	3.53	2.14	19.19
DUB195W04													
DUB195W04	786.53	787.53	1.00	1.0	1747	5632	-778	5.62	26.74	0.03	0.00	0.38	4.70
DUB195W04	791.53	793.87	2.34	2.4	1747	5632	-784	1.14	33.77	0.54	4.01	0.32	14.42
DUB195W04	820.95	824.30	3.35	3.5	1747	5636	-813	6.98	10.50	0.42	0.15	0.06	3.27
DUB195W04	824.30	830.04	5.74	6.0	1746	5636	-818	3.48	43.98	1.15	11.40	0.27	26.51
DUB195W04	842.22	850.74	8.52	8.9	1746	5638	-837	3.05	37.10	0.08	0.02	0.25	2.08
DUB195W05													
DUB195W05	754.09	754.91	0.82	0.9	1696	5631	-739	0.62	28.80	0.39	12.33	0.60	29.73
DUB195W05	755.91	756.91	1.00	1.0	1696	5631	-741	15.50	37.37	0.07	0.02	0.05	7.74
DUB195W05	761.10	761.70	0.60	0.6	1695	5632	-746	10.66	145.03	0.38	0.04	0.03	10.41
DUB195W05	773.25	777.38	4.13	4.3	1691	5633	-759	9.10	55.81	1.51	3.23	0.12	13.36
DUB195W05	777.38	785.49	8.11	8.4	1689	5634	-765	1.58	19.49	0.44	18.82	0.03	29.45
DUB195W05	785.49	790.49	5.00	5.2	1688	5635	-771	8.89	115.89	0.30	1.12	1.45	4.01
DUB196													
DUB196	1257.00	1260.00	3.00	3.1	2624	6202	-1248	1.50	11.77	1.27	0.34	0.00	5.19

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated Vertical thickness meters ⁽²⁾	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB196 Cont.													
DUB196	1364.00	1365.00	1.00	1.0	2610	6207	-1353	2.13	36.34	2.00	0.18	0.00	5.82
DUB196	1378.00	1379.00	1.00	1.0	2608	6207	-1367	1.89	23.66	2.39	0.14	0.00	6.03
DUB196	1388.00	1389.00	1.00	1.0	2606	6208	-1377	2.50	11.66	1.15	0.07	0.02	3.80
DUB196	1391.00	1392.00	1.00	1.0	2606	6208	-1380	7.30	17.49	2.14	0.08	0.00	4.47
DUB196	1395.00	1396.00	1.00	1.0	2606	6208	-1384	9.50	24.00	2.95	0.10	0.00	5.21
DUB197													
DUB197	966.35	1004.50	38.15	40.8	2062	5709	-979	4.32	17.16	0.39	0.14	0.05	3.73
<i>includes</i>													
DUB197	975.00	979.50	4.50	4.8	2064	5709	-971	5.61	44.43	1.53	0.17	0.25	7.48
DUB197	989.20	1004.50	15.30	16.4	2060	5710	-990	8.26	25.98	0.36	0.27	0.03	3.18
DUB197	998.00	999.00	1.00	1.1	2060	5710	-992	81.09	247.89	2.67	0.68	0.02	12.49
DUB197	1060.45	1060.95	0.50	0.5	2048	5711	-1053	4.05	8.57	0.13	0.00	0.02	3.33
DUB197	1067.25	1068.85	1.60	1.7	2047	5711	-1060	4.78	9.34	0.21	0.43	0.03	3.70
DUB198													
DUB198	902.27	906.68	4.41	5.3	1950	5117	-863	0.23	11.16	0.28	12.68	0.06	29.56
DUB198	909.50	914.00	4.50	5.4	1947	5118	-870	5.07	90.37	0.09	0.02	0.46	5.50
<i>includes</i>													
DUB198	913.33	914.00	0.67	0.8	1947	5118	-872	18.48	294.86	0.09	0.00	1.97	2.96
DUB198W01													
DUB198W01	Assays pending.												
DUB198W02													
DUB198W02	Assays pending.												
DUB199													
DUB199	848.15	866.00	17.85	17.8	1908	5194	-849	2.00	13.16	0.75	7.47	0.04	29.43
<i>includes</i>													
DUB199	848.15	861.00	12.85	12.8	1908	5194	-847	0.58	6.12	0.34	10.31	0.03	35.03
DUB199	861.00	866.00	5.00	5.0	1908	5193	-856	5.63	31.26	1.81	0.16	0.07	15.06
DUB199	876.00	877.00	1.00	1.0	1907	5191	-868	3.84	5.14	0.26	0.00	0.00	9.49
DUB199W01													
DUB199W01	853.05	864.82	11.77	11.8	1909	5193	-843	0.83	11.88	0.54	12.48	0.35	35.74
DUB199W01	864.82	873.95	9.13	9.1	1910	5191	-853	2.14	12.08	0.78	0.07	0.02	10.73
DUB199W02													
DUB199W02	Abandoned metallurgical hole.												
DUB199W03													
DUB199W03	Abandoned metallurgical hole.												
DUB200													
DUB200	845.58	855.65	10.07	10.8	1802	5718	-844	11.96	64.19	1.92	3.43	0.27	9.38
<i>includes</i>													
DUB200	845.58	853.09	7.51	8.0	1803	5718	-843	15.21	81.36	2.43	4.57	0.34	11.66
DUB200	846.70	847.84	1.14	1.2	1803	5718	-843	4.69	65.09	2.77	15.16	0.01	25.30
DUB200	850.96	851.37	0.41	0.4	1803	5718	-843	84.45	260.91	3.14	1.28	0.36	6.43
DUB200W01													
DUB200W01	840.00	844.25	4.25	4.5	1805	5717	-831	0.32	59.39	0.71	0.00	0.00	11.40
	844.25	852.00	7.75	8.3	1804	5717	-837	11.00	80.03	2.63	5.33	0.20	14.72
	852.00	858.39	6.39	6.8	1803	5717	-844	3.88	15.45	0.31	0.31	0.07	3.76

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB200W02													
DUB200W02	849.00	856.26	7.26	7.8	1804	5718	-842	12.23	63.69	2.25	3.89	0.18	10.20
<i>includes</i>													
DUB200W02	849.00	851.00	2.00	2.1	1805	5718	-839	4.79	65.49	3.54	8.98	0.07	20.03
DUB200W02	851.00	856.26	5.26	5.6	1804	5718	-843	15.05	63.00	1.76	1.95	0.22	6.46
DUB200W02	857.77	862.48	4.71	5.0	1803	5718	-849	2.86	14.32	0.22	0.06	0.08	3.61
DUB200W03													
DUB200W03	Assays pending.												
DUB201													
DUB201	931.40	932.45	1.05	1.2	2056	5087	-912	5.04	130.29	0.17	0.00	0.45	9.45
DUB201	1162.59	1163.00	0.41	0.5	1991	5063	-1133	12.55	41.83	3.33	0.12	0.00	10.40
DUB202													
DUB202	No significant values.												
DUB203													
DUB203	998.60	999.93	1.33	1.4	2119	5900	-989	1.45	20.99	0.26	5.94	0.00	7.53
DUB203	1033.57	1034.80	1.23	1.3	2113	5904	-1024	22.67	59.08	1.29	0.09	0.05	7.43
<i>includes</i>													
DUB203	1034.37	1034.80	0.43	0.5	2113	5904	-1024	53.11	136.46	2.81	0.21	0.09	9.32
DUB204													
DUB204	761.00	763.00	2.00	2.1	1810	5423	-757	5.01	214.63	0.19	0.00	0.82	6.18
DUB204	765.68	766.37	0.69	0.7	1810	5423	-761	7.23	297.26	0.11	0.03	3.00	4.74
DUB204	840.92	860.43	19.51	20.7	1796	5421	-844	4.64	34.03	1.16	5.01	0.19	10.48
<i>includes</i>													
DUB204	840.92	846.01	5.09	5.4	1797	5421	-837	7.07	47.34	0.15	0.94	0.41	4.64
DUB204	846.01	857.57	11.56	12.3	1796	5421	-845	4.38	34.30	1.80	6.83	0.12	13.98
DUB204	862.75	863.58	0.83	0.9	1794	5421	-856	5.28	14.74	0.10	0.19	0.08	3.89
DUB204	871.00	878.00	7.00	7.4	1792	5421	-868	20.63	104.67	0.35	0.70	1.27	3.51
<i>includes</i>													
DUB204	874.00	876.00	2.00	2.1	1792	5421	-868	55.05	197.49	0.46	0.54	2.41	2.17
DUB204	884.00	887.00	3.00	3.2	1790	5421	-878	3.07	22.29	0.10	0.02	0.22	3.13
DUB204	900.00	901.00	1.00	1.1	1788	5420	-893	5.49	7.54	0.13	1.09	0.05	3.07
DUB204	911.12	913.00	1.88	2.0	1786	5420	-905	1.73	25.63	0.44	9.41	0.29	12.49
DUB204	950.00	951.00	1.00	1.1	1779	5419	-942	3.98	6.51	0.14	1.05	0.17	3.49
DUB204	957.00	970.00	13.00	13.8	1777	5419	-955	1.12	25.92	0.21	5.91	0.69	20.17
DUB204	975.39	978.38	2.99	3.2	1775	5419	-968	7.47	92.66	0.31	0.54	1.58	3.99
DUB204W01													
DUB204W01	839.05	845.00	5.95	6.3	1797	5423	-835	6.68	66.99	0.24	1.08	0.74	5.38
DUB204W01	845.00	860.18	15.18	16.1	1795	5423	-846	3.69	24.45	1.76	6.28	0.02	13.51
<i>includes</i>													
DUB204W01	845.00	848.72	3.72	3.9	1796	5423	-840	1.41	28.81	2.35	13.36	0.00	28.53
DUB204W01	848.72	860.18	11.46	12.1	1794	5423	-848	4.43	23.04	1.58	3.99	0.03	8.64
DUB204W01	860.18	864.00	3.82	4.0	1793	5423	-855	5.33	52.91	0.15	0.61	1.02	2.59
DUB204W01	870.00	875.00	5.00	5.3	1791	5423	-865	12.14	80.43	0.19	0.62	0.85	2.57
DUB204W01	880.59	883.00	2.41	2.6	1789	5423	-874	2.34	49.98	0.43	0.44	0.26	7.39
DUB204W01	895.00	899.42	4.42	4.7	1786	5423	-890	4.15	9.03	0.09	1.22	0.14	3.06
DUB204W01	909.59	910.37	0.78	0.8	1784	5423	-902	5.33	14.94	0.28	17.19	0.06	16.25
DUB204W01	953.13	968.00	14.87	15.8	1773	5424	-952	1.82	54.07	0.24	4.27	1.25	14.29
DUB204W01	976.64	978.60	1.96	2.1	1770	5424	-968	4.05	121.89	0.30	0.06	2.27	3.46

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB204W02													
DUB204W02	799.85	803.57	3.72	3.9	1823	5366	-789	0.41	19.23	0.14	4.78	0.12	14.05
<i>includes</i>													
DUB204W02	801.65	802.57	0.92	1.0	1823	5365	-789	0.14	14.40	0.09	14.51	0.03	24.81
DUB204W02	814.34	831.35	17.01	18.0	1822	5359	-809	0.22	12.17	0.67	26.96	0.03	17.12
DUB204W02	871.02	872.02	1.00	1.1	1819	5344	-855	4.56	72.69	0.20	0.02	0.96	2.12
DUB204W02	928.48	929.48	1.00	1.1	1815	5327	-910	3.09	23.31	0.86	0.32	0.12	4.89
DUB204W02	936.61	940.30	3.69	3.9	1813	5324	-919	13.83	98.28	0.44	1.65	0.98	11.95
<i>includes</i>													
DUB204W02	939.48	940.30	0.82	0.9	1813	5324	-920	54.55	300.00	0.53	0.13	3.26	3.43
DUB204W02	940.30	950.26	9.96	10.6	1812	5323	-925	1.71	55.07	0.33	9.58	0.81	15.06
DUB204W02	950.26	964.90	14.64	15.5	1810	5319	-937	4.55	2.64	0.05	0.02	0.00	3.93
DUB204W02	967.19	976.19	9.00	9.5	1808	5315	-950	1.07	26.06	0.32	1.88	0.30	9.25
DUB204W02	993.49	998.49	5.00	5.3	1806	5308	-973	4.64	111.70	0.63	0.66	2.77	3.99
DUB204W03													
DUB204W03	762.57	766.57	4.00	4.2	1818	5453	-760	1.97	144.43	0.13	0.00	0.56	4.46
DUB204W03	830.91	832.78	1.87	2.0	1809	5457	-826	0.50	10.79	0.10	5.41	0.11	16.23
DUB204W03	834.78	844.57	9.79	10.4	1808	5457	-834	5.40	59.11	1.98	2.14	0.17	9.24
DUB204W03	844.57	856.57	12.00	12.7	1806	5458	-845	1.17	13.99	0.86	7.86	0.01	27.08
DUB204W03	856.57	860.57	4.00	4.2	1805	5458	-852	4.64	39.43	0.52	0.41	0.89	5.96
DUB204W03	880.57	894.60	14.03	14.9	1800	5459	-881	3.53	26.78	0.41	1.21	0.08	2.33
<i>includes</i>													
DUB204W03	889.57	890.57	1.00	1.1	1800	5460	-884	17.21	65.83	1.17	4.43	0.18	3.62
DUB204W03	893.60	894.60	1.00	1.1	1799	5460	-887	19.27	134.74	1.83	0.66	0.03	4.54
DUB204W03	917.60	924.00	6.40	6.8	1795	5461	-914	3.27	53.83	0.61	0.95	0.24	9.87
DUB204W03	961.07	981.56	20.49	21.7	1786	5463	-963	2.18	39.56	0.49	5.98	0.26	25.81
DUB204W03	981.56	1006.00	24.44	25.9	1782	5463	-986	6.68	52.54	0.21	0.43	0.36	6.90
<i>includes</i>													
DUB204W03	982.00	985.00	3.00	3.2	1783	5463	-975	46.93	245.37	0.17	0.68	2.60	4.70
DUB204W04													
DUB204W04	806.14	811.34	5.20	5.5	1847	5364	-798	0.04	8.25	0.17	4.80	0.02	26.07
DUB204W04	834.94	843.43	8.49	9.0	1850	5356	-828	0.27	18.32	0.69	17.89	0.02	17.98
DUB204W04	914.94	917.66	2.72	2.9	1858	5336	-902	5.94	48.86	3.20	0.39	0.11	6.71
DUB204W04	929.80	930.53	0.73	0.8	1859	5333	-915	6.82	13.37	0.80	0.03	0.00	4.02
DUB204W04	937.00	938.00	1.00	1.1	1859	5330	-922	2.43	16.46	1.39	0.13	0.00	3.77
DUB204W04	947.00	948.00	1.00	1.1	1860	5327	-931	2.74	27.09	0.76	0.06	0.11	4.42
DUB204W04	972.00	976.00	4.00	4.2	1862	5319	-957	12.51	46.20	0.99	0.06	0.00	3.18
DUB205													
DUB205	786.45	803.90	17.45	18.3	1831	5186	-791	0.76	14.02	0.36	13.20	0.47	25.74
DUB205	803.90	815.55	11.65	12.2	1830	5184	-805	7.00	31.16	1.41	0.15	0.08	12.38
<i>includes</i>													
DUB205	803.90	809.75	5.85	6.1	1830	5185	-802	11.03	50.35	2.18	0.25	0.15	14.34
DUB205W01													
DUB205W01	788.09	810.27	22.18	23.3	1832	5182	-787	7.77	43.48	1.40	6.98	0.72	19.51
<i>includes</i>													
DUB205W01	788.09	791.48	3.39	3.6	1833	5183	-778	0.27	6.36	0.15	16.54	0.15	24.87
DUB205W01	794.10	795.08	0.98	1.0	1833	5182	-782	40.18	70.97	0.38	0.05	0.83	12.30
DUB205W01	791.48	797.96	6.48	6.8	1833	5182	-783	7.07	30.26	0.34	1.13	1.07	15.03
DUB205W01	797.96	803.56	5.60	5.9	1832	5181	-789	2.46	33.22	0.74	15.85	1.33	27.38
DUB205W01	803.56	810.27	6.71	7.0	1832	5180	-795	16.67	83.57	3.60	0.39	0.15	14.56

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB205W01 Cont.													
DUB205W01	810.27	817.87	7.60	8.0	1831	5179	-802	3.33	7.99	0.49	0.04	0.01	10.01
DUB206													
DUB206	733.53	738.00	4.47	4.7	1737	5406	-719	0.88	36.05	0.05	0.00	0.21	7.22
DUB206	819.00	828.60	9.60	10.1	1712	5406	-804	2.93	26.43	2.37	3.87	0.07	16.84
DUB206	848.37	852.00	3.63	3.8	1705	5406	-829	7.97	10.90	0.18	3.05	0.01	3.29
DUB206	932.60	935.15	2.55	2.7	1681	5407	-909	0.44	10.17	0.38	8.42	0.33	21.13
DUB206	936.65	937.43	0.78	0.8	1680	5407	-912	0.31	13.71	0.18	6.09	0.72	11.60
DUB206W01													
DUB206W01	818.28	829.60	11.32	11.9	1712	5407	-804	4.99	29.77	1.65	4.10	0.18	15.67
<i>includes</i>													
DUB206W01	818.28	820.62	2.34	2.5	1714	5407	-800	15.44	68.30	0.78	0.26	0.78	3.65
DUB206W01	820.62	824.67	4.05	4.3	1713	5407	-803	2.34	27.48	2.73	5.71	0.01	24.39
DUB206W01	824.67	827.20	2.53	2.7	1712	5407	-806	3.33	18.64	1.79	1.72	0.03	9.35
DUB206W01	827.20	829.60	2.40	2.5	1711	5407	-808	1.04	7.81	0.54	7.62	0.04	19.31
DUB206W02													
DUB206W02	763.09	768.28	5.19	5.4	1769	5371	-752	0.20	9.22	0.15	8.26	0.06	26.27
DUB206W02	841.61	856.81	15.20	16.0	1754	5359	-833	2.87	17.83	0.20	1.34	0.40	3.74
DUB206W02	856.81	863.90	7.09	7.4	1752	5357	-844	3.45	13.90	0.40	5.87	0.14	11.52
DUB206W02	872.92	880.92	8.00	8.4	1749	5354	-860	3.13	24.00	0.27	1.75	0.50	6.24
DUB206W02	890.10	895.49	5.39	5.7	1746	5351	-875	1.69	27.15	0.17	0.35	0.29	2.51
DUB206W02	895.49	896.54	1.05	1.1	1746	5351	-878	1.31	26.10	1.37	5.11	0.02	18.92
DUB206W02	925.71	954.34	28.60	30.0	1737	5343	-921	0.71	19.86	0.38	4.73	0.29	15.58
<i>includes</i>													
DUB206W02	925.71	934.35	8.64	9.1	1739	5345	-911	0.71	13.30	0.16	4.48	0.15	16.26
DUB206W02	934.35	944.03	9.68	10.2	1738	5343	-920	0.79	23.12	0.33	1.24	0.39	8.59
DUB206W02	944.03	954.31	10.28	10.8	1736	5341	-930	0.63	22.29	0.60	8.22	0.32	21.60
DUB206W03													
DUB206W03	824.55	830.18	5.63	5.9	1742	5450	-812	2.13	51.26	0.65	3.86	0.50	10.12
DUB206W03	833.63	853.95	20.32	21.3	1740	5452	-828	6.95	54.50	2.66	3.11	0.12	13.39
DUB206W03	858.87	864.87	6.00	6.3	1737	5454	-846	2.93	10.17	0.27	0.70	0.03	1.97
DUB206W03	870.92	872.76	1.84	1.9	1736	5455	-855	1.01	15.86	0.47	2.97	0.28	15.57
DUB206W03	876.48	877.48	1.00	1.1	1735	5455	-861	9.33	8.57	0.17	0.38	0.09	7.70
DUB206W03	953.64	970.17	16.53	17.4	1722	5465	-944	8.39	28.85	0.29	1.83	0.46	4.59
<i>includes</i>													
DUB206W03	956.64	958.64	2.00	2.1	1723	5465	-940	61.51	50.40	0.28	1.45	0.25	4.18
DUB207													
DUB207	844.59	860.43	15.84	16.6	1777	5519	-836	10.93	46.86	0.64	2.07	0.28	5.93
<i>includes</i>													
DUB207	845.46	845.79	0.33	0.3	1779	5519	-829	2.88	55.20	1.24	10.02	0.69	24.00
DUB207	858.60	859.43	0.83	0.9	1776	5519	-842	74.57	36.34	1.15	0.98	0.28	5.20
DUB207	867.43	869.43	2.00	2.1	1773	5518	-851	4.37	15.77	0.33	0.20	0.02	2.32
DUB207	886.09	888.63	2.54	2.7	1769	5518	-870	17.39	56.92	0.66	0.82	0.07	3.25
DUB207	895.63	898.80	3.17	3.3	1766	5518	-879	1.65	24.31	0.53	4.31	0.38	21.87
<i>includes</i>													
DUB207	897.23	898.80	1.57	1.6	1766	5518	-880	0.95	14.06	0.30	6.88	0.03	38.34
DUB207	905.14	908.55	3.41	3.6	1764	5517	-889	1.47	5.63	0.10	4.35	0.06	14.26

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB207 Cont.													
DUB207	984.00	985.00	1.00	1.1	1745	5515	-964	5.38	58.63	0.07	0.00	0.70	3.20
DUB208													
DUB208	834.24	848.83	14.59	14.9	1878	5227	-827	0.74	9.03	0.28	14.20	0.49	31.65
DUB208	848.83	860.20	11.37	11.6	1878	5226	-840	5.97	16.85	0.89	0.09	0.01	12.24
<i>includes</i>													
DUB208	855.83	859.53	3.70	3.8	1877	5226	-843	10.80	16.53	0.86	0.06	0.00	16.60
DUB208W01													
DUB208W01	830.95	845.41	14.46	14.7	1878	5227	-823	0.55	8.18	0.20	11.58	0.43	32.78
DUB208W01	845.41	856.69	11.28	11.5	1877	5225	-836	14.22	38.09	1.61	0.38	0.02	13.95
DUB208W01	861.69	862.69	1.00	1.0	1876	5224	-847	3.46	8.23	0.45	0.03	0.00	6.90
DUB209													
DUB209	610.58	611.01	0.43	0.5	1874	5848	-597	5.25	38.74	0.39	5.11	1.65	13.47
DUB210													
DUB210	991.69	992.00	0.31	0.3	2093	5601	-971	0.51	16.11	0.20	10.18	0.43	8.50
DUB210	1002.24	1005.72	3.48	3.4	2094	5600	-983	7.19	56.33	0.09	0.00	0.90	1.20
DUB210	1016.53	1016.76	0.23	0.2	2095	5600	-996	24.45	132.69	0.09	0.04	1.58	0.84
DUB210	1069.39	1072.39	3.00	2.9	2098	5599	-1050	5.02	8.00	0.02	0.01	0.07	4.78
DUB210	1023.56	1060.41	36.85	36.1	2096	5600	-1021	13.83	134.90	0.30	0.14	1.51	1.82
<i>includes</i>													
DUB210	1040.50	1041.07	0.57	0.6	2096	5600	-1020	65.83	254.40	0.65	0.00	3.75	0.72
DUB210	1057.78	1059.00	1.22	1.2	2097	5599	-1037	97.47	308.69	0.26	0.00	1.30	0.72
DUB210DPN													
DUB210DPN	No significant values.												
DUB211													
DUB211	905.00	910.70	5.70	5.5	2005	5294	-874	2.62	89.38	0.19	1.16	4.17	10.27
DUB211	917.08	926.77	9.69	9.3	2007	5294	-888	3.60	19.60	0.34	4.46	0.17	21.37
<i>includes</i>													
DUB211	920.74	922.74	2.00	1.9	2007	5294	-888	11.85	51.26	0.99	7.02	0.08	19.26
DUB211	929.59	934.08	4.49	4.3	2008	5294	-898	2.35	23.92	1.10	7.60	0.12	23.20
DUB212													
DUB212	757.65	757.88	0.23	0.2	1754	5789	-721	0.21	30.86	0.03	3.30	1.00	6.08
DUB213													
DUB213	896.28	939.15	42.87	45.9	1915	5456	-909	1.01	10.22	0.53	15.68	0.26	22.85
<i>includes</i>													
DUB213	909.85	934.40	24.55	26.3	1915	5456	-913	0.37	4.24	0.38	20.74	0.17	26.67
DUB213	939.15	947.15	8.00	8.6	1912	5454	-934	5.57	73.54	0.14	0.03	1.33	1.30
DUB213	976.80	979.80	3.00	3.2	1908	5450	-968	3.01	15.66	0.45	0.04	0.01	5.40
DUB213	1040.00	1040.55	0.55	0.6	1901	5442	-1030	4.05	4.11	0.02	2.15	0.08	1.39
DUB213	1066.43	1066.76	0.33	0.4	1897	5439	-1055	11.59	52.11	1.93	0.08	0.02	3.17
DUB214													
DUB214	762.00	764.50	2.50	2.7	1797	5109	-743	0.32	40.80	0.15	5.97	0.87	24.00
<i>includes</i>													
DUB214	762.50	763.50	1.00	1.1	1797	5109	-743	0.27	47.66	0.12	13.20	1.08	29.78
DUB214	764.77	767.17	2.40	2.6	1796	5109	-746	0.27	23.13	0.18	1.91	0.47	10.60
DUB214	774.87	775.27	0.40	0.4	1796	5107	-755	0.62	86.40	1.04	9.73	1.84	33.96

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB214 Cont.													
DUB214	777.21	777.67	0.46	0.5	1796	5106	-757	1.27	32.57	1.08	4.96	0.31	18.63
DUB214	781.04	793.87	12.83	13.7	1795	5104	-767	3.02	32.81	1.13	16.54	0.21	27.99
<i>includes</i>													
DUB214	781.04	791.04	10.00	10.7	1795	5104	-766	0.94	12.65	0.47	20.02	0.20	29.02
DUB214	791.04	793.87	2.83	3.0	1795	5103	-771	10.38	104.05	3.46	3.61	0.28	24.34
DUB214	907.00	910.00	3.00	3.2	1783	5077	-884	0.49	32.46	0.17	1.97	0.49	28.06
DUB215													
DUB215	595.61	595.75	0.14	0.1	1984	5802	-586	0.38	3.43	0.12	6.04	0.68	7.30
DUB215	810.64	810.81	0.17	0.2	1978	5785	-801	0.14	30.51	0.19	3.13	0.39	20.80
DUB215	937.91	987.08	49.17	52.6	1965	5770	-951	7.56	23.25	0.19	0.07	0.14	6.09
<i>includes</i>													
DUB215	937.91	948.15	10.24	11.0	1967	5773	-932	28.53	75.14	0.66	0.23	0.35	5.72
DUB215	960.70	961.70	1.00	1.1	1965	5770	-950	15.36	63.77	0.14	0.02	0.68	9.50
DUB215	986.08	987.08	1.00	1.1	1963	5768	-975	30.07	38.06	0.03	0.00	0.29	3.70
DUB216													
DUB216	723.23	733.38	0.15	0.2	1647	5611	-709	0.17	19.54	0.15	11.40	0.18	17.28
DUB216	736.93	742.82	5.89	6.3	1645	5611	-715	0.63	28.21	0.31	6.29	0.47	19.13
DUB216	751.48	759.57	8.09	8.7	1641	5612	-730	2.99	54.08	0.25	0.42	0.37	6.74
<i>includes</i>													
DUB216	751.48	752.12	0.64	0.7	1642	5612	-727	14.82	42.59	0.92	0.37	0.05	5.68
DUB217													
DUB217	884.94	888.66	3.72	4.0	2068	5454	-864	0.21	16.07	0.40	4.16	0.08	17.37
<i>includes</i>													
DUB217	887.18	887.98	0.80	0.9	2068	5454	-865	0.10	12.69	0.22	9.50	0.06	10.79
DUB217	899.90	904.00	4.10	4.4	2070	5452	-879	0.08	17.87	0.11	3.18	0.36	21.07
<i>includes</i>													
DUB217	901.08	901.61	0.53	0.6	2069	5452	-878	0.14	39.43	0.19	13.55	0.30	18.87
DUB217	940.24	955.00	14.76	15.8	2074	5443	-924	2.86	11.02	0.78	0.02	0.00	7.42
<i>includes</i>													
DUB217	941.52	942.23	0.71	0.8	2074	5444	-918	19.54	42.17	2.42	0.06	0.00	17.81
DUB217	951.78	955.00	3.22	3.4	2075	5442	-929	6.43	34.12	2.09	0.10	0.00	9.48
DUB218													
DUB218	No significant values.												
DUB219													
DUB219	No significant values.												
DUB220													
DUB220	768.80	774.87	6.07	6.7	1583	5158	-745	3.16	60.35	0.17	0.06	0.78	9.79
DUB220	783.70	788.50	4.80	5.3	1579	5158	-758	2.74	67.08	0.11	6.47	0.99	22.66
DUB220	788.50	796.50	8.00	8.8	1577	5159	-764	3.63	40.69	0.12	2.32	0.41	19.32
<i>includes</i>													
DUB218	795.50	796.00	0.50	0.6	1576	5159	-767	26.54	39.77	0.07	0.88	0.22	7.13
DUB220W01													
DUB220W01	Abandoned.												
DUB220W02													
DUB220W02	792.00	798.10	6.10	6.7	1590	5114	-770	3.15	11.61	0.05	0.01	0.17	5.12
DUB220W02	798.10	808.50	10.40	11.4	1588	5114	-778	0.31	11.12	0.09	6.72	0.14	15.87
DUB220W02	822.40	825.50	3.10	3.4	1582	5114	-798	4.64	101.46	0.11	0.24	0.97	3.76

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB220W02 Cont.													
DUB220W02	826.50	829.50	3.00	3.3	1580	5114	-802	0.34	18.23	0.05	5.79	0.27	11.81
DUB220W02	849.00	851.00	2.00	2.2	1574	5114	-823	2.91	31.03	0.23	1.33	0.48	10.36
DUB220W02	858.60	858.80	0.20	0.2	1572	5114	-831	7.06	20.91	0.03	0.00	0.36	1.65
DUB220W02	869.00	875.00	6.00	6.6	1568	5114	-844	18.77	203.37	0.32	0.01	2.05	2.50
DUB220W02	878.40	894.00	15.60	17.2	1564	5114	-857	1.58	26.31	0.25	4.57	0.50	12.29
DUB220W02	898.20	906.45	8.25	9.1	1559	5113	-873	3.02	46.36	0.69	9.47	0.91	22.86
DUB221													
DUB221	905.29	912.56	7.27	7.6	1943	5604	-902	0.56	21.33	0.69	6.07	0.36	10.45
DUB221	912.56	918.00	5.44	5.7	1942	5604	-908	3.77	22.55	0.51	0.50	0.08	2.93
DUB221	972.46	972.71	0.25	0.3	1937	5605	-965	77.28	73.71	0.18	0.03	0.07	8.52
DUB221	1094.24	1104.21	9.97	10.5	1924	5605	-1091	6.58	26.47	0.76	0.11	0.00	5.54
DUB222													
DUB222	807.00	809.63	2.63	2.8	1738	5673	-786	6.93	30.35	0.10	0.42	0.07	2.83
DUB222	809.63	820.47	10.84	11.7	1736	5673	-793	2.96	72.53	2.92	7.83	0.04	23.68
DUB222	820.47	823.48	3.01	3.3	1734	5672	-800	15.10	176.90	0.87	1.76	0.55	4.95
DUB223													
DUB223	Assays pending.												
DUB224													
DUB224	Abandoned.												
DUB225													
DUB225	780.95	781.25	0.30	0.3	1728	5739	-759	32.16	81.94	0.03	0.00	0.41	0.78
DUB226													
DUB226	805.85	806.05	0.20	0.2	1885	5607	-799	0.27	40.46	0.29	6.25	0.77	27.54
DUB226	871.40	875.15	3.75	3.9	1875	5610	-866	0.85	24.33	0.28	2.71	0.26	16.09
DUB226	875.15	900.15	25.00	26.3	1873	5610	-880	3.94	14.61	0.28	0.15	0.01	3.17
<i>includes</i>													
DUB226	877.50	878.50	1.00	1.1	1874	5610	-871	16.56	34.97	0.06	0.04	0.00	1.25
DUB226	885.00	885.15	0.15	0.2	1873	5610	-878	12.51	161.49	5.33	2.85	0.09	9.23
DUB226	891.00	891.10	0.10	0.1	1872	5610	-883	139.75	205.03	0.80	5.29	0.00	9.73
DUB226	893.55	893.65	0.10	0.1	1872	5610	-886	15.50	260.23	9.04	1.30	0.38	13.58
DUB226	895.35	895.55	0.20	0.2	1872	5610	-888	125.42	436.11	9.40	2.34	0.19	17.41
DUB226	909.00	913.00	4.00	4.2	1869	5611	-903	25.98	129.80	0.13	1.05	1.22	3.01
DUB226	918.00	920.35	2.35	2.5	1868	5611	-911	2.42	4.20	0.03	0.33	0.05	1.57
DUB226	925.55	926.25	0.70	0.7	1867	5611	-918	7.41	53.14	0.28	0.72	0.71	5.85
DUB226	927.15	927.80	0.65	0.7	1867	5611	-919	3.12	9.94	0.40	1.71	0.02	17.69
DUB227													
DUB227	749.77	750.74	0.97	1.0	1759	5064	-744	0.58	86.74	0.08	12.50	2.23	18.84
DUB227	750.74	759.18	8.44	9.0	1758	5063	-749	2.39	92.77	0.12	0.01	0.41	5.58
DUB227	759.18	761.16	1.98	2.1	1758	5063	-754	0.10	13.32	0.25	8.18	0.36	23.95
DUB227	761.16	762.10	0.94	1.0	Geotechnical Sample - Assays Pending.								
DUB227	762.10	767.18	5.08	5.4	1757	5062	-758	0.22	9.50	0.21	18.36	0.13	29.89
DUB227	767.18	767.95	0.77	0.8	Geotechnical Sample - Assays Pending.								
DUB227	767.95	770.71	2.76	3.0	1757	5062	-763	0.24	6.60	0.21	17.08	0.01	34.80
DUB227	791.85	793.10	1.25	1.3	1755	5059	-786	4.16	72.89	3.00	1.24	0.01	16.06

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters	Estimated ⁽²⁾ Vertical thickness meters	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB228													
DUB228	600.00	601.00	1.00	1.1	1833	5652	-586	0.21	33.26	0.08	10.86	0.69	9.92
DUB228	846.12	849.05	2.93	3.1	1776	5664	-826	2.28	30.74	0.41	0.29	0.16	4.71
DUB228	849.05	855.32	6.27	6.6	1775	5664	-830	3.80	55.96	1.64	11.43	0.21	31.90
DUB228	855.32	858.14	2.82	3.0	1773	5665	-835	6.38	81.65	1.41	1.89	0.11	9.31
DUB228	863.91	869.74	5.83	6.1	1771	5666	-844	13.35	111.55	0.13	0.19	0.42	4.23
<i>includes</i>													
DUB228	866.74	867.74	1.00	1.1	1770	5666	-845	66.00	416.91	0.08	0.30	1.54	1.31
DUB229													
DUB229	862.69	864.84	2.15	2.3	1821	5698	-832	1.71	57.56	0.53	0.56	1.94	4.69
DUB229	864.84	869.34	4.50	4.8	1821	5698	-835	1.90	37.69	1.27	18.25	0.32	29.15
DUB229	869.34	881.00	11.66	12.5	1819	5697	-843	13.08	38.40	1.14	0.94	0.08	7.26
<i>includes</i>													
DUB229	871.47	871.90	0.43	0.5	1820	5697	-839	178.97	260.57	0.71	1.38	0.64	4.87
DUB230													
DUB230	855.00	855.25	0.25	0.3	1802	5612	-840	1.75	82.97	0.18	16.52	3.74	4.42
DUB230	855.25	864.00	8.75	9.2	1801	5612	-845	23.11	91.28	1.15	0.81	0.14	6.88
<i>includes</i>													
DUB230	862.07	864.00	1.93	2.0	1800	5612	-848	85.29	255.13	1.98	0.17	0.05	4.78
DUB230	864.00	879.70	15.70	16.5	1798	5613	-857	3.30	6.20	0.12	0.03	0.02	4.36
DUB230	879.70	887.38	7.68	8.1	1795	5613	-868	3.11	35.70	0.88	18.31	0.59	22.25
DUB230	887.38	892.00	4.62	4.9	1793	5613	-874	2.91	32.04	0.08	0.10	0.27	2.47
DUB231													
DUB231	826.70	831.00	4.30	4.7	1900	5380	-822	0.12	12.65	0.17	3.44	0.05	24.02
DUB231	854.40	863.00	8.60	9.5	1900	5375	-851	0.40	12.44	0.53	3.10	0.02	12.63
DUB231	952.80	953.45	0.65	0.7	1897	5355	-943	28.35	20.23	0.89	0.10	0.02	2.59
DUB231	979.25	982.00	2.75	3.0	1896	5349	-970	2.80	14.92	0.36	0.04	0.01	2.50
DUB232													
DUB232	779.32	785.43	6.11	6.7	1777	5036	-771	0.46	12.85	0.26	10.27	0.17	28.36
DUB232	801.36	806.24	4.88	5.4	1776	5031	-792	0.68	56.40	0.30	0.19	0.75	9.23
DUB233													
DUB233	924.15	929.36	5.21	5.5	1995	5819	-916	0.38	10.78	0.22	1.80	0.04	8.42
DUB233	929.36	931.24	1.88	2.0	1995	5819	-920	1.10	20.01	0.43	9.33	0.00	16.35
DUB233	931.24	939.00	7.76	8.1	1995	5819	-925	2.91	2.82	0.02	0.03	0.00	3.96
DUB233	965.84	985.77	19.93	20.9	1992	5816	-965	6.87	17.18	0.16	0.05	0.13	5.20
<i>includes</i>													
DUB233	968.80	969.80	1.00	1.1	1993	5817	-959	40.22	28.46	0.15	0.06	0.09	7.93
DUB233	979.33	979.92	0.59	0.6	1992	5816	-969	64.42	49.03	0.04	0.04	0.04	7.55
DUB233	984.38	984.79	0.41	0.4	1991	5816	-974	35.21	228.00	1.76	0.41	0.99	4.47
DUB234													
DUB234	861.90	866.50	4.60	4.8	1852	5542	-858	0.76	49.05	0.58	6.29	1.62	19.08
DUB234	866.50	879.50	13.00	13.7	1851	5542	-866	10.28	45.08	1.09	1.12	0.20	4.63
<i>includes</i>													
DUB234	876.50	878.00	1.50	1.6	1850	5542	-870	75.71	245.30	4.37	0.71	0.78	7.84
DUB234	900.00	922.00	22.00	23.1	1845	5542	-904	4.91	9.65	0.15	0.51	0.04	2.63
<i>includes</i>													
DUB234	903.50	904.00	0.50	0.5	1846	5542	-897	13.20	22.29	0.09	3.77	0.00	2.68
DUB234	906.00	906.50	0.50	0.5	1846	5542	-899	17.04	27.09	0.02	0.06	0.03	1.31
DUB234	909.50	910.00	0.50	0.5	1845	5542	-903	50.95	41.49	0.13	7.70	0.55	4.44
DUB234	912.00	913.00	1.00	1.1	1845	5542	-905	13.99	9.60	0.02	0.21	0.04	1.81

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters ⁽¹⁾	Estimated Vertical thickness meters ⁽²⁾	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB235													
DUB235	880.58	881.53	0.95	1.0	1856	5605	-859	0.38	6.57	0.20	11.69	0.01	26.57
DUB235	886.76	901.79	15.03	15.8	1852	5602	-872	4.15	8.16	0.16	0.18	0.00	3.06
<i>includes</i>													
DUB235	898.14	898.43	0.29	0.3	1851	5601	-875	58.11	169.71	3.23	1.32	0.02	10.83
DUB235	899.12	899.43	0.13	0.1	1851	5601	-876	27.26	65.14	1.48	9.51	0.02	17.36
DUB235	908.99	909.15	0.16	0.2	1849	5599	-886	25.99	260.91	18.19	1.91	0.08	18.50
DUB235	914.80	917.31	2.51	2.6	1847	5597	-892	4.41	39.73	0.11	1.47	0.48	4.31
DUB235	928.69	936.59	7.90	8.3	1844	5593	-908	9.30	33.42	1.13	1.90	0.38	13.56
<i>includes</i>													
DUB235	933.76	936.59	2.83	3.0	1843	5593	-910	20.03	52.48	1.78	1.61	0.51	13.02
DUB235	943.30	945.96	2.66	2.8	1841	5591	-919	4.36	52.76	0.20	0.03	0.48	5.63
DUB236													
DUB236	Assays pending.												
DUB237													
DUB237	Assays pending.												
DUB238													
DUB238	Assays pending.												
DUB239													
DUB239	Assays pending.												
DUB239W01													
DUB239W01	Assays pending.												
DUB240													
DUB240	Assays pending.												
DUB241													
DUB241	Assays pending.												
DUB242													
DUB242	Assays pending.												
DUB243													
DUB243	Assays pending.												
DUB244													
DUB244	Assays pending.												
DUB244W01													
DUB244W01	Assays pending.												
DUB244W02													
DUB244W02	Assays pending.												
DUB244W03													
DUB244W03	Drilling.												
DUB245													
DUB245	Assays pending.												
DUB246													
DUB246	Assays pending.												
DUB247													
DUB247	Assays pending.												

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.

Hudson Bay Mining and Smelting Co., Limited
Lalor Project
Assay Results to April 17th, 2009

Hole	From	To	Core length meters ⁽¹⁾	Estimated Vertical thickness meters ⁽²⁾	Intersection Location ERL Surface Grid			Au g/t	Ag g/t	Cu %	Zn %	Pb %	Fe %
					East meters	North meters	Depth meters						
DUB247W01													
DUB247W01	Assays pending.												
DUB247W02													
DUB247W02	Drilling.												
DUB248													
DUB248	Assays pending.												
DUB249													
DUB249	Assays pending.												
DUB250													
DUB250	Assays pending.												
DUB251													
DUB251	Drilling.												
DUB252													
DUB252	Drilling.												
DUB253													
DUB253	Drilling.												

Holes highlighted have new or additional results since the previous press release

(1) Intersection assays are either a single assay of a sample of the entire intersection length or a composite of assays calculated from interval weighted assays over the intersection length

(2) Vertical thickness is estimated using the local dip of the zone and the orientation of the hole and is provided for projecting to plan map.