

Sabodala Resources (inclusive of reserves)

Cutoff (g/t)	Measured			Indicated			Measured+Indicated			Inferred		
	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)
0.40	38.9	1.50	1,876	21.7	1.32	921	60.6	1.44	2,797	17.7	1.03	586
0.60	29.2	1.84	1,726	15.7	1.64	828	44.9	1.77	2,553	11.7	1.30	491
0.65	27.4	1.92	1,687	14.7	1.71	807	42.1	1.84	2,494	10.6	1.38	469
0.80	22.9	2.15	1,584	12.2	1.91	750	35.1	2.07	2,334	7.7	1.62	401
1.00	18.6	2.44	1,459	9.9	2.15	684	28.5	2.34	2,143	5.8	1.86	347
1.50	11.9	3.13	1,198	6.3	2.68	543	18.2	2.97	1,740	2.8	2.58	232

Niakafiri Resources (inclusive of reserves)

Cutoff (g/t)	Measured			Indicated			Measured+Indicated			Inferred		
	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)
0.50	0.3	1.77	15	7.9	1.33	340	8.2	1.34	355	6.2	0.97	192
0.75	0.3	1.84	15	6.1	1.55	304	6.3	1.57	319	3.5	1.25	139
1.00	0.2	1.94	14	4.9	1.72	270	5.1	1.73	284	1.6	1.68	89

Sabodala Reserves

Cutoff (g/t)	Proven			Probable			Proven+Probable			Inferred		
	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)
1.00	12.79	2.63	1,083	3.1	2.52	250	15.9	2.61	1,332	0.07	2.91	6
0.65 - 1.0	4.93	0.81	129	0.9	0.82	23	5.8	0.81	151	0.01	0.84	0
Total	17.7	2.13	1,211	3.9	2.15	272	21.7	2.13	1,484	0.08	2.61	6

Niakafiri Reserves

Cutoff (g/t)	Proven			Probable			Proven+Probable			Inferred			
	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	MTons	Au Grade (g/t)	Ounces (000's)	
Oxide	0.50	0.1	2.00	7	2.0	1.62	103	2.1	1.64	110	0.24	1.17	9
Fresh	0.60	0.0	1.97	3	0.5	1.83	32	0.6	1.84	35	0.01	1.31	0
Total	0.2	1.99	10	2.5	1.67	135	2.7	1.68	145	0.24	1.17	9	

The mineral reserves and mineral resources estimations reported above are documented in conformity with Canadian National Instrument 43-101 and reconciled to the JORC classification. The estimations follow the same procedures reported in a 2007 technical report that is available on SEDAR. Resources are based on a US\$700 gold price and assume life-of-mine milling recoveries of 91.4% for Sabodala ore, 92% for Niakafiri oxide ore and 90% for Niakafiri fresh ore. Direct milling costs are expected to average \$13.52 per tonne Sabodala ore milled, \$11.61 per tonne Niakafiri fresh ore milled and \$9.53 per tonne Niakafiri oxide ore milled.