



ML150 long section with blocks coloured by resource category.

Resource by Deposit, Category and Mining Method											
Deposit	Resource	Mining	Tonnes	Gold		Silver		Copper		Gold Equivalent	
	Category	Method	Mt	g/t	MOz	g/t	MOz	%	Mlb	g/t	MOz
Kora/Eutompi	Inferred	Mechanical	3.36	7.1	0.77	32.9	3.55	2.2	161	11.5	1.24
		Hand	1.06	7.2	0.25	40.0	1.37	2.3	55	12.0	0.41
Irumafimpa	Indicated	Mechanical	0.01	11.5	0.00	2.2	0.00	0.3	0	12.1	0.00
		Hand	0.56	12.6	0.23	8.9	0.16	0.3	3	13.3	0.24
	Inferred	Mechanical	0.07	7.2	0.02	7.4	0.02	0.2	0	7.7	0.02
		Hand	0.45	11.3	0.16	9.6	0.14	0.3	3	12.0	0.17
Total All Deposits	Indicated		0.56	12.6	0.23	9	0.2	0.3	3	13.3	0.24
	Inferred		4.94	7.5	1.20	32	5.1	2.0	219	11.6	1.84

M in Table is millions. Reported tonnage and grade figures have been rounded from raw estimates to reflect the order of accuracy of the estimate. Minor variations may occur during the addition of rounded numbers. There have been no assumptions made as to metal prices or recoveries in this mineral resource estimate other than gold equivalents that are calculated for AuEq = Au g/t + Cu%\*1.7308 + Ag g/t\*0.0185.