

Table 4: Mexico and Esmeralda Vein Drill Results

Drill Hole	From (m)	to (m)	Length (m)	Ag (g/t)	Pb (%)	Zn (%)	AgEq¹ (g/t)
NAM-007	91.0	100.15	9.15	48	0.09	0.06	52
NAM-007	112.0	115.82	3.82	123	0.12	0.05	128
<i>Including</i>	113.9	115.82	1.92	184	0.17	.05	189
NAM-007	187.0	188.0	1.0	148	.07	.18	154
NAM-007	193.0	196.0	3.0	148	.06	.13	153
NAM-007	208.0	209.0	1.0	76	0.35	0.05	87
NAM-007	223.0	224.0	1.0	178	.07	.34	189
NAM-007	246.0	256.0	10.0	69	.14	.25	80
NAM-007	313.0	319.8	6.8	71	3.05	1.88	207
<i>Including</i>	313.0	313.94	0.94	51	0.04	0.31	60
	313.94	315.41	1.47	103	0.29	0.46	123
	315.41	316.44	1.03	82	0.51	0.5	110
	316.44	317.50	1.06	134	13.55	3.94	613
	317.50	319.8	1.55	27	3.18	2.71	188
	319.8	320.4	0.75	26	0.6	3.92	150
NAM-013	118.87	122.16	3.29	268	0.23	0.11	277
<i>Including</i>	121.7	122.16	0.46	1,360	.71	.12	1,382
NAM-013	134.0	135.0	1.0	93	.10	.52	110
NAM-013	184.0	192.0	8.0	41	.14	.26	52
NAM-013	195.0	196.0	1.0	91	.25	.05	99
NAM-013	223.0	224.0	1.0	23	.64	1.80	90
NAM-013	238.0	243.15	5.15	23	.81	2.3	108
NAM-013	247.75	248.55	.8	34	.77	1.62	100
NAM-013	249.45	249.8	.35	79	.62	1.33	132
NAM-013	259.0	264.0	5.0	268	.17	.24	279
<i>Including</i>	259.0	261.0	2.0	435	.39	.44	457
NAM-013	346.67	352.5	5.83	186	1.08	2.81	293
<i>Including</i>	351.48	352.5	1.02	998	2.47	6.61	1,246

¹The Silver equivalent grades ("AgEq") have been calculated using metal prices of US\$25oz Silver; US\$1.00/lb Zinc; and US\$1.00/lb Lead. Metal recoveries are not considered in this calculation. Further drilling is required to provide a more accurate assessment of vein thickness and true width may vary.