

| REO-LIGHT = 87.68% | | | | | REO-HEAVY = 5.50% | | | | | | | | | Yttrium |
|--------------------------------|--------------------------------|--------------------------------|--------------------------------|--------------------------------|--------------------------------|--------------------------------|--------------------------------|--------------------------------|--------------------------------|--------------------------------|--------------------------------|--------------------------------|--------------------------------|-------------------------------|
| La ₂ O ₃ | Ce ₂ O ₃ | Pr ₂ O ₃ | Nd ₂ O ₃ | Sm ₂ O ₃ | Eu ₂ O ₃ | Gd ₂ O ₃ | Tb ₂ O ₃ | Dy ₂ O ₃ | Ho ₂ O ₃ | Er ₂ O ₃ | Tm ₂ O ₃ | Yb ₂ O ₃ | Lu ₂ O ₃ | Y ₂ O ₃ |
| 23.67 | 41.70 | 4.42 | 15.44 | 2.45 | 0.73 | 1.99 | 0.25 | 1.23 | 0.22 | 0.58 | 0.07 | 0.38 | 0.05 | 6.82 |