



PEREGRINE
DIAMONDS LTD.

To exercise control over the DMS results, a representative 350.0 kilogram control sample collected concurrently with the bulk sample was processed by caustic fusion at the SRC for diamonds larger than the 0.106 mm sieve size. The results are presented in the following table.

SUMMARY OF CAUSTIC FUSION DIAMOND RESULTS FOR A 350.0 KG SAMPLE FROM THE CH-6 KIMBERLITE

Sample Weight (dry kg)	Numbers of Diamonds According to Sieve Size Fraction (mm)											Total Diamonds	Carats (+0.850 mm sieve size)
	+0.106 -0.150	+0.150 -0.212	+0.212 -0.300	+0.300 -0.425	+0.425 -0.600	+0.600 -0.850	+0.850 -1.180	+1.180 -1.700	+1.700 -2.360	+2.360 -3.350	+3.350 -4.750		
350.0	317	228	150	99	60	32	11	9	1	0	0	907	0.52