

GOLDEN RIDGE DRILL INTERSECTIONS ^(1,2)


Hole No.	Easting	Northing	Azimuth	Dip	From (metres)	To (metres)	Interval (metres)	Au (g/t)
GR-11-69	2400310.9	7433061	025	-45	21.90	49.50	27.60	0.71
					including 28.40	39.00	10.60	1.13
					73.55	166.00	92.45	0.89
					including 115.30	119.80	4.50	1.29
					and 142.30	165.00	22.70	2.37
					including 149.25	151.25	2.00	5.78
GR-11-70	2400352.4	7433005	295	-60	29.25	45.25	16.00	2.32
					including 32.00	39.70	7.70	3.61
					115.10	116.70	1.60	2.58
					141.00	142.00	1.00	3.76
					169.50	172.80	3.30	0.77
					232.50	236.50	4.00	1.73
GR-11-71	2400441.2	7432958.2	115	-45	59.00	66.00	7.00	0.39
					71.50	74.00	2.50	1.00
					118	132	14.00	0.7
GR-11-72	2400147.2	7432779.3	115	-45	61.30	62.60	1.30	3.76
GR-11-73 ⁽³⁾	2400328.1	7433244.4	190	-55	32.95	41.00	8.05	1.44
					61.60	62.95	1.35	1.09
					73.70	241.10	167.40	0.70
					including 73.70	77.70	4.00	1.82
					and 100.15	130.20	30.05	1.37
					and 136.00	145.00	9.00	1.51
					and 204.00	207.00	3.00	2.56
and 228.00	241.10	13.10	1.67					
GR-11-74	2400126.2	7432897.9	115	-45	48.00	52.70	4.70	0.66
					194.70	199.16	4.46	0.89
GR-11-75	2400457	7433195.5	190	-55	14.50	16.10	1.60	0.49
					62.00	63.50	1.50	0.63
					70.95	73.13	2.18	0.85
					163.00	172.00	9.00	1.17
					189.00	194.00	5.00	0.56
					207.90	213.50	5.60	0.52
GR-11-76	2400068.5	7432982.6	115	-45	28.00	31.00	3.00	2.23
					38.65	40.00	1.35	0.54
					74.30	75.00	0.70	0.79
					81.15	86.50	5.35	0.67

¹Intervals are core length. True width will be defined with additional drilling


²Assays performed by Activation Laboratories Ltd, Ontario using the fire assay method 1A3-50 (Fire Assay Gravimetric (QOP AA-Au) on 50 grams of prepared sample.

³The GR-11-73 intersection of 167.40m grading 0.70 g/t Au, includes 6 intervals totaling 37m which have not been sampled. A zero grade was used in the weighted average grade calculation.

Golden Ridge Drill Plan (Holes from current program shown in red)



Preliminary cross section (GR11-69 & 73)



Model: Structural control of mineralization

