
GAX-061 25.3 opt Silver over 23.3 ft (868.9 gpt over 7.1 m)

Sample from interval 119.8 ft – 123.0 ft (36.5 m - 37.5 m)

Grade 77.9 opt silver (2670 gpt silver)

Brecciated and silicified andesite with disseminated acanthite (silver sulfide)



Silica with finely disseminated acanthite (silver sulfide)

0	cm	6.4
0	in	2.5