

Figure 1: Location of the Korkan-Bigar trend and the Kraku Pestar target area within the greater sediment-hosted gold belt, defined in this image by mapped 'target stratigraphy' (yellow) and anomalous gold soil geochemistry within the Korkan-Bigar trend *only*. The total metal contour plots for Korkan, Bigar Hill and Kraku Pestar have been superimposed on the sediment-hosted gold belt as defined to date by drilling.




Figure 2: Gram-meter (intervals >0.4g/t Au x thickness), total metal contour plot of all Bigar Hill drilling to date superimposed on topography. The section lines A-A' relates to Figure 3.




Figure 3: Northwest-southeast cross-section through the Bigar Hill target area showing detailed stratigraphy and gold mineralized drill intersections to date. The section is looking northeast.




Figure 4: Gram-meter (intervals >0.4g/t Au x thickness), total metal contour plot of all Korkan drilling to date superimposed on topography. Note the location of KODD061 on the northeast margin of the drill defined mineralized 'footprint'.

Table 1: All Bigar Hill gold drill intercepts at various cut-off grades.

REVERSE CIRCULATION DRILLING SIGNIFICANT INTERVALS								
Bigar Hill								
<i>1g/t Au cut-off, 5m minimum length, 5m maximum internal dilution</i>								
Hole ID	From (ft)	To (ft)	Interval (ft)	Au (Oz/t)	From (m)	To (m)	Interval (m)	Au (g/t)
BHRC003	45.9	88.6	42.7	0.039	14	27	13	1.20
BHRC005	226.4	344.5	118.1	0.148	69	105	36	4.61
BHRC005	374.0	397.0	23.0	0.060	114	121	7	1.87
BHRC005	587.3	603.7	16.4	0.040	179	184	5	1.23
BHRC006	9.8	75.5	65.6	0.087	3	23	20	2.70
BHRC009	32.8	78.7	45.9	0.074	10	24	14	2.30
BHRC012	75.5	157.5	82.0	0.048	23	48	25	1.49
BHRC013	98.4	114.8	16.4	0.063	30	35	5	1.97
BHRC013	134.5	210.0	75.5	0.077	41	64	23	2.39
BHRC013	672.6	711.9	39.4	0.034	205	217	12	1.06
BHRC015	433.1	580.7	147.6	0.074	132	177	45	2.29
BHRC017	23.0	39.4	16.4	0.050	7	12	5	1.56
BHRC017	72.2	144.4	72.2	0.041	22	44	22	1.28
BHRC018	160.8	196.9	36.1	0.067	49	60	11	2.07
BHRC018	459.3	518.4	59.1	0.087	140	158	18	2.70
BHRC019	259.2	337.9	78.7	0.068	79	103	24	2.12
BHRC019	374.0	397.0	23.0	0.039	114	121	7	1.20
BHRC020	370.7	406.8	36.1	0.115	113	124	11	3.57
BHRC020	689.0	734.9	45.9	0.034	210	224	14	1.05
BHRC021	488.8	515.1	26.2	0.120	149	157	8	3.73
BHRC022	416.7	449.5	32.8	0.061	127	137	10	1.91
BHRC022	675.9	744.8	68.9	0.071	206	227	21	2.22
BHRC023	288.7	377.3	88.6	0.127	88	115	27	3.96
BHRC024	794.0	813.6	19.7	0.092	242	248	6	2.87
BHRC025	462.6	524.9	62.3	0.051	141	160	19	1.59
BHRC025	767.7	787.4	19.7	0.037	234	240	6	1.15
BHRC027	538.1	554.5	16.4	0.064	164	169	5	2.00
BHRC028	607.0	646.3	39.4	0.040	185	197	12	1.23
BHRC029	725.1	744.8	19.7	0.049	221	227	6	1.52
BHRC030	584.0	620.1	36.1	0.063	178	189	11	1.97
BHRC031	521.7	574.1	52.5	0.045	159	175	16	1.41
BHRC031	616.8	633.2	16.4	0.062	188	193	5	1.94
BHRC036	626.6	679.1	52.5	0.067	191	207	16	2.09
BHRC036	771.0	859.6	88.6	0.050	235	262	27	1.57
BHRC036	879.3	902.2	23.0	0.046	268	275	7	1.43

BHRC037	623.4	705.4	82.0	0.059	190	215	25	1.82
BHRC038	639.8	662.7	23.0	0.056	195	202	7	1.74
BHRC038	702.1	741.5	39.4	0.035	214	226	12	1.09
BHRC038	984.3	1056.4	72.2	0.049	300	322	22	1.53
BHRC039	580.7	607.0	26.2	0.135	177	185	8	4.21
BHRC041	613.5	659.4	45.9	0.086	187	201	14	2.67
BHRC042	157.5	183.7	26.2	0.074	48	56	8	2.30
BHRC045	157.5	196.9	39.4	0.048	48	60	12	1.49
BHRC046	554.5	574.1	19.7	0.034	169	175	6	1.07
BHRC047	216.5	236.2	19.7	0.053	66	72	6	1.66
BHRC047	262.5	308.4	45.9	0.128	80	94	14	3.99
BHRC047	465.9	502.0	36.1	0.081	142	153	11	2.51
BHRC047	672.6	708.7	36.1	0.101	205	216	11	3.14
BHRC051	675.9	725.1	49.2	0.292	206	221	15	9.09
BHRC053	652.9	725.1	72.2	0.034	199	221	22	1.07
BHRC053	754.6	790.7	36.1	0.053	230	241	11	1.66
BHRC054	9.8	29.5	19.7	0.054	3	9	6	1.67

0.4g/t Au cut-off, 5m minimum length, 5m maximum internal dilution

Hole ID	From (ft)	To (ft)	Interval (ft)	Au (Oz/t)	From (m)	To (m)	Interval (m)	Au (g/t)
BHRC002	55.8	111.5	55.8	0.014	17	34	17	0.45
BHRC003	45.9	108.3	62.3	0.029	14	33	19	0.89
BHRC005	226.4	347.8	121.4	0.145	69	106	37	4.50
BHRC005	370.7	433.1	62.3	0.032	113	132	19	1.01
BHRC005	456.0	495.4	39.4	0.032	139	151	12	1.01
BHRC005	584.0	610.2	26.2	0.032	178	186	8	0.98
BHRC006	9.8	78.7	68.9	0.084	3	24	21	2.60
BHRC006	108.3	154.2	45.9	0.019	33	47	14	0.58
BHRC007	98.4	118.1	19.7	0.016	30	36	6	0.49
BHRC008	170.6	187.0	16.4	0.019	52	57	5	0.60
BHRC009	32.8	157.5	124.7	0.038	10	48	38	1.18
BHRC009	180.4	252.6	72.2	0.017	55	77	22	0.53
BHRC010	78.7	213.3	134.5	0.020	24	65	41	0.63
BHRC011	42.7	59.1	16.4	0.105	13	18	5	3.28
BHRC011	88.6	147.6	59.1	0.016	27	45	18	0.51
BHRC012	75.5	210.0	134.5	0.037	23	64	41	1.15
BHRC012	246.1	301.8	55.8	0.014	75	92	17	0.43
BHRC012	331.4	351.0	19.7	0.015	101	107	6	0.47
BHRC012	508.5	538.1	29.5	0.015	155	164	9	0.47
BHRC013	95.1	252.6	157.5	0.050	29	77	48	1.56
BHRC013	672.6	715.2	42.7	0.033	205	218	13	1.04



BHRC014	295.3	311.7	16.4	0.050	90	95	5	1.55
BHRC015	423.2	584.0	160.8	0.069	129	178	49	2.14
BHRC015	607.0	633.2	26.2	0.019	185	193	8	0.59
BHRC016	55.8	255.9	200.1	0.017	17	78	61	0.54
BHRC017	23.0	42.7	19.7	0.047	7	13	6	1.47
BHRC017	72.2	147.6	75.5	0.040	22	45	23	1.25
BHRC018	157.5	305.1	147.6	0.027	48	93	45	0.85
BHRC018	459.3	551.2	91.9	0.065	140	168	28	2.01
BHRC019	242.8	410.1	167.3	0.043	74	125	51	1.34
BHRC019	433.1	469.2	36.1	0.017	132	143	11	0.52
BHRC019	610.2	626.6	16.4	0.022	186	191	5	0.68
BHRC020	364.2	429.8	65.6	0.070	111	131	20	2.19
BHRC020	515.1	561.0	45.9	0.013	157	171	14	0.40
BHRC020	649.6	734.9	85.3	0.025	198	224	26	0.77
BHRC021	482.3	518.4	36.1	0.093	147	158	11	2.89
BHRC021	584.0	600.4	16.4	0.017	178	183	5	0.53
BHRC022	413.4	452.8	39.4	0.054	126	138	12	1.69
BHRC022	675.9	751.3	75.5	0.067	206	229	23	2.09
BHRC023	282.2	380.6	98.4	0.116	86	116	30	3.61
BHRC023	439.6	456.0	16.4	0.071	134	139	5	2.20
BHRC023	675.9	744.8	68.9	0.014	206	227	21	0.42
BHRC024	761.2	813.6	52.5	0.074	232	248	16	2.29
BHRC025	462.6	531.5	68.9	0.048	141	162	21	1.50
BHRC025	751.3	790.7	39.4	0.025	229	241	12	0.77
BHRC027	511.8	557.7	45.9	0.032	156	170	14	0.98
BHRC027	682.4	705.4	23.0	0.014	208	215	7	0.42
BHRC028	603.7	682.4	78.7	0.025	184	208	24	0.78
BHRC028	797.2	836.6	39.4	0.029	243	255	12	0.90
BHRC029	725.1	744.8	19.7	0.049	221	227	6	1.52
BHRC030	577.4	620.1	42.7	0.057	176	189	13	1.78
BHRC030	846.5	872.7	26.2	0.017	258	266	8	0.53
BHRC031	521.7	593.8	72.2	0.036	159	181	22	1.13
BHRC031	613.5	646.3	32.8	0.037	187	197	10	1.16
BHRC031	685.7	721.8	36.1	0.113	209	220	11	3.50
BHRC035	790.7	813.6	23.0	0.027	241	248	7	0.83
BHRC036	607.0	689.0	82.0	0.050	185	210	25	1.55
BHRC036	771.0	902.2	131.2	0.043	235	275	40	1.33
BHRC037	616.8	728.3	111.5	0.046	188	222	34	1.43
BHRC037	879.3	935.0	55.8	0.016	268	285	17	0.50
BHRC037	987.5	1003.9	16.4	0.014	301	306	5	0.43
BHRC038	633.2	741.5	108.3	0.030	193	226	33	0.94



BHRC038	787.4	807.1	19.7	0.039	240	246	6	1.20
BHRC038	862.9	921.9	59.1	0.016	263	281	18	0.49
BHRC038	964.6	1059.7	95.1	0.042	294	323	29	1.31
BHRC039	574.1	623.4	49.2	0.080	175	190	15	2.50
BHRC041	600.4	682.4	82.0	0.056	183	208	25	1.74
BHRC042	144.4	183.7	39.4	0.053	44	56	12	1.64
BHRC045	157.5	246.1	88.6	0.042	48	75	27	1.31
BHRC045	652.9	689.0	36.1	0.031	199	210	11	0.95
BHRC046	554.5	577.4	23.0	0.034	169	176	7	1.05
BHRC046	751.3	780.8	29.5	0.014	229	238	9	0.43
BHRC046	820.2	839.9	19.7	0.028	250	256	6	0.87
BHRC047	216.5	236.2	19.7	0.053	66	72	6	1.66
BHRC047	262.5	321.5	59.1	0.102	80	98	18	3.17
BHRC047	462.6	502.0	39.4	0.075	141	153	12	2.34
BHRC047	672.6	725.1	52.5	0.074	205	221	16	2.29
BHRC047	764.4	784.1	19.7	0.019	233	239	6	0.59
BHRC051	669.3	725.1	55.8	0.260	204	221	17	8.10
BHRC053	383.9	400.3	16.4	0.030	117	122	5	0.93
BHRC053	649.6	728.3	78.7	0.033	198	222	24	1.04
BHRC053	754.6	800.5	45.9	0.047	230	244	14	1.47
BHRC054	9.8	39.4	29.5	0.043	3	12	9	1.35

DIAMOND DRILLING SIGNIFICANT INTERVALS								
Bigar Hill								
<i>1g/t Au cut-off, 5m minimum length, 5m maximum internal dilution</i>								
Hole ID	From (ft)	To (ft)	Interval (ft)	Au (Oz/t)	From (m)	To (m)	Interval (m)	Au (g/t)
BHDD004	170.6	206.7	36.1	0.041	52	63	11	1.28
BHDD004	410.1	456.0	45.9	0.047	125	139	14	1.47
BHDD005	439.6	505.2	65.6	0.091	134	154	20	2.82
BHDD005	869.4	889.1	19.7	0.045	265	271	6	1.41
BHDD006	282.2	311.7	29.5	0.049	86	95	9	1.51
BHDD007	764.4	794.0	29.5	0.143	233	242	9	4.44
BHDD010	646.3	679.1	32.8	0.052	197	207	10	1.62
BHDD010	869.4	899.0	29.5	0.087	265	274	9	2.71
BHDD011	393.7	449.5	55.8	0.099	120	137	17	3.08
BHDD011	646.3	666.0	19.7	0.033	197	203	6	1.02
BHDD014	377.3	426.5	49.2	0.068	115	130	15	2.10
BHDD014	534.8	567.6	32.8	0.038	163	173	10	1.18

BHDD016	95.1	213.3	118.1	0.045	29	65	36	1.39
BHDD017	449.5	465.9	16.4	0.280	137	142	5	8.70
BHDD017	636.5	682.4	45.9	0.098	194	208	14	3.05
BHDD017	774.3	800.5	26.2	0.052	236	244	8	1.61
BHDD019	675.9	696.5	20.7	0.040	206	212.3	6.3	1.23
BHDD020	20.3	124.7	104.3	0.067	6.2	38	31.8	2.09
BHDD021	541.3	584.0	42.7	0.102	165	178	13	3.18
BHDD023	73.8	108.3	34.4	0.061	22.5	33	10.5	1.90
BHDD023	403.5	459.3	55.8	0.060	123	140	17	1.87
BHDD029	242.8	344.5	101.7	0.154	74	105	31	4.78
BHDD031	646.3	669.3	23.0	0.046	197	204	7	1.44
BHDD032	334.6	383.9	49.2	0.043	102	117	15	1.35
BHDD034	413.4	577.4	164.0	0.078	126	176	50	2.44
BHDD043	6.9	72.2	65.3	0.095	2.1	22	19.9	2.97
BHDD044	249.3	393.7	144.4	0.142	76	120	44	4.41
BHDD044	426.5	442.9	16.4	0.121	130	135	5	3.75
BHDD044	475.7	494.8	19.0	0.135	145	150.8	5.8	4.21
BHDD045	134.5	196.5	62.0	0.068	41	59.9	18.9	2.12
BHDD047	413.4	442.9	29.5	0.134	126	135	9	4.16
BHDD047	675.9	767.7	91.9	0.047	206	234	28	1.45

0.4g/t Au cut-off, 5m minimum length, 5m maximum internal dilution

Hole ID	From (ft)	To (ft)	Interval (ft)	Au (Oz/t)	From (m)	To (m)	Interval (m)	Au (g/t)
BHDD001	246.1	262.5	16.4	0.014	75	80	5	0.44
BHDD002	157.5	223.1	65.6	0.018	48	68	20	0.57
BHDD004	160.8	301.8	141.1	0.021	49	92	43	0.67
BHDD004	397.0	475.7	78.7	0.034	121	145	24	1.05
BHDD004	639.8	656.2	16.4	0.029	195	200	5	0.90
BHDD005	387.1	403.5	16.4	0.077	118	123	5	2.40
BHDD005	436.4	521.7	85.3	0.073	133	159	26	2.26
BHDD005	584.0	610.2	26.2	0.044	178	186	8	1.37
BHDD005	846.5	912.1	65.6	0.024	258	278	20	0.76
BHDD006	282.2	321.5	39.4	0.043	86	98	12	1.32
BHDD007	590.6	626.6	36.1	0.022	180	191	11	0.69
BHDD007	744.8	794.0	49.2	0.091	227	242	15	2.82
BHDD010	626.6	692.3	65.6	0.033	191	211	20	1.03
BHDD010	843.2	899.0	55.8	0.055	257	274	17	1.70
BHDD011	387.1	482.3	95.1	0.063	118	147	29	1.97
BHDD011	633.2	666.0	32.8	0.026	193	203	10	0.81
BHDD013	1020.3	1046.6	26.2	0.024	311	319	8	0.76
BHDD014	374.0	439.6	65.6	0.053	114	134	20	1.65



BHDD014	492.1	567.6	75.5	0.023	150	173	23	0.71
BHDD014	666.0	698.8	32.8	0.026	203	213	10	0.82
BHDD016	95.1	216.5	121.4	0.044	29	66	37	1.37
BHDD016	239.5	308.4	68.9	0.018	73	94	21	0.55
BHDD017	446.2	465.9	19.7	0.237	136	142	6	7.37
BHDD017	636.5	682.4	45.9	0.098	194	208	14	3.05
BHDD017	774.3	807.1	32.8	0.045	236	246	10	1.41
BHDD019	672.6	718.5	45.9	0.030	205	219	14	0.92
BHDD020	20.3	128.0	107.6	0.066	6.2	39	32.8	2.04
BHDD021	400.3	416.7	16.4	0.019	122	127	5	0.58
BHDD021	439.6	456.0	16.4	0.027	134	139	5	0.85
BHDD021	541.3	584.0	42.7	0.102	165	178	13	3.18
BHDD023	73.8	111.5	37.7	0.059	22.5	34	11.5	1.82
BHDD023	223.1	242.8	19.7	0.025	68	74	6	0.77
BHDD023	400.3	469.2	68.9	0.051	122	143	21	1.59
BHDD026	75.1	147.6	72.5	0.019	22.9	45	22.1	0.59
BHDD027	869.4	889.1	19.7	0.023	265	271	6	0.71
BHDD029	223.1	344.5	121.4	0.130	68	105	37	4.05
BHDD029	370.7	436.4	65.6	0.020	113	133	20	0.63
BHDD029	600.4	626.6	26.2	0.017	183	191	8	0.54
BHDD031	636.5	669.3	32.8	0.039	194	204	10	1.21
BHDD031	692.3	748.0	55.8	0.013	211	228	17	0.40
BHDD032	331.4	387.1	55.8	0.040	101	118	17	1.24
BHDD033	29.5	52.5	23.0	0.033	9	16	7	1.01
BHDD034	413.4	610.2	196.9	0.067	126	186	60	2.08
BHDD037	708.7	754.6	45.9	0.019	216	230	14	0.58
BHDD040	1207.3	1230.3	23.0	0.021	368	375	7	0.65
BHDD041	29.5	88.6	59.1	0.016	9	27	18	0.50
BHDD043	6.9	124.7	117.8	0.060	2.1	38	35.9	1.88
BHDD043	436.4	472.4	36.1	0.014	133	144	11	0.44
BHDD044	223.1	446.2	223.1	0.105	68	136	68	3.26
BHDD044	472.4	494.8	22.3	0.117	144	150.8	6.8	3.65
BHDD044	590.6	698.8	108.3	0.016	180	213	33	0.51
BHDD045	105.0	216.5	111.5	0.046	32	66	34	1.43
BHDD045	492.1	538.1	45.9	0.022	150	164	14	0.68
BHDD045	580.7	643.0	62.3	0.059	177	196	19	1.85
BHDD047	413.4	456.0	42.7	0.097	126	139	13	3.01
BHDD047	675.9	767.7	91.9	0.047	206	234	28	1.45
BHDD048	554.5	584.0	29.5	0.018	169	178	9	0.57
BHDD049	741.5	757.9	16.4	0.036	226	231	5	1.12



- Significant intervals 'not in bold' have been previously released.
- Diamond drill samples are generally taken on a 1m basis and weigh ~3kg.
- Reverse circulation drill samples are taken on a 1m basis and weigh ~5kg.
- Assay method: Fire assay Au (50g).
- Intercept widths do not necessarily represent true width.
- No top cut applied.
- Refer to www.avalaresources.com for a full listing of significant intervals at various cut-off grades.
- Reverse circulation-diamond twin drill hole 'pairs':
 - BHRC015-BHDD034
 - BHRC016-BHDD026
 - BHRC017-BHDD020
 - BHRC018-BHDD004
 - BHRC019-BHDD029
 - BHDD043-BHRC006
 - BHDD044-BHRC005
 - BHDD045-BHRC013
 - BHDD047-BHRC022
 - BHDD049-BHRC024

Table 2: All Korkan gold drill intercepts at various cut-off grades.

DIAMOND DRILLING SIGNIFICANT INTERVALS								
Korkan								
<i>1g/t Au cut-off, 5m minimum length, 5m maximum internal dilution</i>								
Hole ID	From (ft)	To (ft)	Interval (ft)	Au (Oz/t)	From (m)	To (m)	Interval (m)	Au (g/t)
KODD001	55.8	226.4	170.6	0.138	17	69	52	4.30
KODD002	433.1	488.8	55.8	0.096	132	149	17	3.00
KODD007	790.7	856.3	65.6	0.056	241	261	20	1.76
KODD009	111.5	170.6	59.1	0.060	34	52	18	1.88
KODD009	206.7	278.9	72.2	0.053	63	85	22	1.65
KODD013	180.4	216.5	36.1	0.042	55	66	11	1.32
KODD016	88.6	121.4	32.8	0.103	27	37	10	3.22
KODD018	656.2	682.4	26.2	0.051	200	208	8	1.60
KODD044	849.7	892.4	42.7	0.186	259	272	13	5.80
KODD048	265.7	285.4	19.7	0.064	81	87	6	1.99
KODD051	839.9	866.1	26.2	0.035	256	264	8	1.09
KODD058	695.5	728.3	32.8	0.206	212	222	10	6.40
KODD060	154.2	213.3	59.1	0.043	47	65	18	1.34
KODD061	944.9	971.1	26.2	0.035	288	296	8	1.10
KODD063	236.2	265.7	29.5	0.047	72	81	9	1.45

<i>0.4g/t Au cut-off, 5m minimum length, 5m maximum internal dilution</i>								
Hole ID	From (ft)	To (ft)	Interval (ft)	Au (Oz/t)	From (m)	To (m)	Interval (m)	Au (g/t)
KODD001	55.8	226.4	170.6	0.138	17	69	52	4.30
KODD002	433.1	498.7	65.6	0.085	132	152	20	2.63
KODD005	751.3	794.0	42.7	0.017	229	242	13	0.52
KODD007	164.0	180.4	16.4	0.014	50	55	5	0.43
KODD007	764.4	889.1	124.7	0.035	233	271	38	1.09
KODD009	111.5	180.4	68.9	0.054	34	55	21	1.68
KODD009	206.7	285.4	78.7	0.050	63	87	24	1.56
KODD009	344.5	360.9	16.4	0.027	105	110	5	0.84
KODD010	771.0	839.9	68.9	0.017	235	256	21	0.54
KODD012	761.2	777.6	16.4	0.019	232	237	5	0.58
KODD013	177.2	216.5	39.4	0.040	54	66	12	1.26
KODD015	1000.7	1046.6	45.9	0.023	305	319	14	0.70
KODD016	66.3	121.4	55.1	0.067	20.2	37	16.8	2.07
KODD016	731.6	761.2	29.5	0.025	223	232	9	0.78
KODD018	357.6	387.1	29.5	0.015	109	118	9	0.47
KODD018	656.2	682.4	26.2	0.051	200	208	8	1.60
KODD037	315.0	337.9	23.0	0.038	96	103	7	1.17
KODD037	397.0	426.5	29.5	0.022	121	130	9	0.68
KODD038	830.1	846.5	16.4	0.026	253	258	5	0.80
KODD043	265.7	305.1	39.4	0.024	81	93	12	0.74
KODD044	849.7	895.7	45.9	0.175	259	273	14	5.44
KODD044	915.4	941.6	26.2	0.014	279	287	8	0.44
KODD044	1174.5	1190.9	16.4	0.016	358	363	5	0.48
KODD045	0.0	65.6	65.6	0.022	0	20	20	0.70
KODD046	935.0	964.6	29.5	0.039	285	294	9	1.20
KODD048	262.5	292.0	29.5	0.048	80	89	9	1.48
KODD051	170.6	203.4	32.8	0.017	52	62	10	0.53
KODD051	830.1	876.0	45.9	0.027	253	267	14	0.85
KODD055	2021.0	2037.4	16.4	0.017	616	621	5	0.54
KODD057	587.3	603.7	16.4	0.015	179	184	5	0.48
KODD058	689.0	728.3	39.4	0.175	210	222	12	5.43
KODD059	1345.1	1370.1	24.9	0.014	410	417.6	7.6	0.45
KODD060	78.7	246.1	167.3	0.028	24	75	51	0.88
KODD061	620.7	643.0	22.3	0.028	189.2	196	6.8	0.87
KODD061	679.1	718.5	39.4	0.013	207	219	12	0.41
KODD061	905.5	1020.3	114.8	0.020	276	311	35	0.62
KODD063	236.2	278.9	42.7	0.037	72	85	13	1.14
KODD063	305.1	334.6	29.5	0.019	93	102	9	0.59



KODD063	521.7	593.8	72.2	0.023	159	181	22	0.71
---------	-------	-------	------	-------	-----	-----	----	------

- Significant intervals 'not in bold' have been previously released.
- Diamond drill samples are generally taken on a 1m basis and weigh ~3kg.
- Assay method: Fire assay Au (50g).
- Intercept widths do not necessarily represent true width.
- No top cut applied.
- Note: KODD061 had no core recovery from 135.1 to 184.1 meters.
- Refer to www.avalaresources.com for a full listing of significant intervals at various cut-off grades.