

Table 1: All Bigar Hill gold drill intercepts at various cut-off grades.

DRILLING SIGNIFICANT INTERVALS								
Bigar Hill								
<i>1g/t Au cut-off, 5m minimum length, 5m maximum internal dilution</i>								
Hole ID	From (ft)	To (ft)	Interval (ft)	Au (Oz/t)	From (m)	To (m)	Interval (m)	Au (g/t)
BHDD004	170.6	206.7	36.1	0.041	52	63	11	1.28
BHDD004	410.1	456.0	45.9	0.047	125	139	14	1.47
BHDD005	439.6	505.2	65.6	0.091	134	154	20	2.82
BHDD005	869.4	889.1	19.7	0.045	265	271	6	1.41
BHDD006	282.2	311.7	29.5	0.049	86	95	9	1.51
BHDD007	764.4	794.0	29.5	0.143	233	242	9	4.44
BHDD010	646.3	679.1	32.8	0.052	197	207	10	1.62
BHDD010	869.4	899.0	29.5	0.087	265	274	9	2.71
BHDD011	393.7	449.5	55.8	0.099	120	137	17	3.08
BHDD011	646.3	666.0	19.7	0.033	197	203	6	1.02
BHDD014	377.3	426.5	49.2	0.068	115	130	15	2.1
BHDD014	534.8	567.6	32.8	0.038	163	173	10	1.18
BHDD016	95.1	213.3	118.1	0.045	29	65	36	1.39
BHDD017	449.5	465.9	16.4	0.280	137	142	5	8.7
BHDD017	636.5	682.4	45.9	0.098	194	208	14	3.05
BHDD017	774.3	800.5	26.2	0.052	236	244	8	1.61
BHDD019	675.9	696.5	20.7	0.040	206	212.3	6.3	1.23
BHDD020	20.3	124.7	104.3	0.067	6.2	38	31.8	2.09
BHDD021	541.3	584.0	42.7	0.102	165	178	13	3.18
BHDD023	73.8	108.3	34.4	0.061	22.5	33	10.5	1.9
BHDD023	403.5	459.3	55.8	0.060	123	140	17	1.87
BHDD029	242.8	344.5	101.7	0.154	74	105	31	4.78
BHDD031	646.3	669.3	23.0	0.046	197	204	7	1.44
BHDD032	334.6	383.9	49.2	0.043	102	117	15	1.35
BHDD034	413.4	577.4	164.0	0.078	126	176	50	2.44
<i>0.8g/t Au cut-off, 5m minimum length, 5m maximum internal dilution</i>								
Hole ID	From (ft)	To (ft)	Interval (ft)	Au (Oz/t)	From (m)	To (m)	Interval (m)	Au (g/t)
BHDD004	170.6	210.0	39.4	0.040	52	64	12	1.24
BHDD004	397.0	456.0	59.1	0.040	121	139	18	1.23
BHDD004	639.8	656.2	16.4	0.029	195	200	5	0.90
BHDD005	439.6	505.2	65.6	0.091	134	154	20	2.82
BHDD005	587.3	603.7	16.4	0.059	179	184	5	1.84
BHDD005	869.4	912.1	42.7	0.029	265	278	13	0.92
BHDD006	282.2	318.2	36.1	0.045	86	97	11	1.40

BHDD007	603.7	620.1	16.4	0.037	184	189	5	1.17
BHDD007	764.4	794.0	29.5	0.143	233	242	9	4.44
BHDD010	646.3	679.1	32.8	0.052	197	207	10	1.62
BHDD010	849.7	899.0	49.2	0.059	259	274	15	1.85
BHDD011	390.4	449.5	59.1	0.095	119	137	18	2.96
BHDD011	633.2	666.0	32.8	0.026	193	203	10	0.81
BHDD014	377.3	426.5	49.2	0.068	115	130	15	2.10
BHDD014	508.5	567.6	59.1	0.026	155	173	18	0.80
BHDD016	95.1	213.3	118.1	0.045	29	65	36	1.39
BHDD017	449.5	465.9	16.4	0.280	137	142	5	8.70
BHDD017	636.5	682.4	45.9	0.098	194	208	14	3.05
BHDD017	774.3	800.5	26.2	0.052	236	244	8	1.61
BHDD019	675.9	715.2	39.4	0.031	206	218	12	0.96
BHDD020	20.3	124.7	104.3	0.067	6.2	38	31.8	2.09
BHDD021	541.3	584.0	42.7	0.102	165	178	13	3.18
BHDD023	73.8	111.5	37.7	0.059	22.5	34	11.5	1.82
BHDD023	403.5	459.3	55.8	0.060	123	140	17	1.87
BHDD029	223.1	344.5	121.4	0.130	68	105	37	4.05
BHDD029	370.7	413.4	42.7	0.026	113	126	13	0.81
BHDD031	646.3	669.3	23.0	0.046	197	204	7	1.44
BHDD032	334.6	383.9	49.2	0.043	102	117	15	1.35
BHDD033	29.5	49.2	19.7	0.035	9	15	6	1.08
BHDD034	413.4	577.4	164.0	0.079	126	176	50	2.44
<i>0.4g/t Au cut-off, 5m minimum length, 5m maximum internal dilution</i>								
Hole ID	From (ft)	To (ft)	Interval (ft)	Au (Oz/t)	From (m)	To (m)	Interval (m)	Au (g/t)
BHDD001	246.1	262.5	16.4	0.014	75	80	5	0.44
BHDD002	157.5	223.1	65.6	0.018	48	68	20	0.57
BHDD004	160.8	301.8	141.1	0.021	49	92	43	0.67
BHDD004	397.0	475.7	78.7	0.034	121	145	24	1.05
BHDD004	639.8	656.2	16.4	0.029	195	200	5	0.90
BHDD005	387.1	403.5	16.4	0.077	118	123	5	2.40
BHDD005	436.4	521.7	85.3	0.073	133	159	26	2.26
BHDD005	584.0	610.2	26.2	0.044	178	186	8	1.37
BHDD005	846.5	912.1	65.6	0.024	258	278	20	0.76
BHDD006	282.2	321.5	39.4	0.043	86	98	12	1.32
BHDD007	590.6	626.6	36.1	0.022	180	191	11	0.69
BHDD007	744.8	794.0	49.2	0.091	227	242	15	2.82
BHDD010	626.6	692.3	65.6	0.033	191	211	20	1.03
BHDD010	843.2	899.0	55.8	0.055	257	274	17	1.70
BHDD011	387.1	482.3	95.1	0.063	118	147	29	1.97



BHDD011	633.2	666.0	32.8	0.026	193	203	10	0.81
BHDD013	1020.3	1046.6	26.2	0.024	311	319	8	0.76
BHDD014	374.0	439.6	65.6	0.053	114	134	20	1.65
BHDD014	492.1	567.6	75.5	0.023	150	173	23	0.71
BHDD014	666.0	698.8	32.8	0.026	203	213	10	0.82
BHDD016	95.1	216.5	121.4	0.044	29	66	37	1.37
BHDD016	239.5	308.4	68.9	0.018	73	94	21	0.55
BHDD017	446.2	465.9	19.7	0.237	136	142	6	7.37
BHDD017	636.5	682.4	45.9	0.098	194	208	14	3.05
BHDD017	774.3	807.1	32.8	0.045	236	246	10	1.41
BHDD019	672.6	718.5	45.9	0.030	205	219	14	0.92
BHDD020	20.3	128.0	107.6	0.066	6.2	39	32.8	2.04
BHDD021	400.3	416.7	16.4	0.019	122	127	5	0.58
BHDD021	439.6	456.0	16.4	0.027	134	139	5	0.85
BHDD021	541.3	584.0	42.7	0.102	165	178	13	3.18
BHDD023	73.8	111.5	37.7	0.059	22.5	34	11.5	1.82
BHDD023	223.1	242.8	19.7	0.025	68	74	6	0.77
BHDD023	400.3	469.2	68.9	0.051	122	143	21	1.59
BHDD026	75.1	147.6	72.5	0.019	22.9	45	22.1	0.59
BHDD027	869.4	889.1	19.7	0.023	265	271	6	0.71
BHDD029	223.1	344.5	121.4	0.130	68	105	37	4.05
BHDD029	370.7	436.4	65.6	0.020	113	133	20	0.63
BHDD029	600.4	626.6	26.2	0.017	183	191	8	0.54
BHDD031	636.5	669.3	32.8	0.039	194	204	10	1.21
BHDD031	692.3	748.0	55.8	0.013	211	228	17	0.40
BHDD032	331.4	387.1	55.8	0.040	101	118	17	1.24
BHDD033	29.5	52.5	23.0	0.033	9	16	7	1.01
BHDD034	413.4	610.2	196.9	0.067	126	186	60	2.08

- Significant intervals 'not in bold' have been previously released.
- Diamond drill samples are generally taken on a 1m basis and weigh ~3kg.
- Assay method: Fire assay Au (50g).
- Intercept widths do not necessarily represent true width.
- No top cut applied.