

Table 3: All Kraku Pestar gold drill intercepts at various cut-off grades.

DRILLING SIGNIFICANT INTERVALS								
Kraku Pestar								
<i>1g/t Au cut-off, 5m minimum length, 5m maximum internal dilution</i>								
Hole ID	From (ft)	To (ft)	Interval (ft)	Au (Oz/t)	From (m)	To (m)	Interval (m)	Au (g/t)
PEDD001	38.4	131.2	92.8	0.075	11.7	40	28.3	2.35
PEDD001	196.9	216.5	19.7	0.038	60	66	6	1.18
PEDD002	436.4	452.8	16.4	0.055	133	138	5	1.72
PEDD002	505.2	590.6	85.3	0.059	154	180	26	1.83
PEDD004	42.7	72.2	29.5	0.211	13	22	9	6.56
PEDD008	75.1	98.4	23.3	0.085	22.9	30	7.1	2.64
PEDD008	311.7	331.4	19.7	0.078	95	101	6	2.43
PEDD010	173.9	269.7	95.8	0.055	53	82.2	29.2	1.70
PEDD017	206.7	232.9	26.2	0.059	63	71	8	1.85
<i>0.8g/t Au cut-off, 5m minimum length, 5m maximum internal dilution</i>								
Hole ID	From (ft)	To (ft)	Interval (ft)	Au (Oz/t)	From (m)	To (m)	Interval (m)	Au (g/t)
PEDD001	38.4	216.5	178.1	0.052	11.7	66	54.3	1.61
PEDD002	436.4	452.8	16.4	0.055	133	138	5	1.72
PEDD002	505.2	590.6	85.3	0.059	154	180	26	1.83
PEDD003	308.4	324.8	16.4	0.028	94	99	5	0.86
PEDD004	29.5	88.6	59.1	0.115	9	27	18	3.58
PEDD008	75.1	98.4	23.3	0.085	22.9	30	7.1	2.64
PEDD008	295.3	331.4	36.1	0.054	90	101	11	1.68
PEDD010	170.6	269.7	99.1	0.054	52	82.2	30.2	1.67
PEDD016	1325.5	1351.7	26.2	0.030	404	412	8	0.92
PEDD017	206.7	232.9	26.2	0.059	63	71	8	1.85
<i>0.4g/t Au cut-off, 5m minimum length, 5m maximum internal dilution</i>								
Hole ID	From (ft)	To (ft)	Interval (ft)	Au (Oz/t)	From (m)	To (m)	Interval (m)	Au (g/t)
PEDD001	8.2	282.2	274.0	0.041	2.5	86	83.5	1.28
PEDD002	187.0	236.2	49.2	0.018	57	72	15	0.57
PEDD002	298.6	380.6	82.0	0.017	91	116	25	0.52
PEDD002	416.7	452.8	36.1	0.031	127	138	11	0.96
PEDD002	472.4	633.2	160.8	0.039	144	193	49	1.23
PEDD003	105.0	134.5	29.5	0.061	32	41	9	1.90
PEDD003	288.7	334.6	45.9	0.023	88	102	14	0.70
PEDD004	6.6	121.4	114.8	0.067	2	37	35	2.08
PEDD008	0.0	16.4	16.4	0.021	0	5	5	0.66
PEDD008	71.5	109.6	38.1	0.056	21.8	33.4	11.6	1.73



PEDD008	288.7	334.6	45.9	0.046	88	102	14	1.44
PEDD010	62.3	88.6	26.2	0.016	19	27	8	0.49
PEDD010	167.3	383.9	216.5	0.034	51	117	66	1.05
PEDD014	757.9	777.6	19.7	0.014	231	237	6	0.44
PEDD014	928.5	954.7	26.2	0.015	283	291	8	0.48
PEDD016	1318.9	1355.0	36.1	0.028	402	413	11	0.86
PEDD017	206.7	259.2	52.5	0.035	63	79	16	1.10
PEDD020	416.7	440.3	23.6	0.029	127	134.2	7.2	0.91

- Significant intervals 'not in bold' have been previously released.
- Diamond drill samples are generally taken on a 1m basis and weigh ~3kg.
- Assay method: Fire assay Au (50g).
- Intercept widths do not necessarily represent true width.
- No top cut applied.