

Table 1: Summaries of Selected Assays from

### Homestake Ag Zone:

Hole #	Collar Data			From (m)	To (m)	Interval (m)	Est. Tr. Thck	Au (g/t)	Ag (g/t)	Comments
	Az Deg	Dip Deg	Depth (m)							
HR09-146 ** inc inc	229.0	-58.0	392.3	206.35 209.9 209.9	237.2 214.9 210.8	30.9 5.0 0.9	22.5 3.6 0.7	2.1 10.6 49.0	294.3 1689.6 9027.0	New Assays; Assays pending above and below interval
HR09-137 inc inc and inc	245.0	-47.0	348.4	151.4 170.0 170.9 234.4 236.9	184.3 184.3 175.9 238.7 238.7	32.9 14.4 5.1 4.4 1.9	26.8 11.6 4.1 3.5 1.5	1.4 2.8 6.9 0.2 0.5	51.3 80.0 193.5 162.9 362.6	New Assays added Previously Reported Interval Previously Reported Interval New Assays
HR09-142	210.0	-45.0	428.3	102.05	109.8	7.8	5.7	0.10	37.80	HW Vein?; Assays pending for lower intervals

### Homestake Main Zone

HR09-126	236.0	-52.0	230.7	82.1	91.8	9.7	8.8	0.8	1.4	New Assays
HR09-129 and and inc.	212.0	-63.0	202.4	65.2 121.3 134.3 134.3	66.3 123.8 138.3 135.8	1.1 2.6 4.0 1.5	1.1 2.6 4.0 1.5	9.2 1.7 2.0 5.0	6.8 1.6 30.8 42.9	New Assays
HR09-141 inc. and and	211.0	-65.0	389.3	241.4 241.4 300.6 309.6	245.4 242.3 305.0 313.3	4.0 0.9 4.5 3.5	4.0 0.9 4.5 3.4	2.8 11.4 1.3 1.5	4.5 15.2 8.6 22.6	New Assays Assays pending above zone
HR09-143 inc.	235.0	-63.0	361.8	254.3 254.3	280.0 256.2	25.7 1.9	23.8 1.8	1.7 3.2	1.5 8.2	New Assays Assays pending below zone

Analyzed by FA-ES/AA for gold and ICP-MS by Acme Labs, Vancouver BC; Samples >10g/t Au re-assayed with FA-Grav – check assays are pending; Silver overlimits (>100g/t Ag) re-assayed with FA-Grav.

>0.2g/t Au and 20g/t Ag cut-off used for compositing intervals, <20% internal dilution on +10 metre intervals

\*\* Higher-grade composite in HR09-146 uses >1g/t Au and 30g/t Ag cut-off – no internal dilution