

**Table 3 – Minor Element Assays**

Composite	Concentrate Minor Element Assay																
	Ag g/t	As g/t	Ba g/t	Bi g/t	Cd g/t	Co g/t	Cr g/t	Li g/t	Mn g/t	Mo g/t	Pb g/t	Sb g/t	Sr g/t	Ti %	Tl g/t	V g/t	Zn g/t
H	2	<10	27	<20	<10	2906	89	<20	<10	<20	214	<20	<20	0.007	<20	40	230
M	18	<10	17	<20	<10	3207	98	<20	<10	<20	57	<20	<20	0.005	<20	38	62
J	2	<10	18	<20	<10	2666	92	<20	<10	<20	53	<20	<20	0.004	<20	54	45
G	4	<10	26	<20	<10	1801	20	<20	<10	<20	77	<20	<20	0.002	<20	53	21
SG1 (1)	6	<10	57	<20	<10	3807	85	<20	<10	<20	135	<20	<20	0.005	<20	39	59
SG2 (1)	12	<10	20	<20	<10	3342	77	<20	<10	<20	43	<20	<20	0.009	<20	38	74
SG3 (1)	4	<10	15	<20	<10	3179	79	<20	<10	<20	300	<20	<20	0.005	<20	37	200

Notes:

1. SG 1, SG 2 and SG 3 composites represent three different mineralisation types from the Sleeping Giant ore zone being disseminated, stringer and bleb and semi massive sulphide.