

Significant Drill Hole Intersections El Espino Project, April - June 2010

Drill Hole	Type	From	To	width	Cu%	Au g/t
PXE-402	sulfide	89.0	92.0	3.0	0.29	0.07
	sulfide	127.0	132.0	5.0	0.25	0.03
	sulfide	144.0	147.0	3.0	0.86	0.24
	sulfide	193.0	208.0	15.0	0.32	0.05
	sulfide	200.0	204.0	4.0	0.68	0.08
	sulfide	223.0	247.0	24.0	0.21	0.05
PXE-404	No significant results - failed to reach target					
PXE-406	oxide	4.2	43.0	38.8	0.63	0.13
	oxide	13.1	25.0	11.9	0.92	0.24
	oxide	37.0	43.0	6.0	1.27	0.14
	sulfide	43.0	78.0	35.0	0.51	0.03
	sulfide	43.0	46.0	3.0	1.80	0.07
	sulfide	54.0	62.0	8.0	0.86	0.05
PXE-409	sulfide	82.0	87.0	5.0	0.22	0.08
	sulfide	113.0	118.0	5.0	0.37	0.03
PXE-413	oxide	17.5	20.0	2.5	0.35	0.04
	oxide	58.0	81.0	23.0	0.60	0.07
	oxide	66.0	81.0	15.0	0.84	0.06
	sulfide	81.0	95.0	14.0	1.29	0.25
	sulfide	144.0	148.0	4.0	0.13	0.14
	sulfide	207.0	210.0	3.0	0.15	0.26
PXE-415	oxide	31.0	33.0	2.0	0.33	0.03
PXE-416	sulfide	80.0	106.0	26.0	0.49	0.09
	sulfide	96.0	102.0	6.0	1.02	0.21
PXE-417	oxide	79.0	92.0	13.0	0.62	0.09
	sulfide	92.0	103.0	11.0	0.99	0.11
	sulfide	93.0	100.0	7.0	1.42	0.16
PXE-418	oxide	93.2	97.0	3.8	1.03	0.14
	sulfide	97.0	108.0	11.0	1.07	0.16
PXE-419	oxide	54.0	80.0	26.0	0.50	0.05
	oxide	57.0	72.0	15.0	0.66	0.07
	sulfide	81.0	102.0	21.0	0.25	0.01
	sulfide	91.0	94.0	3.0	0.51	0.02
	sulfide	124.0	130.0	6.0	1.08	1.96
PXE-420	oxide	42.0	46.0	4.0	0.20	0.28
	oxide	63.0	88.0	25.0	0.88	0.09
	oxide	64.0	77.0	13.0	1.32	0.17
	oxide	98.0	106.0	8.0	0.37	0.06
PXE-421	oxide	52.0	58.0	6.0	0.26	0.02
	oxide	56.0	58.0	2.0	0.56	0.02
	oxide	74.7	76.5	1.8	0.51	0.04
	sulfide	120.0	208.0	88.0	0.58	0.09
	sulfide	121.0	128.0	7.0	1.90	0.31
	sulfide	156.0	181.0	25.0	0.86	0.13
	sulfide	190.0	199.0	9.0	0.65	0.07
	sulfide	206.0	208.0	2.0	1.38	0.20

Significant Drill Hole Intersections El Espino Project, April - June 2010

Drill Hole	Type	From	To	width	Cu%	Au g/t
PXE-422	sulfide	88.0	90.0	2.0	1.51	0.84
	sulfide	96.0	97.0	1.0	2.09	0.05
	sulfide	160.0	162.0	2.0	0.48	0.03
	sulfide	168.0	188.0	20.0	0.35	0.09
	sulfide	172.0	183.0	11.0	0.55	0.13
	sulfide	200.0	248.0	48.0	0.58	0.05
	sulfide	213.0	247.0	34.0	0.74	0.06
	sulfide	213.0	221.0	8.0	1.37	0.06
PXE-423	sulfide	225.0	234.0	9.0	0.78	0.10
	sulfide	124.0	134.0	10.0	0.47	0.04
	sulfide	126.0	133.0	7.0	0.61	0.05
	sulfide	154.0	156.0	2.0	0.83	0.06
	sulfide	171.0	186.0	15.0	0.37	0.02
	sulfide	174.0	179.0	5.0	0.61	0.02
	sulfide	198.0	210.0	12.0	0.67	0.08
	sulfide	201.0	209.0	8.0	0.95	0.11
PXE-424	sulfide	213.0	256.0	43.0	0.87	0.33
	sulfide	213.0	218.0	5.0	3.36	0.57
	sulfide	56.0	59.0	3.0	0.45	0.02
PXE-425	sulfide	71.0	73.0	2.0	0.33	0.05
	sulfide	136.0	138.0	2.0	0.58	0.09
	oxide	77.0	98.0	21.0	0.48	0.05
PXE-426	oxide	77.0	85.3	8.3	0.86	0.11
	sulfide	113.6	118.0	4.4	0.37	0.38
	sulfide	70.0	114.0	44.0	0.27	0.07
PXE-427	sulfide	82.0	88.0	6.0	0.87	0.07
	sulfide	118.0	164.0	46.0	0.67	0.25
	sulfide	121.0	138.0	17.0	1.02	0.22
	sulfide	238.0	273.0	35.0	0.53	0.10
	sulfide	238.0	253.0	15.0	0.80	0.11
	sulfide	268.0	272.0	4.0	0.98	0.26
	sulfide	314.6	377.3	62.6	0.00	0.94
	sulfide	314.6	336.0	21.4	0.00	1.87
	sulfide	314.6	319.8	5.1	0.00	3.36
	sulfide	325.0	336.0	11.0	0.00	2.00
	sulfide	353.0	359.0	6.0	0.00	2.04
	sulfide	376.0	377.3	1.3	0.00	1.27
PXE-427	sulfide	74.0	107.0	33.0	1.96	0.58
	sulfide	82.0	106.0	24.0	2.52	0.76
	sulfide	89.0	106.0	17.0	3.23	1.01
	sulfide	110.0	114.0	4.0	0.44	0.14
	sulfide	126.0	128.0	2.0	0.46	0.03
	sulfide	215.0	218.0	3.0	0.02	1.00
	sulfide	236.0	238.2	2.2	0.44	0.19

Significant Drill Hole Intersections El Espino Project, April - June 2010

Drill Hole	Type	From	To	width	Cu%	Au g/t
PXE-428	mixed	29.0	33.0	4.0	0.72	0.19
	sulfide	33.0	45.0	12.0	0.57	0.14
	sulfide	59.0	100.0	41.0	0.73	0.21
	sulfide	72.0	90.0	18.0	1.36	0.37
	sulfide	110.0	130.0	20.0	0.30	0.06
	sulfide	115.0	120.0	5.0	0.78	0.13
	sulfide	137.0	139.0	2.0	0.44	0.06
	sulfide	202.0	206.0	4.0	0.28	0.50
	sulfide	204.0	206.0	2.0	0.41	0.93
PXE-429	sulfide	93.0	138.0	45.0	1.03	0.15
	sulfide	94.0	104.0	10.0	2.52	0.42
	sulfide	134.0	138.0	4.0	1.19	0.11
	sulfide	150.0	265.5	115.5	0.58	0.10
	sulfide	231.0	245.0	14.0	1.15	0.29
	sulfide	252.0	264.0	12.0	1.20	0.21
PXE-430	oxide	121.1	130.4	9.3	0.74	0.10
	sulfide	130.4	157.0	26.6	1.13	0.45
	sulfide	130.4	149.0	18.6	1.45	0.58
PXE-431	oxide	94.0	151.5	57.5	0.90	0.22
	oxide	96.0	121.0	25.0	1.81	0.33
	sulfide	168.0	174.0	6.0	0.25	0.11
	sulfide	202.0	216.0	14.0	0.27	0.17
	sulfide	213.0	216.0	3.0	0.58	0.13
PXE-432	oxide	6.0	14.0	8.0	0.38	0.17
	oxide	34.0	54.0	20.0	1.18	0.97
	oxide	38.0	48.0	10.0	2.04	1.86
	oxide	38.0	42.0	4.0	3.05	3.25
	oxide	45.0	48.0	3.0	2.11	1.68
	oxide	62.0	66.0	4.0	0.44	0.09
	oxide	74.0	97.0	23.0	0.41	0.18
	oxide	89.0	95.0	6.0	0.92	0.46
	oxide	106.0	116.0	10.0	0.33	0.06
	oxide	152.0	158.0	6.0	0.24	0.05
	sulfide	159.0	164.0	5.0	0.27	0.07