

TABLE 1: 2016 DRILLING PROGRAM RESULTS									
Drillhole	Section	Azimuth	Total Length (m)	Intercepts	From (m)	To (m)	Core Intersection Length (m)	True Thickness (m)¹	Cg (%)
LT-16-17	2+00 N	302	135	Intersection	10.4	34.55	24.15	23.9	6.81
				Intersection	81.35	111.0	29.65	29.4	7.24
				<i>Including</i>	92.0	101.2	9.2	9.1	10.14
LT-16-18	2+00 N	302	129	Intersection	16.55	52.1	35.55	35.2	11.21
				<i>Including</i>	18.7	42.2	23.5	23.3	14.13
LT-16-19	2+00 N	302	126	Intersection	63.25	69.55	6.3	6.2	8.34
LT-16-34	1+00 S	302	150	Intersection	25.0	55.1	30.1	29.8	9.09
				<i>Including</i>	44.0	53.0	9.0	8.9	16.50
				Intersection	64.25	115.05	50.8	50.3	13.13
				<i>Including</i>	84.1	111.7	27.6	27.3	16.06
LT-16-33	3+00 S	302	156	Intersection	31.3	133.0	101.7	100.7	10.15
				<i>Including</i>	31.3	55.85	24.55	24.3	17.07
				<i>Including</i>	100.3	110.4	10.1	10.0	14.52
LT-16-32	5+00 S	302	159	Intersection	42.0	145.15	103.15	102.1	10.70
				<i>Including</i>	45.75	76.25	30.5	30.2	16.69
				<i>Including</i>	100.4	113.5	13.1	13.0	14.42
LT-16-31	7+00 S	302	147	Intersection	25.55	124.6	99.05	98.1	12.37
				<i>Including</i>	38.0	79.7	41.7	41.3	16.64
				<i>Including</i>	107.4	122.6	15.2	15.0	14.56
LT-16-20	8+00 S	302	150	Intersection	46.4	130.45	84.05	83.2	11.62
				<i>Including</i>	58.35	104.05	45.7	45.2	15.62
LT-16-21	8+00 S	302	126	Intersection	3.0	70.5	67.5	66.8	12.42
				<i>Including</i>	3.0	31.3	28.3	28.0	19.36
LT-16-30	9+00 S	302	147	Intersection	22.5	110.5	88.0	87.1	11.3
				<i>Including</i>	39.0	85.5	46.5	46.0	15.06
LT-16-23	10+00 S	302	144	Intersection	60.0	72.27	12.27	12.1	7.74
				Intersection	81.0	111.5	30.5	30.2	9.71
				<i>Including</i>	82.9	104.5	21.6	21.4	11.28
				Intersection	126.5	132.95	6.45	6.4	7.95
LT-16-24	10+00 S	302	123	Intersection	18.55	73.55	55.0	54.5	9.60
				<i>Including</i>	37.0	57.55	20.55	20.3	11.79
LT-16-27	12+00 S	302	156	Intersection	79.2	117.3	38.1	37.7	6.41
LT-16-28	12+00 S	302	126	Intersection	6.5	20.0	13.5	13.4	6.84
				Intersection	28.75	43.55	14.8	14.7	6.64
LT-16-29	12+00 S	302	114	Intersection	6.5	16.8	10.3	10.2	5.6

Mineralized intersections are calculated with Cg > 5% over a minimum of 6 m, the maximum internal dilution is 6 m and no external dilution is considered.

¹ Carbon analyses were performed by the Consortium de Recherche Appliquée en Traitement et Transformation des Substances Minérales (“COREM”) of Québec-City, an ISO/IEC 17025:2005 certified facility using LECO high frequency combustion method with infrared measurement (code LSA-M-B10) and are reported as graphitic carbon (Cg).

² True thicknesses are listed in this news release. The drill holes have been loaded into Gemcom and the three-dimensional deposit envelope has an azimuth of 210 degrees and dips at -40 degrees. HQ drill holes crosscut the envelope of the mineralized zone’ strike and dip at a high angle. The conversion factor for true thickness is 0.99 of the core intersection length.