

Table 2: Mexico Vein Drill Intercepts

HOLE ID	FROM (m)	TO (m)	LENGTH (m)	Ag g/t	PB (%)	ZN (%)	AgEq (g/t)
NAM-019	209	211	2	88	0.05	0.04	77
NAM-019	238.2	239.04	0.84	64	3.31	8.73	394
NAM-021	47	48	1	46	0.12	0.22	55
NAM-021	129	133	4.0	51	.04	0.01	53
NAM-021	140.3	140.52	0.22	111	0.09	0.04	115
NAM-021	145	145.95	0.95	96	0.05	0.33	106
NAM-021	204	205	1	221	0.02	0.18	227
NAM-026	323	324	1	8	2.29	1.55	113
NAM-026	444	457	13	43	0.59	1.54	101
Including	447	448.06	1.06	87	0.09	0.43	101
Including	448.06	448.52	0.46	256	0.04	0.09	259
Including	449.22	449.71	0.49	212	0.04	0.05	214
including	449.71	450.26	0.55	88	0.70	2.45	175
including	450.26	451	0.74	62	1.80	14.20	501
NAM-030	266	267.5	1.5	19	0.57	3.86	141
NAM-030	371.55	379.37	8.72	12.5	1.34	1.23	85
NAM-030	494	495	1	73	5.30	13.00	575
NAM-030	504	505	1	42	0.30	2.19	110
NAM-030	514	515.4	1.4	27	0.74	7.69	198
NAM-030	542.54	543.1	0.56	325	0.08	0.07	329

The Silver equivalent grades ("AgEq") have been calculated using metal prices of US\$25oz Silver; US\$1.00/lb Zinc; and US\$1.00/lb Lead. Metal recoveries are not considered in this calculation. Further drilling is required to provide a more accurate assessment of vein thickness and true width may vary.