

Table 3: El Gallo 2 Mill & Heap Leach Recoveries, Densities and Capping Grades by Zone

Resource Area	Silver Recovery (%)	Gold Recovery (%)	Density (t/m3)	Silver Capping (gpt)	Gold Capping (gpt)
El Gallo Deposit - Mill*	87.6	79.2	2.50	-	-
El Gallo Deposit - Heap Leach	60.0	60.0	2.50	-	-
Palmarito In Situ	73.6	88.4	2.58	-	-
Palmarito Tailings	54.2	63.9	1.51	-	-
Palmarito Dumps	88.8	82.4	2.00	-	-
Chapotillo	88.0	91.1	2.49	350	3.5
Haciendita	81.4	95.0	2.60	100/200	-
Mina Grande	61.8	80.5	2.60	70/200/-	7/7.7/20
Mina Grande Tailings	72.6	80.1	1.47	-	-
Los Mautos	85.0	75.0	2.47	-	-
San Jose del Alamo**	35.0	70.0	2.50	50	10
Las Milpas	85.0	75.0	2.51	-	-
CSX	85.0	75.0	2.36	2300	-

*El Gallo Deposit search radius was reduced to an average 19 meter influence for composites greater than three standard deviations above the mean. This method was employed versus grade capping.

**San Jose del Alamo used heap leaching to establish recoveries