

Table 2 Inferred Resource Estimate for the Strange Lake B Zone Deposit; Individual Oxides of the TREO.

TREO% Cut-off	Tonnes (x000 t)	La ₂ O ₃ %	Ce ₂ O ₃ %	Pr ₂ O ₃ %	Nd ₂ O ₃ %	Sm ₂ O ₃ %	Eu ₂ O ₃ %	Gd ₂ O ₃ %	Tb ₂ O ₃ %	Dy ₂ O ₃ %	Ho ₂ O ₃ %	Er ₂ O ₃ %	Tm ₂ O ₃ %	Yb ₂ O ₃ %	Lu ₂ O ₃ %	Y ₂ O ₃ %
1.20%	11,809	0.148	0.316	0.036	0.124	0.033	0.002	0.038	0.009	0.066	0.015	0.046	0.008	0.046	0.006	0.461
1.10%	21,757	0.143	0.305	0.034	0.120	0.032	0.002	0.035	0.009	0.059	0.013	0.041	0.007	0.041	0.005	0.413
1.00%	40,388	0.139	0.296	0.033	0.116	0.030	0.002	0.032	0.008	0.052	0.012	0.035	0.006	0.037	0.005	0.360
0.95%	54,560	0.137	0.291	0.032	0.114	0.028	0.002	0.030	0.007	0.048	0.011	0.033	0.006	0.034	0.004	0.334
0.90%	82,541	0.134	0.282	0.031	0.110	0.027	0.002	0.028	0.006	0.044	0.010	0.030	0.005	0.031	0.004	0.302
0.85%	114,823	0.132	0.274	0.030	0.107	0.026	0.002	0.027	0.006	0.041	0.009	0.028	0.005	0.029	0.004	0.281
0.80%	133,654	0.130	0.269	0.030	0.105	0.025	0.001	0.026	0.006	0.039	0.009	0.027	0.005	0.028	0.004	0.271
0.70%	137,639	0.129	0.268	0.030	0.105	0.025	0.001	0.026	0.006	0.039	0.009	0.027	0.005	0.028	0.004	0.269