

**Table 1: Kamila Zone - Inca Vein Drilling Summary of Recent Results**

Hole ID	Easting (m)	Northing (m)	Depth (m)	Az	Dip	From (m)	To (m)	Length* (m)	True Width TW (m)	Gold Grade (g/t)	Silver Grade (g/t)	Grade (g/t) (Au_eq)	Interval (m at g/t Au_eq) - Vein
CA-11-304	2439457	6547732	461.50	45	-72	328.00	328.90	0.90	0.49	0.82	131	2.69	1.50m at 1.01g/t gold & 198g/t silver or 3.83g/t Au_eq from 328m (Inca Vein)
						328.90	329.50	0.60	0.33	1.29	298	5.55	
						419.50	420.30	0.80	0.43	0.53	155	2.74	
						420.30	421.05	0.75	0.41	1.38	415	7.31	
						421.05	421.70	0.65	0.35	0.56	169	2.97	
						421.70	422.55	0.85	0.46	2.05	645	11.26	
CA-11-305	2439531	6547708	439.40	45	-65	387.20	388.20	1.00	0.57	3.99	184	6.62	1.00m at 3.99g/t gold & 184g/t silver or 6.62g/t Au_eq from 387.20 (Inca Vein) Preliminary
CA-11-306	2439549	6547693	360.40	45	-60	308.50	309.55	1.05	0.72	52.00	7210	155.00	5.90m at 15.80g/t gold & 2610g/t silver or 53.09g/t Au_eq from 308.50m (Inca Vein). Best individual Interval 308.50m – 309.55m: 1.05m at 52g/t gold & 7210g/t silver or 155.0g/t Au_eq Preliminary
						309.55	310.25	0.70	0.48	3.91	904	16.82	
						310.25	310.75	0.50	0.34	4.00	837	15.96	
						310.75	311.40	0.65	0.44	2.50	568	10.61	
						311.40	312.05	0.65	0.44	0.08	20	0.37	
						312.05	312.70	0.65	0.44	8.57	1030	23.28	
						312.70	313.30	0.60	0.41	30.91	6624	125.54	
						313.30	313.85	0.55	0.37	12.33	2564	48.96	
						313.85	314.40	0.55	0.37	2.38	621	11.25	
						319.95	320.50	0.55	0.37	2.32	417	8.28	

Note: (\*) The column length represents downhole widths

1. Au\_eq grade calculated using a gold to silver ratio of 1:70. As per May 2010 Current Casposo NI-4310 Technical Report

The gold equivalent cut-off was determined according to the parameters below:

- Au/Ag ratio 1:70.00
- Au Price US\$933.33/oz
- Ag Price US\$15.50/oz
- Au processing recovery 93.7%
- Ag processing recovery 80.6%

Gold equivalency is determined by metal price and recovery factors.

Metal prices are the average prices assumed in the Casposo life of mine plan..

Processing recoveries were determined by metallurgical testwork carried out by independent consultants on diamond drill core from Casposo.

The equivalency is calculated by the formula:

$$\text{Gold: Silver ratio} = (\text{gold price} \div \text{silver price}) \times (\text{gold recovery} \div \text{silver recovery})$$

$$= (933.33 \div 15.5) \times (.937 \div .806)$$

$$= 70.00$$

Gold equivalency is calculated by the formula: Au\_eq g/t = Au g/t + (Ag g/t ÷ 70.00)

2. NSR – No significant Results All samples were prepared and assayed by Alex Stewart (Assayers) Argentina Laboratory in Mendoza Argentina.

3. Gold by FA and either a gravimetric or AAS finish, using method gold 4-50 or gold 4A-50 for samples with gold>10g/t

4. Silver by three techniques: four-acid digestion followed by AAS reading for check samples up to February 2006, aqua regia digestion followed by inductively coupled plasma with optical emission spectroscopy (ICP-OES) reading for all samples in mineralised intersections after February 2006.

Method numbers were GMA, ICP-AR-39 and silver 4A-50.