

**Table 1: Kamila Zone – Inca Vein Drilling Summary of Results**

Hole ID	Easting (m)	Northing (m)	Depth (m)	Az	Dip	From (m)	To (m)	Length* (m) (Downhole)	Gold Grade (g/t)	Silver Grade (g/t)	Grade (g/t) (Au_eq)	(**) Estimated True Width of Intercept	Interval (m at gold g/t and g/t silver or g/t Au_eq)
CA-11-318	2439530	6547707	380.60	45°	-63°	342.15	343.00	0.85	17.24	1310	35.95	7.71	8.25m at 8.33g/t gold and 817.79g/t silver or 20.02g/t Au_eq from 342.15m incl 2.8m at 17.23g/t gold and 965.6g/t silver or 31.03g/t Au_eq from 342.15m and 2.55m at 7.78g/t gold and 1534.3g/t silver or 29.70g/t Au_eq from 347.85m
						343.00	343.95	0.95	23.61	1156	40.12		
						343.95	344.95	1.00	11.17	492	18.20		
						344.95	345.80	0.85	0.09	25	0.45		
						345.80	346.70	0.90	0.17	37	0.70		
						346.70	347.30	0.60	0.51	68	1.48		
						347.30	347.85	0.55	0.23	64	1.14		
						347.85	348.35	0.50	1.27	543	9.03		
						348.35	348.85	0.50	32.97	6168	121.08		
						348.85	349.40	0.55	2.89	571	11.05		
349.40	350.40	1.00	1.12	243	4.59								
CA-11-319	2439530	6547744	447.5	45°	-70°	413.55	414.50	0.95	0.08	7	0.18	3.03	3.45m at 0.10g/t gold, 15.61 g/t silver or 0.32g/t Au_eq from 413.45m
						414.50	415.40	0.90	0.15	12	0.32		
						415.40	416.00	0.60	0.08	14	0.28		
						416.00	417.00	1.00	0.09	28	0.49		
CA-11-320	2439519	6547808	324.0	45°	-75	246.80	247.45	0.65	0.14	31	0.58	1.41	1.65m at 0.32g/t gold and 22.5 g/t silver or .64 g/t Au_eq from 246.8m
						247.45	248.45	1.00	0.44	17	0.68		
CA-11-321	2439501	6547750	401.0	45°	-65	261.10	262.15	1.05	0.13	15	0.34	1.9	2.00m at 0.09g/t gold and 9.3g/t silver or 0.22 g/t Au_eq from 261.1m
						262.15	263.10	0.95	0.05	3	0.09		
CA-11-322	2439444	6547764	422.2	45°	-75°	358.60	360.10	1.50	0.04	9	0.17	1.77	2.10m at 0.03g/t gold and 12.4g/t silver or 0.21g/t Au_eq from 358.6m
						360.10	360.70	0.60	0.02	21	0.32		
CA-11-323	2439501	6547750	317.00	45°	-68°	289.00	289.95	0.95	26.98	4514	91.47	8.31	9.00m at 10.98g/t gold and 1320.2g/t silver or 29.84 g/t Au_eq from 289m including 2.4m at 40.51g/t gold and 4800.3g/t silver or 109.08g/t Au_eq from 289.0m
						289.95	290.70	0.75	20.00	3486	69.8		
						290.70	291.40	0.70	80.84	6597	175.1		
						291.40	292.35	0.95	0.47	157	2.71		
						292.35	293.50	1.15	0.10	34	0.59		
						293.50	294.10	0.60	0.11	29	0.52		
						294.10	295.00	0.90	0.12	25	0.48		
						295.00	295.95	0.95	0.20	46	0.86		
						295.95	296.60	0.65	0.27	47	0.94		
296.60	298.00	1.40	0.36	42	0.96								
CA-11-324	2439417	6547778	352.6	45°	-65°	305.90	306.90	1.00	0.05	1	0.06	3.32	3.55m at 0.04g/t gold and 7,15g/t silver or 0.09 g/t Au_eq from 305.9m
						306.90	307.60	0.70	0.02	18	0.28		
						307.60	308.60	1.00	0.05	5	0.12		

						308.60	309.45	0.85	0.03	8	0.14		
CA-11-325	2439403	6547807	332.50	45°	-63°	302.50	303.05	0.55	0.42	131	2.29	3.42	3.65m at 2.32g/t gold and 850.6g/t silver or 14.47 g/t Au_eq from 302.5m
						303.05	303.80	0.75	0.05	17	0.29		
						303.80	304.35	0.55	6.80	1927	34.33		
						304.35	305.25	0.90	0.06	32	0.52		
						305.25	306.15	0.90	4.88	2146	35.54		
CA-11-326	2439569	6547677	372.40	33°	-63°	342.80	343.25	0.45	4.65	2048	33.91	10.36	11.2m at 2.66g/t gold and 539.98g/t silver or 10.37g/t Au_eq from 341.5m including 9.9m at 2.99g/t gold and 602.62g/t silver or 11.59g/t Au_eq from 342.8m and 3.10m at 8.31g/t gold and 1433.7g/t silver or 28.7g/t Au_eq from 342.8m
						343.25	344.15	0.90	3.66	1733	28.42		
						344.15	345.00	0.85	0.32	103	1.79		
						345.00	345.90	0.90	22.34	2084	52.11		
						345.90	347.00	1.10	0.27	93	1.60		
						347.00	347.85	0.85	0.23	49	0.93		
						347.85	348.55	0.70	2.46	1195	19.53		
						348.55	349.15	0.60	0.73	421	6.74		
						349.15	349.70	0.55	0.03	14	0.23		
						349.70	350.55	0.85	0.69	221	3.85		
						350.55	351.40	0.85	0.09	22	0.40		
						351.40	352.10	0.70	0.29	64	1.20		
						352.10	352.70	0.60	0.43	49	1.13		

Note: (\*) The column "Length" represents downhole length of core drilled that comprises the sample interval or assay interval

NSR – No Significant Results

Au\_eq grade calculated using gold to silver ratio of 1:70. As per May 2010 Current Casposo NI-4310 Technical Report. The gold equivalent cut-off was determined according to the parameters below:

Au/Ag ratio 1:70.00

Au Price US\$933.33/oz

Ag Price US\$15.50/oz

Au processing recovery 93.7%

Ag processing recovery 80.6%

Gold equivalency is determined by metal price and recovery factors.

Metal prices are the average prices assumed in the Casposo life of mine plan.

Processing recoveries were determined by metallurgical testwork carried out by independent consultants on diamond drill core from Casposo.

The equivalency is calculated by the formula:

$$\begin{aligned} \text{Gold:Silver ratio} &= (\text{gold price} \div \text{silver price}) \times (\text{gold recovery} \div \text{silver recovery}) \\ &= (933.33 \div 15.5) \times (.937 \div .806) \\ &= 70.00 \end{aligned}$$

Gold equivalency is calculated by the formula: Au\_eq g/t = Au g/t + (Ag g/t ÷ 70.00)

NSR – No significant Results All samples were prepared and assayed by Alex Stewart (Assayers) Argentina Laboratory in Mendoza Argentina.

Gold by FA and either a gravimetric or AAS finish, using method gold 4-50 or gold 4A-50 for samples with gold>10g/t

Silver by three techniques: four-acid digestion followed by AAS reading for check samples up to February 2006, aqua regia digestion followed by inductively coupled plasma with optical emission spectroscopy (ICP-OES) reading for all samples in mineralised intersections after February 2006. Method numbers were GMA, ICP-AR-39 and silver 4A-50.

(\*\*) The column "Estimated True Width" is an estimate only based on current knowledge of the geometry of the mineralised zone.

Estimated True Width Calculation Methodology

$$T = AB ((\sin a \times \cos b) - (\cos a \times \sin b \times \cos c))$$

T = true width

AB = drillhole intersection length

a = dip of the drill hole

b = dip of the formation

c = angle between the direction of the dip of the Vein and the bearing of the hole. ( c = Drill Hole Dip Direction - Bed/Vein Dip Direction)