

# Figure 1. Tumipampa Cross Cut : localization, sampling and mineralization of the Manto Dorado Structure



Roof Wall

Width (m)	Au (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
4.85	36.48	1.49	0.43	0.08	0.12

North Hanging Wall

Width (m)	Au (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
4.90	22.35	1.15	0.29	0.11	0.25

North Bottom Wall

Width (m)	Au (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
2.50	2.31	0.11	0.01	0.04	0.11

South Hanging Wall

Width (m)	Au (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
4.75	21.26	0.54	0.04	0.04	0.05

South Bottom Wall

Width (m)	Au (g/t)	Ag (oz/t)	Cu (%)	Pb (%)	Zn (%)
2.65	1.98	0.06	0.01	0.02	0.06

82.1 g/t Au over 0.40 meters  
111.5 g/t Au over 0.75 meters

Gold mineralization in low grade veinlets

## Manto Dorado ( Width. 7.40 m)

cut-out in red from floor to ceiling

Composed of abundant pyrite, quartz, calcite, chalcopryrite, specularite, aragonite and sericite

Located in gray quartzite rock altered by silicification

Soraya Quartz Formation
  Altered Grey Quartzite
  Polymetallic Mineralized Manto Dorado

Fault  
 Vein